

3 March 2025

## CONFIRMATION DRILLING RESULTS SUPPORT MODEL AT MURCHISON SOUTH

### HIGHLIGHTS

- All 14 holes drilled, successfully intersected gold at the Company's Murchison South gold project.
- Drilling provides continuity and validation against historical drilling.
- Significant assay results from this program include (down hole widths):
  - 25PFRC001 (Hole 1)  
**41m @ 2.01 g/t from surface; including  
15m @ 2.01 g/t from 2m, and  
5m @ 10.01 g/t from 36m**
  - 25PFRC002 (Hole 2)  
**22m @ 0.70 g/t from 33m; including  
10m @ 1.05 g/t from 33m, and  
1m @ 1.61 g/t from 45m**
  - 25PFRC003 (Hole 3)  
**9m @ 1.32 g/t from 50m; including  
1m @ 6.59 g/t from 52m, and  
1m @ 2.53 g/t from 55m**
  - 25PFRC005 (Hole 5)  
**9m @ 1.07 g/t from 58m; including  
1m @ 4.85 g/t from 60m**
- Significant assay results from historical drilling include (down hole widths):\*
  - **12m @ 6.61 g/t from 10m** PFRC116 (Hole 116)
  - **2m @ 50.5 g/t from 22m** PFRC049 (Hole 49)
  - **7m @ 2.43 g/t from 26m** PFRC115 (Hole 115)
  - **3m @ 92.1 g/t from 41m including 1m @ 271 g/t from 42m** PFRC120 (Hole 120)
  - **3m @ 8.04 g/t from 45m & 3m @ 5.21 g/t from 140m** PFRC134 (Hole 134)
  - **3m @ 8.05 g/t from 77m & 2m @ 4.94 g/t from 82m** PFRC135 (Hole 135)
  - **4m @ 6.28 g/t from 79m & 6m @ 3.56 g/t from 120m** PFRC150 (Hole 150)
  - **4m @ 2.64 g/t from 99m** PFRC133 (Hole 33)

Reach Resources Limited (ASX: RR1 & RR10A) ("Reach" or "the Company") is pleased to announce all assays have now been received from its RC drill program at the Company's 100% owned Murchison South gold project, near Payne's Find, in the gold rich Murchison Mineral Field of WA (see Figure 1).

All 14 drill holes contained gold mineralisation. Mining Plus will now incorporate the latest drill data into their model, with a focus on pit optimization in high grade areas.

\*Refer to RR1 ASX Announcement Annual Report to shareholders 23/08/2021 and JORC tables below.

For personal use only




Figure 1: Murchison South Gold Project showing the Blue Heaven deposit with current and historic drilling.

Eleven (11) holes of the current drilling program were completed to test continuity against ~300 historical drill holes, and additionally to test the veracity of the interim mineralisation model constructed by Mining Plus. The focus remains on zones of high grade mineralisation with the aim being to define these areas within the Company's inferred resource and provide areas of focus for future mining development. Three (3) holes (25PFRC012 – 25PFRC014) were exploration holes designed to test the estimated position of the Primrose fault. All 14 holes contained gold mineralisation and were drilled at or close to the estimated position of the Primrose fault, on the contact between mafic schist and gneiss.

Significant intercepts and the drill collar details from the recent drill program are shown in Table 1 & 2 respectively below. All gold assay results can be found in Appendix A of JORC Table 1.

Importantly, we can now confirm the objective of the program has been met, as the results broadly support alignment with historical drill results and the interim mineralisation model developed by Mining Plus. Refer to Cross sections 1-3 below.

Commenting on the results CEO Jeremy Bower said:

*"We are very pleased with the results of this program as they align with and confirm the interpretation of the mineralisation from the model recently developed by Mining Plus. There are over 300 holes drilled at our Blue Heaven deposit, including high grade, shallow intersections and a JORC Inferred resource. Receiving validation of historical results gives the Company and Mining Plus confidence in the mineralisation model and the ability to continue moving towards development.*

*Mining Plus will now incorporate these results into their own model, and we will also choose samples to undergo initial metallurgical testing to begin to understand our potential gold recovery. Following this we will be provided with different potential pit shell scenarios at different grade cut offs based on certain economic parameters after which we plan to undertake a diamond drill program to provide material for further metallurgical testing and geotechnical assessment for potential future mining development.*

*This is an exciting time for the Company and our shareholders, and we look forward to sharing our progress as work continues."*

For personal use only




Figure 2: Cross Section 1 showing Au grades from current and historic drilling within the interim mineralisation model. Refer to RR1 ASX Announcement “Excellent Assay Results Support Resource Estimation” 1/11/2021 for historical drill results and JORC tables below.





Figure 1. Cross Section 2 showing Au grades from current drilling that align with the interim mineralisation model



The three cross-sections represent distinct mineralised zones across the mineralisation model. The drill holes validate the geological model, with most beginning in mafic schist, crossing the Primrose Shear contact, and terminating in gneiss. The cross-sections demonstrate strong correlation between the current drilling program and the interim mineralisation model, with only minor refinements required. Results support the interpretation of the deposit as a narrow-vein gold system within a low-grade envelope, aligning well with the data and described in previous reports as a structurally controlled quartz lode gold system striking 310°-360° dipping approximately west at ~70°, with high grade gold developed in shoots and fractures splaying from the lode system (Refer to RR1 ASX Announcement 28/10/20). Mining Plus is conducting a detailed analysis to further assess the relationship between the current and historic drilling. Exploration holes 25PFRC012-014 intersected only mafic schist and, despite encountering numerous quartz veins, did not identify a distinct fault zone, indicating that the Primrose Shear may lie further east in this area.

Table 1. Significant Intercepts of Recent Drilling

HOLE_ID	FROM	TO	INTERVAL (m)	FA-Au-g/t	Significant Intercepts (2m @ >1g/t / 1m @ > 2g/t)
25PFRC001	0	41	41	2.01	Including 15 m @ 2.01 g/t from 2 m and 5 m @ 10.01 g/t from 36 m
25PFRC002	33	55	22	0.70	Including 10 m @ 1.05 g/t from 33 m and 1 m @ 1.61 g/t from 45 m
25PFRC002	60	70	6	0.48	Including 2 m @ 1.48 g/t from 62 m
25PFRC002	77	93	16	0.31	Including 1 m @ 2.29 g/t from 84 m
25PFRC003	50	59	9	1.32	Including 1 m @ 6.59 g/t from 52 m and 1 m @ 2.53 g/t from 55 m
25PFRC004	0	16	16	0.77	Including 3 m @ 2.82 g/t from 9 m
25PFRC005	58	67	9	1.07	Including 1 m @ 4.85 g/t from 60 m
25PFRC008	77	103	26	0.54	Including 2 m @ 2.14 g/t from 87 m
25PFRC009	69	87	18	0.51	2 m @ 1.25 g/t from 84 m
25PFRC010	29	34	5	0.77	
25PFRC011	32	49	17	0.56	Including 3 m @ 1.19 g/t from 32 m and 2 m @ 1.67 g/t from 47 m
25PFRC011	65	71	6	0.67	Including 2 m @ 1.71 g/t from 65 m

Lower cut-off 0.1ppm Au, Minimum length 2m, Internal dilution 2m, Min. grade of final composite 0.5ppm, Max. waste 2m, no top-cut

For personal use only

Table 2. Drill collar details

HoleID	HoleType	EOH	Dip	Azimuth	Easting	Northing	RL
25PFRC001	RC	80.0	-60.0	90.0	566621.8	6764197.8	349.9
25PFRC002	RC	150.0	-60.0	90.0	566592.4	6764205.3	349.9
25PFRC003	RC	59.0	-60.0	90.0	566650.3	6764170.8	350.1
25PFRC004	RC	120.0	-62.0	90.0	566622.7	6764172.0	350.3
25PFRC005	RC	80.0	-60.0	90.0	566762.5	6764064.9	350.4
25PFRC006	RC	115.0	-63.0	90.0	566735.9	6764062.1	350.8
25PFRC007	RC	110.0	-60.0	90.0	566781.7	6764000.4	351.0
25PFRC008	RC	137.0	-62.0	90.0	566760.3	6763967.6	352.1
25PFRC009	RC	100.0	-64.0	90.0	566798.2	6763923.4	352.0
25PFRC010	RC	70.0	-64.0	90.0	566843.5	6763881.5	351.6
25PFRC011	RC	110.0	-64.0	90.0	566798.4	6763874.4	353.8
25PFRC012	RC	100.0	-62.0	60.0	566939.3	6763701.1	348.4
25PFRC013	RC	100.0	-62.0	60.0	567008.7	6763584.6	346.6
25PFRC014	RC	132.0	-62.0	60.0	567075.5	6763472.1	344.7

### Key Next Steps

- Mining Plus continue their independent mining review
- Conduct metallurgical test work
- Engage with mining contractors and processors

*This announcement has been authorised by the Board of Reach Resources Limited*

For further information please contact:

**Jeremy Bower**  
 Chief Executive Officer  
 Level 4, 216 St Georges Terrace  
 Perth, 6000 W.A  
[jeremy@reachresources.com.au](mailto:jeremy@reachresources.com.au)

-ENDS-

For personal use only

**About Reach Resources Limited**

Reach Resources is a critical mineral explorer with a large portfolio of tenements in the resource rich Gascoyne Mineral Field. Recent and historical exploration results have confirmed the presence of Lithium, REE and Manganese across the Company's land holdings.

However, the Company is distinct from other pure explorers by also having an Inferred Gold Resource at Payne's Find and an investment in a downstream patented technology that recycles the rare earth elements from the permanent magnets required in electric vehicles, wind turbines, hard disk drives and MRI machines (RECycle Inc.).

**Competent Person's Statement**

Information in this announcement that relates to exploration results is based on and fairly represents information and supporting documentation prepared and compiled by Mr David Tsiokos, who is a Member of the Australian Institute of Mining, Metallurgy and Petroleum. Mr Tsiokos is the Principal Geologist for Reach Resources Limited employed on a full-time basis and holds options in the company. Mr Tsiokos has sufficient experience, which is relevant to the style of mineralisation and type of deposit under consideration and to the activity which he is undertaking to qualify as a Competent Person, as defined in the 2012 Edition of the Australasian Code for Reporting Exploration Results, Mineral Resources and Ore Reserves. Mr Tsiokos consents to the inclusion in the announcement of the matters based on this information in the form and context in which it appears.

**No New Information**

Except where explicitly stated, this announcement contains references to prior exploration results, all of which have been cross-referenced to previous market announcements made by the Company. The Company confirms that it is not aware of any new information or data that materially affects the information included in the relevant market announcements.

**Forward Looking Statement**

This report contains forward looking statements concerning the projects owned by Reach Resources Limited. If applicable, statements concerning mining reserves and resources may also be deemed to be forward looking statements in that they involve estimates based on specific assumptions. Forward-looking statements are not statements of historical fact and actual events and results may differ materially from those described in the forward looking statements as a result of a variety of risks, uncertainties and other factors. Forward looking statements are based on management's beliefs, opinions and estimates as of the dates the forward looking statements are made and no obligation is assumed to update forward looking statements if these beliefs, opinions and estimates should change or to reflect other future developments.

For personal use only

**Appendix A: Table 1 Murchison South - JORC 2012 Sampling Techniques and Data.**

Criteria	JORC 2012 Explanation	Commentary
<p><b>Sampling Techniques</b></p>	<p>The nature and quality of sampling should be clearly defined, with specific reference to the techniques used, such as cut channels, random chips, or specialized industry-standard measurement tools that are suitable for the minerals being investigated. Examples of such tools include downhole gamma sondes or handheld XRF instruments. These examples should not be viewed as an exhaustive list, as the term "sampling" encompasses a wide range of methods depending on the type of exploration and the minerals targeted.</p> <p>It is essential to outline the measures taken to ensure the representativity of the samples, ensuring that they accurately reflect the mineralization present. This includes proper procedures for sample collection, handling, and processing. Additionally, all measurement tools or systems used must be appropriately calibrated to meet industry standards, and the calibration process should be clearly documented to confirm the reliability and accuracy of the data.</p>	<p><i>11 definition and 3 exploration drill holes were drilled at Murchison South and were sampled by an RC rig, using a cyclone and cone splitter into two calico bags, one was sent to the lab with the sample number printed on it, the other has the meter number written on it and stored in reserve. Each calico bag was put onto the same chute throughout the drilling program. Samples were collected at 1m intervals to collect a ~2.5kg sample. The reject sample was collected by bucket and piled into rows of 10 or 20. 1588 samples from 14 drill holes were assayed for Au using fire assay method (FA50/OE04), 492 samples were tested for Au using photon assay method, and 995 samples were tested for Ag, As, Bi, Cu, Pb, S, Sb, Te, Zn using 4 acid ICPOES or ICPMS at Intertek labs Perth.</i></p>
	<p>The determination of mineralization, which is material to the public report, should also be included. In cases where standard industry methods are followed, a straightforward description may suffice, such as "reverse circulation drilling was used to obtain 1-meter samples, from which 3 kg was pulverized to produce a 30 g charge for fire assay." However, where more complex sampling challenges exist—such as with coarse gold that may present inherent sampling issues—additional details may be required to explain how these challenges were addressed. For unusual commodities or mineralization types, such as submarine nodules, more detailed information on the sampling methods should be disclosed to ensure the clarity and reliability of the report.</p>	<p><i>Historic Drilling</i>  <i>The historic drill holes are reported in Reach Resources company announcements with their requisite JORC Tables: Annual Report to shareholders 23/08/2021, Excellent Assay Results Support Resource Estimation 1/11/2021, Annual Report to Shareholders 28/10/2020</i></p> <p><i>In addition, WAMEX Reports A97485 (2012), A101749 (2014) report drill holes PFRC100-PFRC150, PFGDD01-06 and PFRC003-PFRC070 including techniques, sampling and methodology.</i></p> <p><i>Note: Drill holes with the ID format CXX, where 'X' is an integer were omitted from this report and cross sections as they were drilled in 1987 prior to JORC 2004 and had undergone human selection of samples, often having one or two assays in the entire drill hole. They made the cross sections unduly busy and complicated and therefore omitted. The interpretation of the geology or grade model is not affected by their removal.</i></p>
	<p>Include reference to measures taken to ensure representativity samples and the appropriate calibration of any measurement tools or systems used.</p>	<p><i>Sampling for geochemical analysis was continuous down the length of each hole with 1 sample collected every meter. The cyclone was cleaned after every 6m rod. A geologist was supervising drilling at all times. The calico bag sent for assay was placed on the same chute on the cone splitter throughout the program. The samples were weighed at regular intervals. The drill head was lifted off when the sample was taken to minimise smearing.</i></p>
	<p>Aspects of the determination of mineralisation that are Material to the Public Report.</p>	<p><i>For the interim mineralisation model - Low-grade mineralisation is defined as <math>\geq 0.22</math> ppm Au, while high-grade mineralization is <math>\geq 0.9</math> ppm Au, based on statistical analysis of historical assay results conducted by Mining Plus.</i></p>
<p><b>Drilling Technique</b></p>	<p>Drill type (eg core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc.) and details (e.g. core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc.).</p>	<p><i>A truck mounted RC percussion rig (OX SR 72) was utilized from surface to end of hole. This rig was used to drill all 14 drill holes. All RCholes were down-hole surveyed using a North Seeking Gyro (multi-shot) every ten meters. Holes were drilled at -60° to -64° and aligned using a sighting compass and a Garmin GPS65s. The azimuth is 090° or 060°.</i></p>
<p><b>Drill Sample Recovery</b></p>	<p>Method of recording and assessing core and chip sample recoveries and results assessed.</p>	<p><i>Sample recoveries were visually assessed and documented for each meter.</i></p>
	<p>Measures taken to maximise sample recovery and ensure representative nature of the samples.</p>	<p><i>The cyclone and sample return hose were cleaned and cleared after every rod. Sample recovery was monitored by the geologist per meter interval. Both calico bags were weighed at regular intervals to monitor consistency in sample recovery. Sample recovery was excellent overall.</i></p>

For personal use only

For personal use only

	Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.	<i>This study is yet to be completed.</i>
<b>Logging</b>	Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies.  Whether logging is qualitative or quantitative in nature.	<i>Qualitative codes and descriptions were used to record geological data such as lithology, weathering, regolith, colour, chip percentage, texture, alteration, veins, minerals, prior to sampling.</i>
	Core photography	<i>Chip trays are photographed.</i>
	The total length and percentage of the relevant intersections logged.	<i>The total lengths of all holes have been geologically logged.</i>

<b>Criteria</b>	<b>JORC 2012 Explanation</b>	<b>Commentary</b>
<b>Sub-sampling techniques and sample preparation</b>	If core, whether cut or sawn and whether quarter, half or all core taken.	<i>No core was collected.</i>
	For all sample types, the nature, quality and appropriateness of the sample preparation technique.	<i>All pulp samples were prepared with standard crush then pulverisation techniques at Intertek Maddington (methods SP91, SP05 (for samples over 3kg)  50g subsample taken for fire assay  Photon assay samples were split into two sub samples of approximately 500g</i>
	Quality control procedures adopted for all sub-sampling stages to maximise representativity of samples.	<i>No sub sampling was done</i>
	Measures taken to ensure that the sampling is representative of the in situ material collected, including for instance results for field duplicate/second-half sampling.	<i>A total of 55 field duplicate samples were inserted through the assay batch at a rate of about 1 in 26 samples or 3.8% of the total samples. 1 in 20 were taken in mineralisation and 1 in 40 were taken in waste. Duplicate performance is yet to be determined.</i>
	Whether sample sizes are appropriate to the grain size of the material being sampled.	<i>Crystal size of the rock is broadly uniform in the gneiss 1-3mm. Samples were cone split to ensure even distribution of grain sizes. 2.5-3kg samples are appropriate for this grain size.</i>
<b>Quality of assay data and laboratory tests</b>	The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total.	<i>1588 samples from 14 drill holes were assayed for Au using fire assay method (FA50/OE04), 492 samples were tested for Au using photon assay method, and 995 samples were tested for Ag, As, Bi, Cu, Pb, S, Sb, Te, Zn using 4 acid ICP-OES or ICP-MS at Intertek labs Perth.</i>
	For geophysical tools, spectrometers, handheld XRF instruments, etc., the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc.	<i>No geophysical tools were used</i>
	Nature of quality control procedures adopted (e.g. standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (i.e. lack of bias) and precision have been established.	<i>A total of 55 certified reference standards, and 15 blanks were inserted evenly throughout the assay batch and at mineralised zones determined by the geologist. In addition to this, Intertek Genalysis has also included standard, duplicates and blanks to monitor the performance of the laboratory. The QA/QC analysis is yet to be completed.</i>

<b>Verification of sampling and assaying</b>	The verification of significant intersections by either independent or alternative company personnel.	<i>Results reviewed by the Principal Geologist, the CEO and board personnel.</i>
	The use of twinned holes.	<i>No holes in this program have been twinned. Some historic holes are in close proximity to the holes drilled in this program to compare historic results with this program.</i>
	Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.	<i>Primary data is stored both in its source electronic form. Assay data is retained in both the original certificate (.pdf) form, where available, and the csv files received from the laboratory. Primary data was entered in the field into a portable logging device using standard drop-down codes. At this early stage, text data files are exported and stored in a database on the company server which is backed-up to cloud-based storage each day. Micromine software is used to check and validate drill-hole data.</i>
	Discuss any adjustment to assay data.	<i>Assay data for Au is reported in parts per million (ppm) or the equivalent measurement of grams per ton (g/t). Ag, As, Bi, Cu, Pb, S, Sb, Te, Zn are given in ppm</i>

<b>Criteria</b>	<b>JORC 2012 Explanation</b>	<b>Commentary</b>
<b>Location of data points</b>	Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.	<i>The collar positions were surveyed by dGPS using Survey control: GPS base set on SSM NIN72, with check to SSM NIN132 and a Trimble R10 in RTK mode in GDA2020, Zone 50 datum. dGPS locations are accurate to 20mm horizontal and 30mm vertical relative to Survey Control.</i>
	Specification of the grid system used.	<i>GDA2020 Zone 50 datum.</i>
	Quality and adequacy of topographic control.	<i>Relative level was recorded from the dGPS</i>
<b>Data spacing and distribution</b>	Data spacing for reporting of Exploration Results.	<i>The drill holes were positioned in areas considered to be most effective in validating the interim mineralisation model. Within the identified mineralised zone the drill holes were approximately positioned 30m spacing between drill holes and 50m spacing between drill lines.</i>
	Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.	<i>The drill spacing and distribution was advised by Mining Plus Consultants in order to be used to validate historic drilling based on an interim mineralisation model and deemed sufficient to establish the degree of geological and grade continuity appropriate for resource estimation.</i>
	Whether sample compositing has been applied.	<i>Sample compositing was not applied</i>

Criteria	JORC 2012 Explanation	Commentary
<b>Orientation of data in relation to geological structure</b>	Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.	<i>Drill orientation for the validation holes was consistent with most of the historic drilling and the interim mineralisation model (090°). However, the model varies in orientation and the angle of intercept differs between drill lines. This is most pronounced in drill lines 1 and 2 (25PFRC001-004) where the angle of intercept is ~65°, this increases to ~80° (near perpendicular) in drill lines 3 – 7 (25PFRC005-011). The exploration holes targeted the Primrose fault at 060° and are approximately perpendicular to this structure.</i>
	If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.	<i>This will be assessed once all assays are returned</i>
<b>Sample security</b>	The measures taken to ensure sample security.	<i>Samples were packed into polyweave bags immediately after logging and cable tied shut. The samples were then put into bulka bags at the end of the day. Bulka bags were freighted to Intertek labs using a private courier.</i>
<b>Audits or reviews</b>	The results of any audits or reviews of sampling techniques and data.	<i>No external audits or reviews have yet been completed</i>

#### Appendix 1: Table 2 Murchison South - JORC 2012 Reporting of Exploration Results

Criteria	JORC 2012 Explanation	Commentary
<b>Mineral tenement and land tenure status</b>	Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings.	<i>Murchison South drilling is located within M59/769 situated at Paynes Find, 340km NNE of Perth.. M59/769 is 100% owned by Cervantes Gold PTY LTD which is a wholly owned subsidiary of Reach Resources Ltd.</i>
	The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area.	<i>There are no known impediments to operating on this tenement.</i>
<b>Exploration done by other parties</b>	Acknowledgment and appraisal of exploration by other parties.	<i>Gold was first discovered at Paynes Find in 1911, leading to mining operations that continued until 1982. Several companies have since explored the area. Falcon Australia Limited (1987) conducted drilling programs targeting historical workings, including Carnation and Blue Heaven. Kirkwood Gold NL (1996–1998) drilled multiple holes on M59/10 and M59/244. Hallmark Mining Limited (2002) undertook drilling to test high-grade gold shoots below old workings. Paynes Find Gold Ltd (2011–2012) consolidated the tenements, conducted geological mapping, and completed a 3,800m RC drilling program, identifying gold-bearing quartz reefs. CSA Global and Ravensgate (2013–2015) performed structural and geological reviews, including the interpretation of mineralization controls.</i>
<b>Geology</b>	Deposit type, geological setting and style of mineralisation.	<p><i>The Archean greenstone rocks at Paynes Find comprise interlayered basaltic and dacitic metavolcanic sequences, with subordinate banded iron formations and ultramafic schists. These units have been intruded by strongly deformed granitoids, and the metamorphic grade ranges from upper greenschist to lower amphibolite facies. While the rocks are generally foliated, relic primary textures are commonly preserved.</i></p> <p><i>The basaltic metavolcanics include amygdaloidal lava, tuff, conglomerate, and differentiated flows with thin basal ultramafic horizons. Dacitic metavolcanics consist of massive amygdaloidal lava, banded and crystal tuff, and agglomerate.</i></p> <p><i>A hornblende-biotite-quartz-oligoclase tonalite gneiss at Paynes Find serves as the primary host for gold mineralization. The dominant host rock for auriferous quartz veins is a hornblende-biotite-quartz-feldspar gneiss, which exhibits a weak to strong foliation striking 300°–340° and dipping steeply westward at 60°–80°. The foliation maintains a relatively consistent N-S trend.</i></p>

		<p><i>Gold-bearing quartz veins are oriented roughly north-south, parallel to the dominant foliation, and dip steeply to the southwest with a consistent plunge direction. The mineralized shear zones are tight, reaching up to 2 meters in width, with limited rock alteration. Auriferous quartz veins occasionally split and display boudinage, with high-grade shoots extending along strike for up to 10 meters.</i></p> <p><i>Additional gold mineralization occurs along sheared contacts between mafic/ultramafic units and the gneissic rocks of the Paynes Find prospect. Late-stage pegmatite intrusions, locally known as "bars," crosscut the shear zones, displacing some of the quartz lodes.</i></p>
--	--	---

Criteria	JORC 2012 Explanation	Commentary
<b>Drill hole Information</b>	A summary of all information material to the understanding of the exploration results including a tabulation of survey information for all Material drill holes:	<i>Refer to the tables in this announcement</i>
<b>Data aggregation methods</b>	In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (e.g. cutting of high grades) and cut-off grades are usually Material and should be stated.	<i>No data aggregation methods have been applied</i>
	The assumptions used for any reporting of metal equivalent values should be clearly stated.	<i>No metal equivalent values have been applied</i>
<b>Relationship between mineralisation widths and intercept lengths</b>	These relationships are particularly important in the reporting of Exploration Results. If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported. If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (e.g. 'down hole length, true width not known').	<i>As reported above - Drill orientation for the validation holes was consistent with most of the historic drilling and the interim mineralisation model (090°). However, the model varies in orientation and the angle of intercept differs between drill lines. This is most pronounced in drill lines 1 and 2 (25PFRC001-004) where the angle of intercept is ~65°, this increases to ~80° (near perpendicular) in drill lines 3 – 7 (25PFRC005-011). The exploration holes targeted the Primrose fault at 060° and are approximately perpendicular to this structure. Until the interim mineralisation model is updated the true thickness on a cross section will not be fully understood and therefore 'down hole length' widths will be reported here.</i>
<b>Diagrams</b>	Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views.	<i>Cross sections of significant zones and a plan view map showing these sections are given in this announcement.</i>
<b>Balanced reporting</b>	Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.	<i>See text and tables to this announcement</i>  <i>Additional elements sampled Ag, As, Bi, Cu, Pb, S, Sb, Te, Zn were not published in this report as they provide no material impact to these results.</i>  <i>Drill holes PFRC012 and HPFRC21 were removed from cross section 3 as they interfere with each other and drill hole PFRC146 reducing clarity. Their removal has no material affect on the understanding of the cross section.</i>
<b>Other substantive exploration data</b>	Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater,	<i>No other studies have been completed yet.</i>

Criteria	JORC 2012 Explanation	Commentary
	geotechnical and rock characteristics; potential deleterious or contaminating substances.	
<b>Further work</b>	The nature and scale of planned further work (e.g. tests for lateral extensions or depth extensions or large-scale step-out drilling).	<i>Diamond drilling is planned for metallurgical testwork</i>

For personal use only

Appendix A - Full Assay Results

HOLE_ID	FROM	TO	SAMPLEID	Au_Method	Au-ppm
25PFRC001	0	1	M100001	FA50/OE	0.127
25PFRC001	1	2	M100002	FA50/OE	0.072
25PFRC001	2	3	M100003	FA50/OE	3.278
25PFRC001	3	4	M100004	FA50/OE	3.172
25PFRC001	4	5	M100005	FA50/OE	1.458
25PFRC001	5	6	M100006	FA50/OE	2.563
25PFRC001	6	7	M100007	FA50/OE	0.14
25PFRC001	7	8	M100008	FA50/OE	0.336
25PFRC001	8	9	M100009	FA50/OE	0.296
25PFRC001	9	10	M100010	FA50/OE	1.205
25PFRC001	10	11	M100011	FA50/OE	0.214
25PFRC001	11	12	M100012	FA50/OE	0.099
25PFRC001	12	13	M100013	FA50/OE	0.876
25PFRC001	13	14	M100014	FA50/OE	1.014
25PFRC001	14	15	M100015	FA50/OE	9.452
25PFRC001	15	16	M100016	FA50/OE	5.42
25PFRC001	16	17	M100017	FA50/OE	0.661
25PFRC001	17	18	M100018	FA50/OE	0.152
25PFRC001	18	19	M100019	FA50/OE	0.068
25PFRC001	19	20	M100020	FA50/OE	0.101
25PFRC001	20	21	M100021	FA50/OE	0.085
25PFRC001	21	22	M100022	FA50/OE	0.256
25PFRC001	22	23	M100023	FA50/OE	0.087
25PFRC001	23	24	M100024	FA50/OE	0.168
25PFRC001	24	25	M100027	FA50/OE	0.114
25PFRC001	25	26	M100028	FA50/OE	0.051
25PFRC001	26	27	M100029	FA50/OE	0.11
25PFRC001	27	28	M100031	FA50/OE	0.016
25PFRC001	28	29	M100032	FA50/OE	0.139
25PFRC001	29	30	M100033	FA50/OE	0.079
25PFRC001	30	31	M100034	FA50/OE	0.137
25PFRC001	31	32	M100035	FA50/OE	0.035
25PFRC001	32	33	M100036	FA50/OE	0.052
25PFRC001	33	34	M100037	FA50/OE	0.105
25PFRC001	34	35	M100038	FA50/OE	0.057
25PFRC001	35	36	M100039	FA50/OE	0.045
25PFRC001	36	37	M100040	FA50/OE	3.494
25PFRC001	37	38	M100041	FA50/OE	2.116
25PFRC001	38	39	M100042	FA50/OE	42.677
25PFRC001	39	40	M100043	FA50/OE	1.31
25PFRC001	40	41	M100044	FA50/OE	0.44
25PFRC001	41	42	M100045	FA50/OE	0.222
25PFRC001	42	43	M100046	FA50/OE	0.035
25PFRC001	43	44	M100047	FA50/OE	0.092
25PFRC001	44	45	M100048	FA50/OE	0.073
25PFRC001	45	46	M100049	FA50/OE	0.025
25PFRC001	46	47	M100052	FA50/OE	0.039
25PFRC001	47	48	M100053	FA50/OE	0.014
25PFRC001	48	49	M100054	FA50/OE	0.019
25PFRC001	49	50	M100055	FA50/OE	0.152
25PFRC001	50	51	M100056	FA50/OE	0.136
25PFRC001	51	52	M100057	FA50/OE	0.037
25PFRC001	52	53	M100058	FA50/OE	0.13
25PFRC001	53	54	M100059	FA50/OE	0.24
25PFRC001	54	55	M100060	FA50/OE	0.122
25PFRC001	55	56	M100061	FA50/OE	0.238
25PFRC001	56	57	M100062	FA50/OE	0.035
25PFRC001	57	58	M100063	FA50/OE	0.058
25PFRC001	58	59	M100064	FA50/OE	0.006
25PFRC001	59	60	M100065	FA50/OE	-0.02
25PFRC001	60	61	M100066	FA50/OE	0.008
25PFRC001	61	62	M100067	FA50/OE	0.037

For personal use only

For personal use only

25PFRC001	62	63	M100068	FA50/OE	0.008
25PFRC001	63	64	M100069	FA50/OE	0.012
25PFRC001	64	65	M100070	FA50/OE	0.025
25PFRC001	65	66	M100071	FA50/OE	0.006
25PFRC001	66	67	M100072	FA50/OE	-0.02
25PFRC001	67	68	M100073	FA50/OE	-0.02
25PFRC001	68	69	M100074	FA50/OE	-0.02
25PFRC001	69	70	M100077	FA50/OE	0.018
25PFRC001	70	71	M100078	FA50/OE	0.085
25PFRC001	71	72	M100079	FA50/OE	0.044
25PFRC001	72	73	M100080	FA50/OE	0.008
25PFRC001	73	74	M100081	FA50/OE	-0.02
25PFRC001	74	75	M100082	FA50/OE	0.016
25PFRC001	75	76	M100083	FA50/OE	0.024
25PFRC001	76	77	M100084	FA50/OE	0.024
25PFRC001	77	78	M100085	FA50/OE	-0.02
25PFRC001	78	79	M100086	FA50/OE	0.006
25PFRC001	79	80	M100087	FA50/OE	-0.02
25PFRC002	0	1	M100088	FA50/OE	0.106
25PFRC002	1	2	M100089	FA50/OE	0.061
25PFRC002	2	3	M100090	FA50/OE	0.053
25PFRC002	3	4	M100091	FA50/OE	0.332
25PFRC002	4	5	M100092	FA50/OE	0.126
25PFRC002	5	6	M100093	FA50/OE	0.834
25PFRC002	6	7	M100094	FA50/OE	0.063
25PFRC002	7	8	M100095	FA50/OE	0.033
25PFRC002	8	9	M100096	FA50/OE	0.111
25PFRC002	9	10	M100099	FA50/OE	0.018
25PFRC002	10	11	M100100	FA50/OE	0.018
25PFRC002	11	12	M100101	FA50/OE	0.081
25PFRC002	12	13	M100102	FA50/OE	0.022
25PFRC002	13	14	M100103	FA50/OE	0.022
25PFRC002	14	15	M100104	FA50/OE	0.025
25PFRC002	15	16	M100105	FA50/OE	0.015
25PFRC002	16	17	M100106	FA50/OE	0.049
25PFRC002	17	18	M100107	FA50/OE	0.139
25PFRC002	18	19	M100108	FA50/OE	0.045
25PFRC002	19	20	M100109	FA50/OE	0.157
25PFRC002	20	21	M100110	FA50/OE	0.191
25PFRC002	21	22	M100111	FA50/OE	0.094
25PFRC002	22	23	M100112	FA50/OE	0.022
25PFRC002	23	24	M100113	FA50/OE	0.028
25PFRC002	24	25	M100114	FA50/OE	0.025
25PFRC002	25	26	M100115	FA50/OE	0.016
25PFRC002	26	27	M100116	FA50/OE	0.029
25PFRC002	27	28	M100117	FA50/OE	0.008
25PFRC002	28	29	M100118	FA50/OE	0.01
25PFRC002	29	30	M100119	FA50/OE	-0.02
25PFRC002	30	31	M100120	FA50/OE	0.006
25PFRC002	31	32	M100121	FA50/OE	0.012
25PFRC002	32	33	M100122	FA50/OE	0.008
25PFRC002	33	34	M100123	FA50/OE	4.956
25PFRC002	34	35	M100124	FA50/OE	0.046
25PFRC002	35	36	M100125	FA50/OE	1.577
25PFRC002	36	37	M100126	FA50/OE	0.298
25PFRC002	37	38	M100127	FA50/OE	1.847
25PFRC002	38	39	M100128	FA50/OE	0.418
25PFRC002	39	40	M100129	FA50/OE	0.051
25PFRC002	40	41	M100130	FA50/OE	0.083
25PFRC002	41	42	M100131	FA50/OE	0.952
25PFRC002	42	43	M100132	FA50/OE	0.262
25PFRC002	43	44	M100133	FA50/OE	0.03
25PFRC002	44	45	M100136	FA50/OE	0.02

For personal use only

25PFRC002	45	46	M100137	FA50/OE	1.611
25PFRC002	46	47	M100138	FA50/OE	0.142
25PFRC002	47	48	M100139	FA50/OE	0.015
25PFRC002	48	49	M100140	FA50/OE	0.345
25PFRC002	49	50	M100141	FA50/OE	0.819
25PFRC002	50	51	M100142	FA50/OE	0.153
25PFRC002	51	52	M100143	FA50/OE	0.265
25PFRC002	52	53	M100144	FA50/OE	0.28
25PFRC002	53	54	M100145	FA50/OE	1.043
25PFRC002	54	55	M100146	FA50/OE	0.19
25PFRC002	55	56	M100147	FA50/OE	0.04
25PFRC002	56	57	M100148	FA50/OE	0.063
25PFRC002	57	58	M100149	FA50/OE	0.023
25PFRC002	58	59	M100150	FA50/OE	0.097
25PFRC002	59	60	M100152	FA50/OE	0.031
25PFRC002	60	61	M100153	FA50/OE	0.161
25PFRC002	61	62	M100154	FA50/OE	0.072
25PFRC002	62	63	M100155	FA50/OE	2.586
25PFRC002	63	64	M100156	FA50/OE	0.37
25PFRC002	64	65	M100157	FA50/OE	0.139
25PFRC002	65	66	M100158	FA50/OE	0.051
25PFRC002	66	67	M100159	FA50/OE	0.696
25PFRC002	67	68	M100160	FA50/OE	0.482
25PFRC002	68	69	M100161	FA50/OE	0.094
25PFRC002	69	70	M100162	FA50/OE	0.186
25PFRC002	70	71	M100163	FA50/OE	0.052
25PFRC002	71	72	M100164	FA50/OE	0.016
25PFRC002	72	73	M100165	FA50/OE	0.017
25PFRC002	73	74	M100166	FA50/OE	0.005
25PFRC002	74	75	M100167	FA50/OE	0.028
25PFRC002	75	76	M100168	FA50/OE	0.021
25PFRC002	76	77	M100169	FA50/OE	0.019
25PFRC002	77	78	M100170	FA50/OE	0.488
25PFRC002	78	79	M100171	FA50/OE	0.316
25PFRC002	79	80	M100174	FA50/OE	0.023
25PFRC002	80	81	M100175	FA50/OE	0.172
25PFRC002	81	82	M100176	FA50/OE	0.066
25PFRC002	82	83	M100177	FA50/OE	0.061
25PFRC002	83	84	M100178	FA50/OE	0.225
25PFRC002	84	85	M100179	FA50/OE	2.29
25PFRC002	85	86	M100180	FA50/OE	0.187
25PFRC002	86	87	M100181	FA50/OE	0.082
25PFRC002	87	88	M100182	FA50/OE	0.122
25PFRC002	88	89	M100183	FA50/OE	0.057
25PFRC002	89	90	M100184	FA50/OE	0.399
25PFRC002	90	91	M100185	FA50/OE	0.103
25PFRC002	91	92	M100186	FA50/OE	0.188
25PFRC002	92	93	M100187	FA50/OE	0.181
25PFRC002	93	94	M100188	FA50/OE	0.075
25PFRC002	94	95	M100189	FA50/OE	0.081
25PFRC002	95	96	M100190	FA50/OE	0.081
25PFRC002	96	97	M100191	FA50/OE	0.039
25PFRC002	97	98	M100192	FA50/OE	0.096
25PFRC002	98	99	M100193	FA50/OE	0.086
25PFRC002	99	100	M100194	FA50/OE	0.018
25PFRC002	100	101	M100195	FA50/OE	0.026
25PFRC002	101	102	M100196	FA50/OE	0.021
25PFRC002	102	103	M100197	FA50/OE	0.135
25PFRC002	103	104	M100198	FA50/OE	0.014
25PFRC002	104	105	M100201	FA50/OE	0.012
25PFRC002	105	106	M100202	FA50/OE	0.025
25PFRC002	106	107	M100203	FA50/OE	0.011
25PFRC002	107	108	M100204	FA50/OE	0.008

For personal use only

25PFRC002	108	109	M100205	FA50/OE	-0.02
25PFRC002	109	110	M100206	FA50/OE	0.007
25PFRC002	110	111	M100207	FA50/OE	0.006
25PFRC002	111	112	M100208	FA50/OE	0.067
25PFRC002	112	113	M100209	FA50/OE	0.007
25PFRC002	113	114	M100210	FA50/OE	0.012
25PFRC002	114	115	M100211	FA50/OE	0.009
25PFRC002	115	116	M100212	FA50/OE	0.033
25PFRC002	116	117	M100213	FA50/OE	0.029
25PFRC002	117	118	M100214	FA50/OE	0.022
25PFRC002	118	119	M100215	FA50/OE	0.007
25PFRC002	119	120	M100216	FA50/OE	0.028
25PFRC002	120	121	M100217	FA50/OE	0.02
25PFRC002	121	122	M100218	FA50/OE	0.041
25PFRC002	122	123	M100219	FA50/OE	0.008
25PFRC002	123	124	M100220	FA50/OE	0.023
25PFRC002	124	125	M100223	FA50/OE	0.014
25PFRC002	125	126	M100224	FA50/OE	0.015
25PFRC002	126	127	M100225	FA50/OE	0.01
25PFRC002	127	128	M100226	FA50/OE	0.021
25PFRC002	128	129	M100227	FA50/OE	0.031
25PFRC002	129	130	M100228	FA50/OE	0.03
25PFRC002	130	131	M100229	FA50/OE	0.013
25PFRC002	131	132	M100230	FA50/OE	0.009
25PFRC002	132	133	M100231	FA50/OE	0.013
25PFRC002	133	134	M100232	FA50/OE	0.005
25PFRC002	134	135	M100233	FA50/OE	0.009
25PFRC002	135	136	M100234	FA50/OE	0.008
25PFRC002	136	137	M100235	FA50/OE	0.006
25PFRC002	137	138	M100236	FA50/OE	0.185
25PFRC002	138	139	M100237	FA50/OE	0.009
25PFRC002	139	140	M100238	FA50/OE	0.007
25PFRC002	140	141	M100239	FA50/OE	-0.02
25PFRC002	141	142	M100240	FA50/OE	-0.02
25PFRC002	142	143	M100241	FA50/OE	0.006
25PFRC002	143	144	M100242	FA50/OE	0.025
25PFRC002	144	145	M100243	FA50/OE	0.04
25PFRC002	145	146	M100244	FA50/OE	0.015
25PFRC002	146	147	M100245	FA50/OE	0.009
25PFRC002	147	148	M100246	FA50/OE	0.016
25PFRC002	148	149	M100247	FA50/OE	0.009
25PFRC002	149	150	M100248	FA50/OE	0.028
25PFRC003	0	1	M100249	FA50/OE	0.082
25PFRC003	1	2	M100250	FA50/OE	0.035
25PFRC003	2	3	M100251	FA50/OE	0.046
25PFRC003	3	4	M100252	FA50/OE	0.035
25PFRC003	4	5	M100253	FA50/OE	0.019
25PFRC003	5	6	M100254	FA50/OE	0.325
25PFRC003	6	7	M100255	FA50/OE	0.025
25PFRC003	7	8	M100259	FA50/OE	0.029
25PFRC003	8	9	M100260	FA50/OE	0.29
25PFRC003	9	10	M100261	FA50/OE	0.032
25PFRC003	10	11	M100262	FA50/OE	0.065
25PFRC003	11	12	M100263	FA50/OE	0.241
25PFRC003	12	13	M100264	FA50/OE	0.043
25PFRC003	13	14	M100265	FA50/OE	0.924
25PFRC003	14	15	M100266	FA50/OE	0.055
25PFRC003	15	16	M100267	FA50/OE	0.066
25PFRC003	16	17	M100268	FA50/OE	0.057
25PFRC003	17	18	M100269	FA50/OE	0.129
25PFRC003	18	19	M100270	FA50/OE	0.227
25PFRC003	19	20	M100271	FA50/OE	0.289
25PFRC003	20	21	M100272	FA50/OE	0.326

For personal use only

25PFRC003	21	22	M100273	FA50/OE	0.181
25PFRC003	22	23	M100274	FA50/OE	0.169
25PFRC003	23	24	M100275	FA50/OE	0.178
25PFRC003	24	25	M100276	FA50/OE	0.11
25PFRC003	25	26	M100277	FA50/OE	0.047
25PFRC003	26	27	M100278	FA50/OE	0.144
25PFRC003	27	28	M100279	FA50/OE	0.957
25PFRC003	28	29	M100280	FA50/OE	0.217
25PFRC003	29	30	M100281	FA50/OE	0.208
25PFRC003	30	31	M100282	FA50/OE	0.087
25PFRC003	31	32	M100283	FA50/OE	0.102
25PFRC003	32	33	M100284	FA50/OE	0.097
25PFRC003	33	34	M100285	FA50/OE	0.079
25PFRC003	34	35	M100288	FA50/OE	0.05
25PFRC003	35	36	M100289	FA50/OE	0.266
25PFRC003	36	37	M100290	FA50/OE	1.007
25PFRC003	37	38	M100291	FA50/OE	0.107
25PFRC003	38	39	M100292	FA50/OE	0.027
25PFRC003	39	40	M100293	FA50/OE	0.12
25PFRC003	40	41	M100294	FA50/OE	0.017
25PFRC003	41	42	M100295	FA50/OE	0.077
25PFRC003	42	43	M100296	FA50/OE	0.052
25PFRC003	43	44	M100297	FA50/OE	0.019
25PFRC003	44	45	M100298	FA50/OE	0.01
25PFRC003	45	46	M100299	FA50/OE	0.03
25PFRC003	46	47	M100300	FA50/OE	0.035
25PFRC003	47	48	M100301	FA50/OE	0.087
25PFRC003	48	49	M100302	FA50/OE	0.019
25PFRC003	49	50	M100303	FA50/OE	0.036
25PFRC003	50	51	M100304	FA50/OE	0.199
25PFRC003	51	52	M100305	FA50/OE	0.359
25PFRC003	52	53	M100306	FA50/OE	6.591
25PFRC003	53	54	M100307	FA50/OE	0.614
25PFRC003	54	55	M100308	FA50/OE	0.261
25PFRC003	55	56	M100309	FA50/OE	2.534
25PFRC003	56	57	M100310	FA50/OE	0.802
25PFRC003	57	58	M100311	FA50/OE	0.217
25PFRC003	58	59	M100312	FA50/OE	0.345
25PFRC004	0	1	M100313	FA50/OE	0.203
25PFRC004	1	2	M100314	FA50/OE	0.075
25PFRC004	2	3	M100315	FA50/OE	0.113
25PFRC004	3	4	M100316	FA50/OE	0.044
25PFRC004	4	5	M100317	FA50/OE	0.25
25PFRC004	5	6	M100318	FA50/OE	0.314
25PFRC004	6	7	M100319	FA50/OE	0.383
25PFRC004	7	8	M100320	FA50/OE	0.375
25PFRC004	8	9	M100321	FA50/OE	0.911
25PFRC004	9	10	M100324	FA50/OE	2.654
25PFRC004	10	11	M100325	FA50/OE	4.565
25PFRC004	11	12	M100326	FA50/OE	1.234
25PFRC004	12	13	M100327	FA50/OE	0.504
25PFRC004	13	14	M100328	FA50/OE	0.264
25PFRC004	14	15	M100329	FA50/OE	0.221
25PFRC004	15	16	M100330	FA50/OE	0.159
25PFRC004	16	17	M100331	FA50/OE	0.056
25PFRC004	17	18	M100332	FA50/OE	0.032
25PFRC004	18	19	M100333	FA50/OE	0.016
25PFRC004	19	20	M100334	FA50/OE	0.015
25PFRC004	20	21	M100335	FA50/OE	0.007
25PFRC004	21	22	M100336	FA50/OE	0.009
25PFRC004	22	23	M100337	FA50/OE	0.132
25PFRC004	23	24	M100338	FA50/OE	0.208
25PFRC004	24	25	M100339	FA50/OE	0.021

For personal use only

25PFRC004	25	26	M100340	FA50/OE	0.012
25PFRC004	26	27	M100341	FA50/OE	0.015
25PFRC004	27	28	M100342	FA50/OE	0.065
25PFRC004	28	29	M100343	FA50/OE	0.171
25PFRC004	29	30	M100344	FA50/OE	0.042
25PFRC004	30	31	M100345	FA50/OE	0.037
25PFRC004	31	32	M100346	FA50/OE	0.043
25PFRC004	32	33	M100347	FA50/OE	0.022
25PFRC004	33	34	M100348	FA50/OE	0.077
25PFRC004	34	35	M100349	FA50/OE	0.015
25PFRC004	35	36	M100350	FA50/OE	0.129
25PFRC004	36	37	M100351	FA50/OE	0.007
25PFRC004	37	38	M100352	FA50/OE	0.189
25PFRC004	38	39	M100353	FA50/OE	0.157
25PFRC004	39	40	M100357	FA50/OE	0.423
25PFRC004	40	41	M100358	FA50/OE	0.062
25PFRC004	41	42	M100359	FA50/OE	0.066
25PFRC004	42	43	M100360	FA50/OE	0.065
25PFRC004	43	44	M100361	FA50/OE	0.018
25PFRC004	44	45	M100362	FA50/OE	0.132
25PFRC004	45	46	M100363	FA50/OE	0.031
25PFRC004	46	47	M100364	FA50/OE	0.012
25PFRC004	47	48	M100365	FA50/OE	0.026
25PFRC004	48	49	M100366	FA50/OE	0.264
25PFRC004	49	50	M100367	FA50/OE	0.044
25PFRC004	50	51	M100368	FA50/OE	0.01
25PFRC004	51	52	M100369	FA50/OE	0.006
25PFRC004	52	53	M100370	FA50/OE	0.073
25PFRC004	53	54	M100371	FA50/OE	0.015
25PFRC004	54	55	M100372	FA50/OE	0.026
25PFRC004	55	56	M100373	FA50/OE	-0.02
25PFRC004	56	57	M100374	FA50/OE	-0.02
25PFRC004	57	58	M100375	FA50/OE	0.181
25PFRC004	58	59	M100376	FA50/OE	0.076
25PFRC004	59	60	M100379	FA50/OE	0.107
25PFRC004	60	61	M100380	FA50/OE	1.243
25PFRC004	61	62	M100381	FA50/OE	0.165
25PFRC004	62	63	M100382	FA50/OE	0.18
25PFRC004	63	64	M100383	FA50/OE	0.568
25PFRC004	64	65	M100384	FA50/OE	0.559
25PFRC004	65	66	M100385	FA50/OE	0.974
25PFRC004	66	67	M100386	FA50/OE	0.107
25PFRC004	67	68	M100387	FA50/OE	0.215
25PFRC004	68	69	M100388	FA50/OE	0.04
25PFRC004	69	70	M100389	FA50/OE	0.078
25PFRC004	70	71	M100390	FA50/OE	0.038
25PFRC004	71	72	M100391	FA50/OE	0.014
25PFRC004	72	73	M100392	FA50/OE	0.015
25PFRC004	73	74	M100393	FA50/OE	0.015
25PFRC004	74	75	M100394	FA50/OE	0.014
25PFRC004	75	76	M100395	FA50/OE	0.312
25PFRC004	76	77	M100396	FA50/OE	0.387
25PFRC004	77	78	M100397	FA50/OE	0.546
25PFRC004	78	79	M100398	FA50/OE	0.345
25PFRC004	79	80	M100399	FA50/OE	0.381
25PFRC004	80	81	M100400	FA50/OE	0.366
25PFRC004	81	82	M100401	FA50/OE	0.182
25PFRC004	82	83	M100402	FA50/OE	0.159
25PFRC004	83	84	M100403	FA50/OE	0.043
25PFRC004	84	85	M100404	FA50/OE	0.026
25PFRC004	85	86	M100405	FA50/OE	0.031
25PFRC004	86	87	M100406	FA50/OE	0.091
25PFRC004	87	88	M100407	FA50/OE	0.07

For personal use only

25PFRC004	88	89	M100408	FA50/OE	0.029
25PFRC004	89	90	M100409	FA50/OE	0.029
25PFRC004	90	91	M100410	FA50/OE	0.055
25PFRC004	91	92	M100411	FA50/OE	0.011
25PFRC004	92	93	M100412	FA50/OE	0.013
25PFRC004	93	94	M100413	FA50/OE	0.031
25PFRC004	94	95	M100414	FA50/OE	0.013
25PFRC004	95	96	M100415	FA50/OE	0.03
25PFRC004	96	97	M100416	FA50/OE	-0.02
25PFRC004	97	98	M100417	FA50/OE	0.027
25PFRC004	98	99	M100418	FA50/OE	0.166
25PFRC004	99	100	M100419	FA50/OE	0.022
25PFRC004	100	101	M100420	FA50/OE	0.017
25PFRC004	101	102	M100421	FA50/OE	0.011
25PFRC004	102	103	M100422	FA50/OE	0.302
25PFRC004	103	104	M100423	FA50/OE	0.253
25PFRC004	104	105	M100424	FA50/OE	0.029
25PFRC004	105	106	M100425	FA50/OE	0.529
25PFRC004	106	107	M100426	FA50/OE	0.26
25PFRC004	107	108	M100427	FA50/OE	0.012
25PFRC004	108	109	M100428	FA50/OE	0.005
25PFRC004	109	110	M100431	FA50/OE	0.005
25PFRC004	110	111	M100432	FA50/OE	0.01
25PFRC004	111	112	M100433	FA50/OE	0.039
25PFRC004	112	113	M100434	FA50/OE	0.02
25PFRC004	113	114	M100435	FA50/OE	0.016
25PFRC004	114	115	M100436	FA50/OE	0.021
25PFRC004	115	116	M100437	FA50/OE	0.3
25PFRC004	116	117	M100438	FA50/OE	0.012
25PFRC004	117	118	M100439	FA50/OE	0.03
25PFRC004	118	119	M100440	FA50/OE	0.005
25PFRC004	119	120	M100441	FA50/OE	0.005
25PFRC005	0	1	M100442	FA50/OE	0.077
25PFRC005	1	2	M100443	FA50/OE	0.03
25PFRC005	2	3	M100444	FA50/OE	0.027
25PFRC005	3	4	M100445	FA50/OE	0.013
25PFRC005	4	5	M100446	FA50/OE	0.01
25PFRC005	5	6	M100447	FA50/OE	0.01
25PFRC005	6	7	M100448	FA50/OE	0.037
25PFRC005	7	8	M100449	FA50/OE	0.032
25PFRC005	8	9	M100450	FA50/OE	0.009
25PFRC005	9	10	M100451	FA50/OE	0.011
25PFRC005	10	11	M100452	FA50/OE	0.031
25PFRC005	11	12	M100453	FA50/OE	0.053
25PFRC005	12	13	M100454	FA50/OE	0.106
25PFRC005	13	14	M100455	FA50/OE	0.231
25PFRC005	14	15	M100456	FA50/OE	1.78
25PFRC005	15	16	M100459	FA50/OE	0.299
25PFRC005	16	17	M100460	FA50/OE	0.247
25PFRC005	17	18	M100461	FA50/OE	0.282
25PFRC005	18	19	M100462	FA50/OE	0.083
25PFRC005	19	20	M100463	FA50/OE	0.13
25PFRC005	20	21	M100464	FA50/OE	0.083
25PFRC005	21	22	M100465	FA50/OE	0.006
25PFRC005	22	23	M100466	FA50/OE	0.014
25PFRC005	23	24	M100467	FA50/OE	0.031
25PFRC005	24	25	M100468	FA50/OE	0.008
25PFRC005	25	26	M100469	FA50/OE	0.077
25PFRC005	26	27	M100470	FA50/OE	0.084
25PFRC005	27	28	M100471	FA50/OE	0.03
25PFRC005	28	29	M100472	FA50/OE	0.034
25PFRC005	29	30	M100473	FA50/OE	0.007
25PFRC005	30	31	M100474	FA50/OE	-0.02

For personal use only

25PFRC005	31	32	M100475	FA50/OE	0.168
25PFRC005	32	33	M100476	FA50/OE	0.028
25PFRC005	33	34	M100477	FA50/OE	0.025
25PFRC005	34	35	M100478	FA50/OE	0.169
25PFRC005	35	36	M100481	FA50/OE	0.194
25PFRC005	36	37	M100482	FA50/OE	0.083
25PFRC005	37	38	M100483	FA50/OE	0.024
25PFRC005	38	39	M100484	FA50/OE	0.006
25PFRC005	39	40	M100485	FA50/OE	0.012
25PFRC005	40	41	M100486	FA50/OE	0.157
25PFRC005	41	42	M100487	FA50/OE	0.154
25PFRC005	42	43	M100488	FA50/OE	0.061
25PFRC005	43	44	M100489	FA50/OE	0.137
25PFRC005	44	45	M100490	FA50/OE	0.053
25PFRC005	45	46	M100491	FA50/OE	0.032
25PFRC005	46	47	M100492	FA50/OE	0.091
25PFRC005	47	48	M100493	FA50/OE	2.354
25PFRC005	48	49	M100494	FA50/OE	0.145
25PFRC005	49	50	M100495	FA50/OE	0.094
25PFRC005	50	51	M100496	FA50/OE	0.009
25PFRC005	51	52	M100497	FA50/OE	0.102
25PFRC005	52	53	M100498	FA50/OE	0.07
25PFRC005	53	54	M100499	FA50/OE	0.064
25PFRC005	54	55	M100500	FA50/OE	0.085
25PFRC005	55	56	M100501	FA50/OE	0.093
25PFRC005	56	57	M100502	FA50/OE	0.013
25PFRC005	57	58	M100503	FA50/OE	0.029
25PFRC005	58	59	M100504	FA50/OE	0.284
25PFRC005	59	60	M100505	FA50/OE	0.914
25PFRC005	60	61	M100506	FA50/OE	4.854
25PFRC005	61	62	M100507	FA50/OE	0.465
25PFRC005	62	63	M100508	FA50/OE	1.563
25PFRC005	63	64	M100509	FA50/OE	0.974
25PFRC005	64	65	M100510	FA50/OE	0.191
25PFRC005	65	66	M100513	FA50/OE	0.274
25PFRC005	66	67	M100514	FA50/OE	0.105
25PFRC005	67	68	M100515	FA50/OE	0.049
25PFRC005	68	69	M100516	FA50/OE	0.036
25PFRC005	69	70	M100517	FA50/OE	0.022
25PFRC005	70	71	M100518	FA50/OE	0.027
25PFRC005	71	72	M100519	FA50/OE	0.107
25PFRC005	72	73	M100520	FA50/OE	0.87
25PFRC005	73	74	M100521	FA50/OE	0.076
25PFRC005	74	75	M100523	FA50/OE	0.127
25PFRC005	75	76	M100524	FA50/OE	0.056
25PFRC005	76	77	M100525	FA50/OE	0.01
25PFRC005	77	78	M100526	FA50/OE	0.401
25PFRC005	78	79	M100527	FA50/OE	0.063
25PFRC005	79	80	M100528	FA50/OE	0.032
25PFRC006	0	1	M100529	FA50/OE	0.085
25PFRC006	1	2	M100530	FA50/OE	0.053
25PFRC006	2	3	M100531	FA50/OE	0.027
25PFRC006	3	4	M100532	FA50/OE	0.028
25PFRC006	4	5	M100533	FA50/OE	0.015
25PFRC006	5	6	M100534	FA50/OE	0.013
25PFRC006	6	7	M100535	FA50/OE	0.022
25PFRC006	7	8	M100536	FA50/OE	0.025
25PFRC006	8	9	M100537	FA50/OE	0.009
25PFRC006	9	10	M100538	FA50/OE	0.007
25PFRC006	10	11	M100541	FA50/OE	0.055
25PFRC006	11	12	M100542	FA50/OE	0.014
25PFRC006	12	13	M100543	FA50/OE	0.023
25PFRC006	13	14	M100544	FA50/OE	0.014

For personal use only

25PFRC006	14	15	M100545	FA50/OE	-0.005
25PFRC006	15	16	M100546	FA50/OE	0.014
25PFRC006	16	17	M100547	FA50/OE	0.019
25PFRC006	17	18	M100548	FA50/OE	0.025
25PFRC006	18	19	M100549	FA50/OE	0.103
25PFRC006	19	20	M100550	FA50/OE	0.129
25PFRC006	20	21	M100551	FA50/OE	0.152
25PFRC006	21	22	M100552	FA50/OE	0.096
25PFRC006	22	23	M100553	FA50/OE	0.046
25PFRC006	23	24	M100554	FA50/OE	0.017
25PFRC006	24	25	M100555	FA50/OE	0.055
25PFRC006	25	26	M100556	FA50/OE	0.03
25PFRC006	26	27	M100557	FA50/OE	0.088
25PFRC006	27	28	M100558	FA50/OE	0.086
25PFRC006	28	29	M100559	FA50/OE	0.09
25PFRC006	29	30	M100560	FA50/OE	0.027
25PFRC006	30	31	M100563	FA50/OE	0.012
25PFRC006	31	32	M100564	FA50/OE	0.081
25PFRC006	32	33	M100565	FA50/OE	0.203
25PFRC006	33	34	M100566	FA50/OE	0.156
25PFRC006	34	35	M100567	FA50/OE	0.018
25PFRC006	35	36	M100568	FA50/OE	0.031
25PFRC006	36	37	M100569	FA50/OE	0.023
25PFRC006	37	38	M100570	FA50/OE	0.046
25PFRC006	38	39	M100571	FA50/OE	0.027
25PFRC006	39	40	M100572	FA50/OE	0.007
25PFRC006	40	41	M100573	FA50/OE	0.013
25PFRC006	41	42	M100574	FA50/OE	0.164
25PFRC006	42	43	M100575	FA50/OE	0.01
25PFRC006	43	44	M100576	FA50/OE	0.009
25PFRC006	44	45	M100577	FA50/OE	0.014
25PFRC006	45	46	M100578	FA50/OE	1.471
25PFRC006	46	47	M100579	FA50/OE	0.111
25PFRC006	47	48	M100580	FA50/OE	0.045
25PFRC006	48	49	M100581	FA50/OE	0.044
25PFRC006	49	50	M100582	FA50/OE	0.167
25PFRC006	50	51	M100585	FA50/OE	0.133
25PFRC006	51	52	M100586	FA50/OE	0.121
25PFRC006	52	53	M100587	FA50/OE	0.054
25PFRC006	53	54	M100588	FA50/OE	0.079
25PFRC006	54	55	M100589	FA50/OE	0.1
25PFRC006	55	56	M100590	FA50/OE	0.028
25PFRC006	56	57	M100591	FA50/OE	0.161
25PFRC006	57	58	M100592	FA50/OE	0.44
25PFRC006	58	59	M100593	FA50/OE	0.189
25PFRC006	59	60	M100594	FA50/OE	0.017
25PFRC006	60	61	M100595	FA50/OE	0.031
25PFRC006	61	62	M100596	FA50/OE	0.02
25PFRC006	62	63	M100597	FA50/OE	0.018
25PFRC006	63	64	M100598	FA50/OE	0.015
25PFRC006	64	65	M100599	FA50/OE	0.013
25PFRC006	65	66	M100600	FA50/OE	0.069
25PFRC006	66	67	M100601	FA50/OE	0.102
25PFRC006	67	68	M100602	FA50/OE	0.017
25PFRC006	68	69	M100603	FA50/OE	0.009
25PFRC006	69	70	M100604	FA50/OE	0.177
25PFRC006	70	71	M100607	FA50/OE	0.034
25PFRC006	71	72	M100608	FA50/OE	0.04
25PFRC006	72	73	M100609	FA50/OE	0.081
25PFRC006	73	74	M100610	FA50/OE	0.066
25PFRC006	74	75	M100611	FA50/OE	0.037
25PFRC006	75	76	M100612	FA50/OE	0.274
25PFRC006	76	77	M100613	FA50/OE	0.1

For personal use only

25PFRC006	77	78	M100614	FA50/OE	0.026
25PFRC006	78	79	M100615	FA50/OE	0.014
25PFRC006	79	80	M100616	FA50/OE	0.016
25PFRC006	80	81	M100617	FA50/OE	0.075
25PFRC006	81	82	M100618	FA50/OE	0.121
25PFRC006	82	83	M100619	FA50/OE	0.053
25PFRC006	83	84	M100620	FA50/OE	0.035
25PFRC006	84	85	M100621	FA50/OE	0.159
25PFRC006	85	86	M100622	FA50/OE	0.546
25PFRC006	86	87	M100623	FA50/OE	0.27
25PFRC006	87	88	M100624	FA50/OE	0.149
25PFRC006	88	89	M100625	FA50/OE	0.125
25PFRC006	89	90	M100626	FA50/OE	0.411
25PFRC006	90	91	M100629	FA50/OE	0.072
25PFRC006	91	92	M100630	FA50/OE	0.182
25PFRC006	92	93	M100631	FA50/OE	1.142
25PFRC006	93	94	M100632	FA50/OE	0.19
25PFRC006	94	95	M100633	FA50/OE	0.26
25PFRC006	95	96	M100634	FA50/OE	0.068
25PFRC006	96	97	M100635	FA50/OE	0.286
25PFRC006	97	98	M100636	FA50/OE	0.173
25PFRC006	98	99	M100637	FA50/OE	0.362
25PFRC006	99	100	M100639	FA50/OE	0.273
25PFRC006	100	101	M100640	FA50/OE	0.107
25PFRC006	101	102	M100641	FA50/OE	0.552
25PFRC006	102	103	M100642	FA50/OE	0.271
25PFRC006	103	104	M100643	FA50/OE	0.047
25PFRC006	104	105	M100644	FA50/OE	0.03
25PFRC006	105	106	M100645	FA50/OE	0.036
25PFRC006	106	107	M100646	FA50/OE	0.027
25PFRC006	107	108	M100647	FA50/OE	0.073
25PFRC006	108	109	M100648	FA50/OE	0.157
25PFRC006	109	110	M100649	FA50/OE	0.485
25PFRC006	110	111	M100650	FA50/OE	0.037
25PFRC006	111	112	M100651	FA50/OE	0.019
25PFRC006	112	113	M100652	FA50/OE	-0.005
25PFRC006	113	114	M100653	FA50/OE	0.123
25PFRC006	114	115	M100654	FA50/OE	0.042
25PFRC007	0	1	M100655	FA50/OE	0.046
25PFRC007	1	2	M100656	FA50/OE	0.078
25PFRC007	2	3	M100657	FA50/OE	0.036
25PFRC007	3	4	M100658	FA50/OE	0.061
25PFRC007	4	5	M100659	FA50/OE	0.022
25PFRC007	5	6	M100660	FA50/OE	0.025
25PFRC007	6	7	M100661	FA50/OE	0.011
25PFRC007	7	8	M100662	FA50/OE	0.015
25PFRC007	8	9	M100663	FA50/OE	0.03
25PFRC007	9	10	M100664	FA50/OE	0.012
25PFRC007	10	11	M100665	FA50/OE	0.013
25PFRC007	11	12	M100666	FA50/OE	0.012
25PFRC007	12	13	M100667	FA50/OE	0.017
25PFRC007	13	14	M100668	FA50/OE	0.021
25PFRC007	14	15	M100669	FA50/OE	0.012
25PFRC007	15	16	M100670	FA50/OE	0.014
25PFRC007	16	17	M100671	FA50/OE	0.016
25PFRC007	17	18	M100672	FA50/OE	0.041
25PFRC007	18	19	M100673	FA50/OE	0.059
25PFRC007	19	20	M100674	FA50/OE	0.586
25PFRC007	20	21	M100677	FA50/OE	0.454
25PFRC007	21	22	M100678	FA50/OE	0.028
25PFRC007	22	23	M100679	FA50/OE	0.039
25PFRC007	23	24	M100680	FA50/OE	0.033
25PFRC007	24	25	M100681	FA50/OE	0.048

For personal use only

25PFRC007	25	26	M100682	FA50/OE	0.101
25PFRC007	26	27	M100683	FA50/OE	0.057
25PFRC007	27	28	M100684	FA50/OE	0.042
25PFRC007	28	29	M100685	FA50/OE	0.042
25PFRC007	29	30	M100686	FA50/OE	0.033
25PFRC007	30	31	M100687	FA50/OE	0.022
25PFRC007	31	32	M100688	FA50/OE	0.258
25PFRC007	32	33	M100689	FA50/OE	0.045
25PFRC007	33	34	M100690	FA50/OE	0.032
25PFRC007	34	35	M100691	FA50/OE	0.043
25PFRC007	35	36	M100692	FA50/OE	0.189
25PFRC007	36	37	M100693	FA50/OE	0.527
25PFRC007	37	38	M100694	FA50/OE	0.166
25PFRC007	38	39	M100695	FA50/OE	0.041
25PFRC007	39	40	M100696	FA50/OE	0.068
25PFRC007	40	41	M100699	FA50/OE	0.035
25PFRC007	41	42	M100700	FA50/OE	0.017
25PFRC007	42	43	M100701	FA50/OE	0.059
25PFRC007	43	44	M100702	FA50/OE	0.197
25PFRC007	44	45	M100703	FA50/OE	0.12
25PFRC007	45	46	M100704	FA50/OE	0.071
25PFRC007	46	47	M100705	FA50/OE	0.022
25PFRC007	47	48	M100706	FA50/OE	0.102
25PFRC007	48	49	M100707	FA50/OE	0.047
25PFRC007	49	50	M100708	FA50/OE	0.015
25PFRC007	50	51	M100709	FA50/OE	0.084
25PFRC007	51	52	M100710	FA50/OE	0.055
25PFRC007	52	53	M100711	FA50/OE	0.317
25PFRC007	53	54	M100712	FA50/OE	0.105
25PFRC007	54	55	M100713	FA50/OE	0.353
25PFRC007	55	56	M100714	FA50/OE	0.386
25PFRC007	56	57	M100715	FA50/OE	0.2
25PFRC007	57	58	M100716	FA50/OE	0.213
25PFRC007	58	59	M100717	FA50/OE	0.054
25PFRC007	59	60	M100718	FA50/OE	0.639
25PFRC007	60	61	M100721	FA50/OE	0.773
25PFRC007	61	62	M100722	FA50/OE	0.271
25PFRC007	62	63	M100723	FA50/OE	0.214
25PFRC007	63	64	M100724	FA50/OE	0.324
25PFRC007	64	65	M100725	FA50/OE	0.384
25PFRC007	65	66	M100726	FA50/OE	0.019
25PFRC007	66	67	M100727	FA50/OE	0.129
25PFRC007	67	68	M100728	FA50/OE	0.11
25PFRC007	68	69	M100729	FA50/OE	0.07
25PFRC007	69	70	M100730	FA50/OE	0.022
25PFRC007	70	71	M100732	FA50/OE	0.085
25PFRC007	71	72	M100733	FA50/OE	0.085
25PFRC007	72	73	M100734	FA50/OE	0.009
25PFRC007	73	74	M100735	FA50/OE	0.033
25PFRC007	74	75	M100736	FA50/OE	0.078
25PFRC007	75	76	M100737	FA50/OE	0.06
25PFRC007	76	77	M100738	FA50/OE	0.374
25PFRC007	77	78	M100739	FA50/OE	0.19
25PFRC007	78	79	M100740	FA50/OE	0.198
25PFRC007	79	80	M100741	FA50/OE	0.023
25PFRC007	80	81	M100742	FA50/OE	0.034
25PFRC007	81	82	M100743	FA50/OE	0.01
25PFRC007	82	83	M100744	FA50/OE	0.067
25PFRC007	83	84	M100745	FA50/OE	0.026
25PFRC007	84	85	M100746	FA50/OE	0.138
25PFRC007	85	86	M100747	FA50/OE	0.222
25PFRC007	86	87	M100748	FA50/OE	0.033
25PFRC007	87	88	M100749	FA50/OE	0.062

For personal use only

25PFRC007	88	89	M100750	FA50/OE	0.024
25PFRC007	89	90	M100751	FA50/OE	0.019
25PFRC007	90	91	M100754	FA50/OE	0.007
25PFRC007	91	92	M100755	FA50/OE	0.028
25PFRC007	92	93	M100756	FA50/OE	0.025
25PFRC007	93	94	M100757	FA50/OE	0.01
25PFRC007	94	95	M100758	FA50/OE	-0.005
25PFRC007	95	96	M100759	FA50/OE	0.023
25PFRC007	96	97	M100760	FA50/OE	0.068
25PFRC007	97	98	M100761	FA50/OE	0.044
25PFRC007	98	99	M100762	FA50/OE	0.806
25PFRC007	99	100	M100763	FA50/OE	0.292
25PFRC007	100	101	M100764	FA50/OE	0.218
25PFRC007	101	102	M100765	FA50/OE	0.029
25PFRC007	102	103	M100766	FA50/OE	0.098
25PFRC007	103	104	M100767	FA50/OE	0.219
25PFRC007	104	105	M100768	FA50/OE	0.363
25PFRC007	105	106	M100769	FA50/OE	0.301
25PFRC007	106	107	M100770	FA50/OE	0.863
25PFRC007	107	108	M100771	FA50/OE	0.144
25PFRC007	108	109	M100772	FA50/OE	0.1
25PFRC007	109	110	M100773	FA50/OE	0.16
25PFRC008	0	1	M100774	FA50/OE	0.137
25PFRC008	1	2	M100775	FA50/OE	0.071
25PFRC008	2	3	M100776	FA50/OE	0.046
25PFRC008	3	4	M100777	FA50/OE	0.02
25PFRC008	4	5	M100778	FA50/OE	0.041
25PFRC008	5	6	M100779	FA50/OE	0.062
25PFRC008	6	7	M100780	FA50/OE	0.073
25PFRC008	7	8	M100781	FA50/OE	0.106
25PFRC008	8	9	M100782	FA50/OE	0.014
25PFRC008	9	10	M100783	FA50/OE	0.041
25PFRC008	10	11	M100786	FA50/OE	0.019
25PFRC008	11	12	M100787	FA50/OE	0.034
25PFRC008	12	13	M100788	FA50/OE	0.042
25PFRC008	13	14	M100789	FA50/OE	0.07
25PFRC008	14	15	M100790	FA50/OE	0.036
25PFRC008	15	16	M100791	FA50/OE	0.019
25PFRC008	16	17	M100792	FA50/OE	0.016
25PFRC008	17	18	M100793	FA50/OE	0.022
25PFRC008	18	19	M100794	FA50/OE	0.03
25PFRC008	19	20	M100795	FA50/OE	0.058
25PFRC008	20	21	M100796	FA50/OE	0.023
25PFRC008	21	22	M100797	FA50/OE	0.055
25PFRC008	22	23	M100798	FA50/OE	0.032
25PFRC008	23	24	M100799	FA50/OE	0.047
25PFRC008	24	25	M100800	FA50/OE	0.307
25PFRC008	25	26	M100801	FA50/OE	0.331
25PFRC008	26	27	M100802	FA50/OE	0.063
25PFRC008	27	28	M100803	FA50/OE	0.103
25PFRC008	28	29	M100804	FA50/OE	0.052
25PFRC008	29	30	M100805	FA50/OE	0.259
25PFRC008	30	31	M100806	FA50/OE	0.149
25PFRC008	31	32	M100807	FA50/OE	0.114
25PFRC008	32	33	M100808	FA50/OE	0.01
25PFRC008	33	34	M100809	FA50/OE	0.076
25PFRC008	34	35	M100810	FA50/OE	0.143
25PFRC008	35	36	M100811	FA50/OE	1.32
25PFRC008	36	37	M100812	FA50/OE	0.041
25PFRC008	37	38	M100813	FA50/OE	0.138
25PFRC008	38	39	M100814	FA50/OE	0.01
25PFRC008	39	40	M100815	FA50/OE	-0.005
25PFRC008	40	41	M100816	FA50/OE	0.032

For personal use only

25PFRC008	41	42	M100817	FA50/OE	0.006
25PFRC008	42	43	M100818	FA50/OE	0.007
25PFRC008	43	44	M100819	FA50/OE	0.051
25PFRC008	44	45	M100820	FA50/OE	0.085
25PFRC008	45	46	M100821	FA50/OE	0.048
25PFRC008	46	47	M100822	FA50/OE	0.007
25PFRC008	47	48	M100823	FA50/OE	0.006
25PFRC008	48	49	M100824	FA50/OE	0.028
25PFRC008	49	50	M100825	FA50/OE	0.016
25PFRC008	50	51	M100828	FA50/OE	0.102
25PFRC008	51	52	M100829	FA50/OE	0.152
25PFRC008	52	53	M100830	FA50/OE	0.072
25PFRC008	53	54	M100831	FA50/OE	0.081
25PFRC008	54	55	M100832	FA50/OE	0.016
25PFRC008	55	56	M100833	FA50/OE	0.065
25PFRC008	56	57	M100834	FA50/OE	0.204
25PFRC008	57	58	M100835	FA50/OE	0.932
25PFRC008	58	59	M100836	FA50/OE	0.088
25PFRC008	59	60	M100837	FA50/OE	0.028
25PFRC008	60	61	M100838	FA50/OE	0.042
25PFRC008	61	62	M100839	FA50/OE	0.037
25PFRC008	62	63	M100840	FA50/OE	0.045
25PFRC008	63	64	M100841	FA50/OE	0.202
25PFRC008	64	65	M100842	FA50/OE	0.081
25PFRC008	65	66	M100843	FA50/OE	0.123
25PFRC008	66	67	M100844	FA50/OE	0.032
25PFRC008	67	68	M100845	FA50/OE	0.022
25PFRC008	68	69	M100846	FA50/OE	0.01
25PFRC008	69	70	M100847	FA50/OE	0.011
25PFRC008	70	71	M100848	FA50/OE	0.012
25PFRC008	71	72	M100849	FA50/OE	0.164
25PFRC008	72	73	M100850	FA50/OE	0.072
25PFRC008	73	74	M100851	FA50/OE	0.085
25PFRC008	74	75	M100852	FA50/OE	0.034
25PFRC008	75	76	M100853	FA50/OE	0.027
25PFRC008	76	77	M100854	FA50/OE	0.02
25PFRC008	77	78	M100855	FA50/OE	0.637
25PFRC008	78	79	M100856	FA50/OE	0.08
25PFRC008	79	80	M100857	FA50/OE	0.026
25PFRC008	80	81	M100860	FA50/OE	0.146
25PFRC008	81	82	M100861	FA50/OE	0.099
25PFRC008	82	83	M100862	FA50/OE	0.28
25PFRC008	83	84	M100863	FA50/OE	0.319
25PFRC008	84	85	M100864	FA50/OE	0.049
25PFRC008	85	86	M100865	FA50/OE	0.305
25PFRC008	86	87	M100866	FA50/OE	0.159
25PFRC008	87	88	M100867	FA50/OE	2.233
25PFRC008	88	89	M100868	FA50/OE	2.055
25PFRC008	89	90	M100869	FA50/OE	0.471
25PFRC008	90	91	M100870	FA50/OE	0.651
25PFRC008	91	92	M100871	FA50/OE	0.17
25PFRC008	92	93	M100872	FA50/OE	0.377
25PFRC008	93	94	M100873	FA50/OE	0.487
25PFRC008	94	95	M100874	FA50/OE	0.978
25PFRC008	95	96	M100875	FA50/OE	0.415
25PFRC008	96	97	M100876	FA50/OE	0.684
25PFRC008	97	98	M100877	FA50/OE	0.466
25PFRC008	98	99	M100878	FA50/OE	0.416
25PFRC008	99	100	M100879	FA50/OE	0.631
25PFRC008	100	101	M100882	FA50/OE	0.911
25PFRC008	101	102	M100883	FA50/OE	0.856
25PFRC008	102	103	M100884	FA50/OE	0.163
25PFRC008	103	104	M100885	FA50/OE	0.028

For personal use only

25PFRC008	104	105	M100886	FA50/OE	0.214
25PFRC008	105	106	M100887	FA50/OE	0.166
25PFRC008	106	107	M100888	FA50/OE	0.026
25PFRC008	107	108	M100889	FA50/OE	0.084
25PFRC008	108	109	M100890	FA50/OE	0.061
25PFRC008	109	110	M100891	FA50/OE	0.19
25PFRC008	110	111	M100893	FA50/OE	0.386
25PFRC008	111	112	M100894	FA50/OE	0.536
25PFRC008	112	113	M100895	FA50/OE	0.42
25PFRC008	113	114	M100896	FA50/OE	0.134
25PFRC008	114	115	M100897	FA50/OE	-0.005
25PFRC008	115	116	M100898	FA50/OE	-0.005
25PFRC008	116	117	M100899	FA50/OE	-0.005
25PFRC008	117	118	M100900	FA50/OE	0.006
25PFRC008	118	119	M100901	FA50/OE	0.036
25PFRC008	119	120	M100902	FA50/OE	0.014
25PFRC008	120	121	M100905	FA50/OE	0.006
25PFRC008	121	122	M100906	FA50/OE	0.018
25PFRC008	122	123	M100907	FA50/OE	0.025
25PFRC008	123	124	M100908	FA50/OE	0.015
25PFRC008	124	125	M100909	FA50/OE	0.684
25PFRC008	125	126	M100910	FA50/OE	0.039
25PFRC008	126	127	M100911	FA50/OE	0.107
25PFRC008	127	128	M100912	FA50/OE	0.043
25PFRC008	128	129	M100913	FA50/OE	0.098
25PFRC008	129	130	M100914	FA50/OE	0.048
25PFRC008	130	131	M100915	FA50/OE	0.021
25PFRC008	131	132	M100916	FA50/OE	0.03
25PFRC008	132	133	M100917	FA50/OE	0.007
25PFRC008	133	134	M100918	FA50/OE	0.123
25PFRC008	134	135	M100919	FA50/OE	0.013
25PFRC008	135	136	M100920	FA50/OE	0.017
25PFRC008	136	137	M100921	FA50/OE	-0.005
25PFRC009	0	1	M100922	FA50/OE	0.077
25PFRC009	1	2	M100923	FA50/OE	0.082
25PFRC009	2	3	M100924	FA50/OE	0.037
25PFRC009	3	4	M100925	FA50/OE	0.034
25PFRC009	4	5	M100926	FA50/OE	0.027
25PFRC009	5	6	M100927	FA50/OE	0.025
25PFRC009	6	7	M100928	FA50/OE	0.06
25PFRC009	7	8	M100929	FA50/OE	0.017
25PFRC009	8	9	M100930	FA50/OE	0.024
25PFRC009	9	10	M100931	FA50/OE	0.01
25PFRC009	10	11	M100932	FA50/OE	-0.005
25PFRC009	11	12	M100933	FA50/OE	-0.005
25PFRC009	12	13	M100934	FA50/OE	0.008
25PFRC009	13	14	M100935	FA50/OE	0.021
25PFRC009	14	15	M100936	FA50/OE	0.098
25PFRC009	15	16	M100937	FA50/OE	0.022
25PFRC009	16	17	M100938	FA50/OE	0.005
25PFRC009	17	18	M100939	FA50/OE	-0.005
25PFRC009	18	19	M100940	FA50/OE	0.099
25PFRC009	19	20	M100941	FA50/OE	0.02
25PFRC009	20	21	M100942	FA50/OE	0.012
25PFRC009	21	22	M100943	FA50/OE	0.102
25PFRC009	22	23	M100944	FA50/OE	0.047
25PFRC009	23	24	M100945	FA50/OE	0.096
25PFRC009	24	25	M100946	FA50/OE	0.023
25PFRC009	25	26	M100949	FA50/OE	0.04
25PFRC009	26	27	M100950	FA50/OE	0.059
25PFRC009	27	28	M100951	FA50/OE	0.039
25PFRC009	28	29	M100952	FA50/OE	0.034
25PFRC009	29	30	M100953	FA50/OE	0.032

For personal use only

25PFRC009	30	31	M100954	FA50/OE	0.025
25PFRC009	31	32	M100955	FA50/OE	0.023
25PFRC009	32	33	M100956	FA50/OE	0.082
25PFRC009	33	34	M100957	FA50/OE	0.052
25PFRC009	34	35	M100958	FA50/OE	0.048
25PFRC009	35	36	M100959	FA50/OE	0.393
25PFRC009	36	37	M100960	FA50/OE	0.887
25PFRC009	37	38	M100961	FA50/OE	0.122
25PFRC009	38	39	M100962	FA50/OE	0.034
25PFRC009	39	40	M100963	FA50/OE	0.331
25PFRC009	40	41	M100964	FA50/OE	0.061
25PFRC009	41	42	M100965	FA50/OE	0.012
25PFRC009	42	43	M100966	FA50/OE	0.024
25PFRC009	43	44	M100967	FA50/OE	0.346
25PFRC009	44	45	M100968	FA50/OE	0.145
25PFRC009	45	46	M100969	FA50/OE	0.075
25PFRC009	46	47	M100970	FA50/OE	0.055
25PFRC009	47	48	M100971	FA50/OE	0.07
25PFRC009	48	49	M100972	FA50/OE	0.06
25PFRC009	49	50	M100973	FA50/OE	0.121
25PFRC009	50	51	M100974	FA50/OE	0.055
25PFRC009	51	52	M100975	FA50/OE	0.067
25PFRC009	52	53	M100976	FA50/OE	0.073
25PFRC009	53	54	M100977	FA50/OE	0.329
25PFRC009	54	55	M100978	FA50/OE	0.038
25PFRC009	55	56	M100979	FA50/OE	0.038
25PFRC009	56	57	M100980	FA50/OE	0.343
25PFRC009	57	58	M100981	FA50/OE	0.041
25PFRC009	58	59	M100982	FA50/OE	0.181
25PFRC009	59	60	M100983	FA50/OE	0.202
25PFRC009	60	61	M100984	FA50/OE	0.142
25PFRC009	61	62	M100985	FA50/OE	0.735
25PFRC009	62	63	M100986	FA50/OE	0.222
25PFRC009	63	64	M100987	FA50/OE	0.404
25PFRC009	64	65	M100988	FA50/OE	0.292
25PFRC009	65	66	M100991	FA50/OE	0.235
25PFRC009	66	67	M100992	FA50/OE	0.247
25PFRC009	67	68	M100993	FA50/OE	0.318
25PFRC009	68	69	M100994	FA50/OE	0.059
25PFRC009	69	70	M100995	FA50/OE	0.461
25PFRC009	70	71	M100996	FA50/OE	0.058
25PFRC009	71	72	M100997	FA50/OE	1.872
25PFRC009	72	73	M100998	FA50/OE	0.363
25PFRC009	73	74	M100999	FA50/OE	0.233
25PFRC009	74	75	M101000	FA50/OE	0.093
25PFRC009	75	76	M101001	FA50/OE	0.126
25PFRC009	76	77	M101002	FA50/OE	0.888
25PFRC009	77	78	M101003	FA50/OE	0.426
25PFRC009	78	79	M101004	FA50/OE	0.162
25PFRC009	79	80	M101005	FA50/OE	0.616
25PFRC009	80	81	M101006	FA50/OE	0.33
25PFRC009	81	82	M101007	FA50/OE	0.056
25PFRC009	82	83	M101008	FA50/OE	0.305
25PFRC009	83	84	M101009	FA50/OE	0.306
25PFRC009	84	85	M101010	FA50/OE	1.269
25PFRC009	85	86	M101013	FA50/OE	1.239
25PFRC009	86	87	M101014	FA50/OE	0.348
25PFRC009	87	88	M101015	FA50/OE	0.027
25PFRC009	88	89	M101016	FA50/OE	0.036
25PFRC009	89	90	M101017	FA50/OE	0.06
25PFRC009	90	91	M101019	FA50/OE	0.011
25PFRC009	91	92	M101020	FA50/OE	0.022
25PFRC009	92	93	M101021	FA50/OE	0.028

For personal use only

25PFRC009	93	94	M101022	FA50/OE	0.193
25PFRC009	94	95	M101023	FA50/OE	0.055
25PFRC009	95	96	M101024	FA50/OE	0.169
25PFRC009	96	97	M101025	FA50/OE	0.1
25PFRC009	97	98	M101026	FA50/OE	0.234
25PFRC009	98	99	M101027	FA50/OE	0.157
25PFRC009	99	100	M101028	FA50/OE	0.461
25PFRC010	0	1	M101029	FA50/OE	0.32
25PFRC010	1	2	M101030	FA50/OE	0.214
25PFRC010	2	3	M101031	FA50/OE	0.054
25PFRC010	3	4	M101032	FA50/OE	0.016
25PFRC010	4	5	M101033	FA50/OE	0.024
25PFRC010	5	6	M101034	FA50/OE	0.033
25PFRC010	6	7	M101035	FA50/OE	0.012
25PFRC010	7	8	M101036	FA50/OE	0.028
25PFRC010	8	9	M101037	FA50/OE	0.061
25PFRC010	9	10	M101038	FA50/OE	0.132
25PFRC010	10	11	M101039	FA50/OE	0.283
25PFRC010	11	12	M101040	FA50/OE	0.131
25PFRC010	12	13	M101041	FA50/OE	0.039
25PFRC010	13	14	M101042	FA50/OE	0.049
25PFRC010	14	15	M101043	FA50/OE	0.038
25PFRC010	15	16	M101044	FA50/OE	0.053
25PFRC010	16	17	M101045	FA50/OE	0.192
25PFRC010	17	18	M101046	FA50/OE	0.124
25PFRC010	18	19	M101047	FA50/OE	0.066
25PFRC010	19	20	M101048	FA50/OE	0.057
25PFRC010	20	21	M101051	FA50/OE	0.046
25PFRC010	21	22	M101052	FA50/OE	0.049
25PFRC010	22	23	M101053	FA50/OE	0.041
25PFRC010	23	24	M101054	FA50/OE	0.05
25PFRC010	24	25	M101055	FA50/OE	0.138
25PFRC010	25	26	M101056	FA50/OE	0.031
25PFRC010	26	27	M101057	FA50/OE	0.026
25PFRC010	27	28	M101058	FA50/OE	0.051
25PFRC010	28	29	M101059	FA50/OE	0.065
25PFRC010	29	30	M101060	FA50/OE	0.147
25PFRC010	30	31	M101061	FA50/OE	0.07
25PFRC010	31	32	M101062	FA50/OE	2.577
25PFRC010	32	33	M101063	FA50/OE	0.902
25PFRC010	33	34	M101064	FA50/OE	0.157
25PFRC010	34	35	M101065	FA50/OE	0.059
25PFRC010	35	36	M101066	FA50/OE	0.02
25PFRC010	36	37	M101067	FA50/OE	0.014
25PFRC010	37	38	M101068	FA50/OE	0.007
25PFRC010	38	39	M101069	FA50/OE	0.331
25PFRC010	39	40	M101070	FA50/OE	0.323
25PFRC010	40	41	M101074	FA50/OE	1.113
25PFRC010	41	42	M101075	FA50/OE	0.012
25PFRC010	42	43	M101076	FA50/OE	0.047
25PFRC010	43	44	M101077	FA50/OE	0.054
25PFRC010	44	45	M101078	FA50/OE	0.052
25PFRC010	45	46	M101079	FA50/OE	0.091
25PFRC010	46	47	M101080	FA50/OE	0.026
25PFRC010	47	48	M101081	FA50/OE	0.293
25PFRC010	48	49	M101082	FA50/OE	0.16
25PFRC010	49	50	M101083	FA50/OE	0.276
25PFRC010	50	51	M101084	FA50/OE	0.16
25PFRC010	51	52	M101085	FA50/OE	0.059
25PFRC010	52	53	M101086	FA50/OE	0.057
25PFRC010	53	54	M101087	FA50/OE	0.225
25PFRC010	54	55	M101088	FA50/OE	0.083
25PFRC010	55	56	M101089	FA50/OE	0.056

For personal use only

25PFRC010	56	57	M101090	FA50/OE	0.02
25PFRC010	57	58	M101091	FA50/OE	0.084
25PFRC010	58	59	M101092	FA50/OE	0.943
25PFRC010	59	60	M101095	FA50/OE	0.078
25PFRC010	60	61	M101096	FA50/OE	0.03
25PFRC010	61	62	M101097	FA50/OE	0.052
25PFRC010	62	63	M101098	FA50/OE	0.08
25PFRC010	63	64	M101099	FA50/OE	0.165
25PFRC010	64	65	M101100	FA50/OE	0.064
25PFRC010	65	66	M101101	FA50/OE	0.028
25PFRC010	66	67	M101102	FA50/OE	0.025
25PFRC010	67	68	M101103	FA50/OE	0.025
25PFRC010	68	69	M101104	FA50/OE	0.023
25PFRC010	69	70	M101105	FA50/OE	0.024
25PFRC011	0	1	M101106	FA50/OE	0.084
25PFRC011	1	2	M101107	FA50/OE	0.065
25PFRC011	2	3	M101108	FA50/OE	0.032
25PFRC011	3	4	M101109	FA50/OE	0.015
25PFRC011	4	5	M101110	FA50/OE	0.012
25PFRC011	5	6	M101111	FA50/OE	0.013
25PFRC011	6	7	M101112	FA50/OE	0.023
25PFRC011	7	8	M101113	FA50/OE	0.018
25PFRC011	8	9	M101114	FA50/OE	0.01
25PFRC011	9	10	M101115	FA50/OE	0.008
25PFRC011	10	11	M101116	FA50/OE	-0.005
25PFRC011	11	12	M101117	FA50/OE	0.005
25PFRC011	12	13	M101118	FA50/OE	0.019
25PFRC011	13	14	M101119	FA50/OE	0.012
25PFRC011	14	15	M101120	FA50/OE	0.011
25PFRC011	15	16	M101121	FA50/OE	0.005
25PFRC011	16	17	M101122	FA50/OE	0.015
25PFRC011	17	18	M101123	FA50/OE	0.011
25PFRC011	18	19	M101124	FA50/OE	0.069
25PFRC011	19	20	M101125	FA50/OE	0.021
25PFRC011	20	21	M101128	FA50/OE	0.013
25PFRC011	21	22	M101129	FA50/OE	0.02
25PFRC011	22	23	M101130	FA50/OE	0.013
25PFRC011	23	24	M101131	FA50/OE	0.01
25PFRC011	24	25	M101132	FA50/OE	0.01
25PFRC011	25	26	M101133	FA50/OE	0.015
25PFRC011	26	27	M101134	FA50/OE	0.097
25PFRC011	27	28	M101135	FA50/OE	0.05
25PFRC011	28	29	M101136	FA50/OE	0.233
25PFRC011	29	30	M101137	FA50/OE	0.033
25PFRC011	30	31	M101138	FA50/OE	0.042
25PFRC011	31	32	M101139	FA50/OE	0.027
25PFRC011	32	33	M101140	FA50/OE	0.726
25PFRC011	33	34	M101141	FA50/OE	1.85
25PFRC011	34	35	M101142	FA50/OE	1.001
25PFRC011	35	36	M101143	FA50/OE	0.118
25PFRC011	36	37	M101144	FA50/OE	0.214
25PFRC011	37	38	M101145	FA50/OE	0.775
25PFRC011	38	39	M101146	FA50/OE	0.156
25PFRC011	39	40	M101147	FA50/OE	0.153
25PFRC011	40	41	M101150	FA50/OE	0.092
25PFRC011	41	42	M101151	FA50/OE	0.283
25PFRC011	42	43	M101152	FA50/OE	0.095
25PFRC011	43	44	M101153	FA50/OE	0.078
25PFRC011	44	45	M101154	FA50/OE	0.139
25PFRC011	45	46	M101155	FA50/OE	0.352
25PFRC011	46	47	M101156	FA50/OE	0.208
25PFRC011	47	48	M101157	FA50/OE	1.029
25PFRC011	48	49	M101158	FA50/OE	2.319

For personal use only

25PFRC011	49	50	M101159	FA50/OE	0.071
25PFRC011	50	51	M101160	FA50/OE	0.022
25PFRC011	51	52	M101161	FA50/OE	0.019
25PFRC011	52	53	M101162	FA50/OE	0.098
25PFRC011	53	54	M101163	FA50/OE	0.634
25PFRC011	54	55	M101164	FA50/OE	0.023
25PFRC011	55	56	M101165	FA50/OE	0.031
25PFRC011	56	57	M101166	FA50/OE	0.042
25PFRC011	57	58	M101167	FA50/OE	0.072
25PFRC011	58	59	M101168	FA50/OE	0.163
25PFRC011	59	60	M101169	FA50/OE	0.187
25PFRC011	60	61	M101172	FA50/OE	0.006
25PFRC011	61	62	M101173	FA50/OE	0.057
25PFRC011	62	63	M101174	FA50/OE	0.066
25PFRC011	63	64	M101175	FA50/OE	0.006
25PFRC011	64	65	M101176	FA50/OE	0.071
25PFRC011	65	66	M101177	FA50/OE	2.736
25PFRC011	66	67	M101178	FA50/OE	0.674
25PFRC011	67	68	M101179	FA50/OE	0.104
25PFRC011	68	69	M101180	FA50/OE	0.326
25PFRC011	69	70	M101181	FA50/OE	0.069
25PFRC011	70	71	M101182	FA50/OE	0.108
25PFRC011	71	72	M101183	FA50/OE	0.063
25PFRC011	72	73	M101184	FA50/OE	0.025
25PFRC011	73	74	M101185	FA50/OE	0.239
25PFRC011	74	75	M101186	FA50/OE	0.482
25PFRC011	75	76	M101187	FA50/OE	0.161
25PFRC011	76	77	M101188	FA50/OE	0.068
25PFRC011	77	78	M101189	FA50/OE	0.031
25PFRC011	78	79	M101190	FA50/OE	0.656
25PFRC011	79	80	M101191	FA50/OE	0.102
25PFRC011	80	81	M101194	FA50/OE	0.084
25PFRC011	81	82	M101195	FA50/OE	0.032
25PFRC011	82	83	M101196	FA50/OE	0.08
25PFRC011	83	84	M101197	FA50/OE	0.346
25PFRC011	84	85	M101198	FA50/OE	0.046
25PFRC011	85	86	M101199	FA50/OE	0.086
25PFRC011	86	87	M101200	FA50/OE	0.064
25PFRC011	87	88	M101201	FA50/OE	0.034
25PFRC011	88	89	M101202	FA50/OE	0.016
25PFRC011	89	90	M101203	FA50/OE	0.033
25PFRC011	90	91	M101204	FA50/OE	0.059
25PFRC011	91	92	M101205	FA50/OE	0.018
25PFRC011	92	93	M101206	FA50/OE	0.056
25PFRC011	93	94	M101207	FA50/OE	0.007
25PFRC011	94	95	M101208	FA50/OE	0.018
25PFRC011	95	96	M101209	FA50/OE	0.063
25PFRC011	96	97	M101210	FA50/OE	0.02
25PFRC011	97	98	M101211	FA50/OE	0.086
25PFRC011	98	99	M101212	FA50/OE	0.065
25PFRC011	99	100	M101213	FA50/OE	0.039
25PFRC011	100	101	M101217	FA50/OE	0.053
25PFRC011	101	102	M101218	FA50/OE	0.064
25PFRC011	102	103	M101219	FA50/OE	0.602
25PFRC011	103	104	M101220	FA50/OE	0.135
25PFRC011	104	105	M101221	FA50/OE	0.123
25PFRC011	105	106	M101222	FA50/OE	0.053
25PFRC011	106	107	M101223	FA50/OE	0.037
25PFRC011	107	108	M101224	FA50/OE	0.094
25PFRC011	108	109	M101225	FA50/OE	0.019
25PFRC011	109	110	M101226	FA50/OE	0.03
25PFRC012	0	1	M101227	FA50/OE	0.127
25PFRC012	1	2	M101228	FA50/OE	0.125

For personal use only

25PFRC012	2	3	M101229	FA50/OE	0.032
25PFRC012	3	4	M101230	FA50/OE	0.017
25PFRC012	4	5	M101231	FA50/OE	0.006
25PFRC012	5	6	M101232	FA50/OE	0.009
25PFRC012	6	7	M101233	FA50/OE	-0.005
25PFRC012	7	8	M101234	FA50/OE	0.007
25PFRC012	8	9	M101235	FA50/OE	-0.005
25PFRC012	9	10	M101236	FA50/OE	-0.005
25PFRC012	10	11	M101237	FA50/OE	0.01
25PFRC012	11	12	M101238	FA50/OE	0.08
25PFRC012	12	13	M101239	FA50/OE	0.029
25PFRC012	13	14	M101240	FA50/OE	0.008
25PFRC012	14	15	M101241	FA50/OE	0.02
25PFRC012	15	16	M101244	FA50/OE	0.032
25PFRC012	16	17	M101245	FA50/OE	0.01
25PFRC012	17	18	M101246	FA50/OE	0.011
25PFRC012	18	19	M101247	FA50/OE	-0.005
25PFRC012	19	20	M101248	FA50/OE	0.012
25PFRC012	20	21	M101249	FA50/OE	0.006
25PFRC012	21	22	M101250	FA50/OE	0.012
25PFRC012	22	23	M101251	FA50/OE	0.013
25PFRC012	23	24	M101252	FA50/OE	0.007
25PFRC012	24	25	M101253	FA50/OE	0.007
25PFRC012	25	26	M101254	FA50/OE	0.011
25PFRC012	26	27	M101255	FA50/OE	0.009
25PFRC012	27	28	M101256	FA50/OE	-0.005
25PFRC012	28	29	M101257	FA50/OE	0.017
25PFRC012	29	30	M101258	FA50/OE	0.015
25PFRC012	30	31	M101259	FA50/OE	0.051
25PFRC012	31	32	M101260	FA50/OE	0.023
25PFRC012	32	33	M101261	FA50/OE	0.071
25PFRC012	33	34	M101262	FA50/OE	0.097
25PFRC012	34	35	M101263	FA50/OE	0.028
25PFRC012	35	36	M101264	FA50/OE	0.133
25PFRC012	36	37	M101265	FA50/OE	0.013
25PFRC012	37	38	M101266	FA50/OE	0.017
25PFRC012	38	39	M101267	FA50/OE	0.01
25PFRC012	39	40	M101268	FA50/OE	0.011
25PFRC012	40	41	M101271	FA50/OE	0.044
25PFRC012	41	42	M101272	FA50/OE	-0.005
25PFRC012	42	43	M101273	FA50/OE	0.006
25PFRC012	43	44	M101274	FA50/OE	0.016
25PFRC012	44	45	M101275	FA50/OE	0.072
25PFRC012	45	46	M101276	FA50/OE	0.016
25PFRC012	46	47	M101277	FA50/OE	0.031
25PFRC012	47	48	M101278	FA50/OE	0.006
25PFRC012	48	49	M101279	FA50/OE	0.013
25PFRC012	49	50	M101280	FA50/OE	0.018
25PFRC012	50	51	M101281	FA50/OE	0.022
25PFRC012	51	52	M101282	FA50/OE	0.017
25PFRC012	52	53	M101283	FA50/OE	0.018
25PFRC012	53	54	M101284	FA50/OE	0.019
25PFRC012	54	55	M101285	FA50/OE	0.018
25PFRC012	55	56	M101286	FA50/OE	0.055
25PFRC012	56	57	M101287	FA50/OE	0.009
25PFRC012	57	58	M101288	FA50/OE	0.037
25PFRC012	58	59	M101289	FA50/OE	0.026
25PFRC012	59	60	M101290	FA50/OE	0.012
25PFRC012	60	61	M101291	FA50/OE	0.013
25PFRC012	61	62	M101292	FA50/OE	0.018
25PFRC012	62	63	M101293	FA50/OE	0.024
25PFRC012	63	64	M101294	FA50/OE	0.022
25PFRC012	64	65	M101295	FA50/OE	0.027

For personal use only

25PFRC012	65	66	M101296	FA50/OE	0.014
25PFRC012	66	67	M101297	FA50/OE	0.026
25PFRC012	67	68	M101298	FA50/OE	0.076
25PFRC012	68	69	M101299	FA50/OE	0.046
25PFRC012	69	70	M101300	FA50/OE	0.008
25PFRC012	70	71	M101304	FA50/OE	0.015
25PFRC012	71	72	M101305	FA50/OE	0.136
25PFRC012	72	73	M101306	FA50/OE	0.077
25PFRC012	73	74	M101307	FA50/OE	0.063
25PFRC012	74	75	M101308	FA50/OE	0.008
25PFRC012	75	76	M101309	FA50/OE	0.007
25PFRC012	76	77	M101310	FA50/OE	0.008
25PFRC012	77	78	M101311	FA50/OE	0.023
25PFRC012	78	79	M101312	FA50/OE	0.009
25PFRC012	79	80	M101313	FA50/OE	0.023
25PFRC012	80	81	M101314	FA50/OE	0.024
25PFRC012	81	82	M101315	FA50/OE	0.019
25PFRC012	82	83	M101316	FA50/OE	0.027
25PFRC012	83	84	M101317	FA50/OE	0.034
25PFRC012	84	85	M101318	FA50/OE	0.013
25PFRC012	85	86	M101319	FA50/OE	0.025
25PFRC012	86	87	M101320	FA50/OE	0.016
25PFRC012	87	88	M101321	FA50/OE	0.01
25PFRC012	88	89	M101322	FA50/OE	0.052
25PFRC012	89	90	M101323	FA50/OE	0.061
25PFRC012	90	91	M101324	FA50/OE	0.037
25PFRC012	91	92	M101325	FA50/OE	0.297
25PFRC012	92	93	M101326	FA50/OE	0.058
25PFRC012	93	94	M101327	FA50/OE	0.031
25PFRC012	94	95	M101328	FA50/OE	0.03
25PFRC012	95	96	M101329	FA50/OE	0.062
25PFRC012	96	97	M101330	FA50/OE	0.064
25PFRC012	97	98	M101331	FA50/OE	0.049
25PFRC012	98	99	M101334	FA50/OE	0.036
25PFRC012	99	100	M101335	FA50/OE	0.022
25PFRC013	0	1	M101336	FA50/OE	0.06
25PFRC013	1	2	M101337	FA50/OE	0.06
25PFRC013	2	3	M101338	FA50/OE	0.019
25PFRC013	3	4	M101339	FA50/OE	0.035
25PFRC013	4	5	M101340	FA50/OE	0.046
25PFRC013	5	6	M101341	FA50/OE	0.022
25PFRC013	6	7	M101342	FA50/OE	0.01
25PFRC013	7	8	M101343	FA50/OE	0.007
25PFRC013	8	9	M101344	FA50/OE	-0.005
25PFRC013	9	10	M101345	FA50/OE	0.026
25PFRC013	10	11	M101346	FA50/OE	0.016
25PFRC013	11	12	M101347	FA50/OE	-0.005
25PFRC013	12	13	M101348	FA50/OE	0.042
25PFRC013	13	14	M101349	FA50/OE	0.033
25PFRC013	14	15	M101350	FA50/OE	-0.005
25PFRC013	15	16	M101351	FA50/OE	0.007
25PFRC013	16	17	M101352	FA50/OE	0.011
25PFRC013	17	18	M101353	FA50/OE	0.006
25PFRC013	18	19	M101354	FA50/OE	0.008
25PFRC013	19	20	M101355	FA50/OE	0.008
25PFRC013	20	21	M101358	FA50/OE	0.016
25PFRC013	21	22	M101359	FA50/OE	0.008
25PFRC013	22	23	M101360	FA50/OE	0.009
25PFRC013	23	24	M101361	FA50/OE	0.017
25PFRC013	24	25	M101362	FA50/OE	0.037
25PFRC013	25	26	M101363	FA50/OE	0.06
25PFRC013	26	27	M101364	FA50/OE	0.058
25PFRC013	27	28	M101365	FA50/OE	0.04

For personal use only

25PFRC013	28	29	M101366	FA50/OE	0.109
25PFRC013	29	30	M101367	FA50/OE	0.061
25PFRC013	30	31	M101368	FA50/OE	0.021
25PFRC013	31	32	M101369	FA50/OE	0.041
25PFRC013	32	33	M101370	FA50/OE	0.014
25PFRC013	33	34	M101371	FA50/OE	0.022
25PFRC013	34	35	M101372	FA50/OE	0.023
25PFRC013	35	36	M101373	FA50/OE	0.088
25PFRC013	36	37	M101374	FA50/OE	0.014
25PFRC013	37	38	M101375	FA50/OE	0.013
25PFRC013	38	39	M101376	FA50/OE	0.019
25PFRC013	39	40	M101377	FA50/OE	0.014
25PFRC013	40	41	M101381	FA50/OE	0.021
25PFRC013	41	42	M101382	FA50/OE	0.012
25PFRC013	42	43	M101383	FA50/OE	0.011
25PFRC013	43	44	M101384	FA50/OE	0.014
25PFRC013	44	45	M101385	FA50/OE	0.017
25PFRC013	45	46	M101386	FA50/OE	0.018
25PFRC013	46	47	M101387	FA50/OE	0.02
25PFRC013	47	48	M101388	FA50/OE	0.02
25PFRC013	48	49	M101389	FA50/OE	0.033
25PFRC013	49	50	M101390	FA50/OE	0.013
25PFRC013	50	51	M101391	FA50/OE	0.015
25PFRC013	51	52	M101392	FA50/OE	0.02
25PFRC013	52	53	M101393	FA50/OE	-0.005
25PFRC013	53	54	M101394	FA50/OE	0.027
25PFRC013	54	55	M101395	FA50/OE	0.011
25PFRC013	55	56	M101396	FA50/OE	-0.005
25PFRC013	56	57	M101397	FA50/OE	0.024
25PFRC013	57	58	M101398	FA50/OE	0.014
25PFRC013	58	59	M101399	FA50/OE	0.007
25PFRC013	59	60	M101400	FA50/OE	0.021
25PFRC013	60	61	M101401	FA50/OE	0.013
25PFRC013	61	62	M101402	FA50/OE	0.027
25PFRC013	62	63	M101403	FA50/OE	0.013
25PFRC013	63	64	M101404	FA50/OE	0.008
25PFRC013	64	65	M101405	FA50/OE	0.014
25PFRC013	65	66	M101406	FA50/OE	0.013
25PFRC013	66	67	M101407	FA50/OE	-0.005
25PFRC013	67	68	M101408	FA50/OE	0.008
25PFRC013	68	69	M101409	FA50/OE	0.006
25PFRC013	69	70	M101410	FA50/OE	0.01
25PFRC013	70	71	M101413	FA50/OE	0.005
25PFRC013	71	72	M101414	FA50/OE	0.009
25PFRC013	72	73	M101415	FA50/OE	0.01
25PFRC013	73	74	M101416	FA50/OE	0.007
25PFRC013	74	75	M101417	FA50/OE	0.031
25PFRC013	75	76	M101418	FA50/OE	0.031
25PFRC013	76	77	M101419	FA50/OE	0.025
25PFRC013	77	78	M101420	FA50/OE	0.017
25PFRC013	78	79	M101421	FA50/OE	0.011
25PFRC013	79	80	M101422	FA50/OE	0.08
25PFRC013	80	81	M101423	FA50/OE	0.119
25PFRC013	81	82	M101424	FA50/OE	1.842
25PFRC013	82	83	M101425	FA50/OE	0.131
25PFRC013	83	84	M101426	FA50/OE	0.042
25PFRC013	84	85	M101427	FA50/OE	0.028
25PFRC013	85	86	M101428	FA50/OE	0.014
25PFRC013	86	87	M101429	FA50/OE	0.007
25PFRC013	87	88	M101430	FA50/OE	0.026
25PFRC013	88	89	M101431	FA50/OE	0.035
25PFRC013	89	90	M101432	FA50/OE	0.034
25PFRC013	90	91	M101433	FA50/OE	0.027

For personal use only

25PFRC013	91	92	M101434	FA50/OE	0.013
25PFRC013	92	93	M101435	FA50/OE	0.035
25PFRC013	93	94	M101436	FA50/OE	0.015
25PFRC013	94	95	M101437	FA50/OE	0.042
25PFRC013	95	96	M101438	FA50/OE	0.076
25PFRC013	96	97	M101439	FA50/OE	0.022
25PFRC013	97	98	M101440	FA50/OE	0.016
25PFRC013	98	99	M101441	FA50/OE	0.018
25PFRC013	99	100	M101442	FA50/OE	0.016
25PFRC014	0	1	M101445	FA50/OE	0.041
25PFRC014	1	2	M101446	FA50/OE	0.061
25PFRC014	2	3	M101447	FA50/OE	0.175
25PFRC014	3	4	M101448	FA50/OE	0.054
25PFRC014	4	5	M101449	FA50/OE	0.04
25PFRC014	5	6	M101450	FA50/OE	0.011
25PFRC014	6	7	M101451	FA50/OE	0.017
25PFRC014	7	8	M101452	FA50/OE	0.014
25PFRC014	8	9	M101453	FA50/OE	0.021
25PFRC014	9	10	M101454	FA50/OE	0.024
25PFRC014	10	11	M101455	FA50/OE	0.091
25PFRC014	11	12	M101456	FA50/OE	0.05
25PFRC014	12	13	M101457	FA50/OE	0.043
25PFRC014	13	14	M101458	FA50/OE	0.021
25PFRC014	14	15	M101459	FA50/OE	0.028
25PFRC014	15	16	M101460	FA50/OE	0.051
25PFRC014	16	17	M101461	FA50/OE	0.042
25PFRC014	17	18	M101462	FA50/OE	0.043
25PFRC014	18	19	M101463	FA50/OE	0.047
25PFRC014	19	20	M101464	FA50/OE	0.021
25PFRC014	20	21	M101467	FA50/OE	0.024
25PFRC014	21	22	M101468	FA50/OE	0.049
25PFRC014	22	23	M101469	FA50/OE	0.05
25PFRC014	23	24	M101470	FA50/OE	0.024
25PFRC014	24	25	M101471	FA50/OE	0.028
25PFRC014	25	26	M101472	FA50/OE	0.028
25PFRC014	26	27	M101473	FA50/OE	0.013
25PFRC014	27	28	M101474	FA50/OE	0.013
25PFRC014	28	29	M101475	FA50/OE	0.014
25PFRC014	29	30	M101476	FA50/OE	0.012
25PFRC014	30	31	M101477	FA50/OE	0.022
25PFRC014	31	32	M101478	FA50/OE	0.017
25PFRC014	32	33	M101479	FA50/OE	0.023
25PFRC014	33	34	M101480	FA50/OE	0.026
25PFRC014	34	35	M101481	FA50/OE	0.028
25PFRC014	35	36	M101482	FA50/OE	0.038
25PFRC014	36	37	M101483	FA50/OE	0.03
25PFRC014	37	38	M101484	FA50/OE	0.024
25PFRC014	38	39	M101485	FA50/OE	0.018
25PFRC014	39	40	M101486	FA50/OE	0.042
25PFRC014	40	41	M101490	FA50/OE	0.009
25PFRC014	41	42	M101491	FA50/OE	0.011
25PFRC014	42	43	M101492	FA50/OE	0.009
25PFRC014	43	44	M101493	FA50/OE	0.014
25PFRC014	44	45	M101494	FA50/OE	0.02
25PFRC014	45	46	M101495	FA50/OE	0.017
25PFRC014	46	47	M101496	FA50/OE	0.033
25PFRC014	47	48	M101497	FA50/OE	0.017
25PFRC014	48	49	M101498	FA50/OE	0.023
25PFRC014	49	50	M101499	FA50/OE	0.041
25PFRC014	50	51	M101500	FA50/OE	0.024
25PFRC014	51	52	M101501	FA50/OE	0.045
25PFRC014	52	53	M101502	FA50/OE	0.031
25PFRC014	53	54	M101503	FA50/OE	0.345

For personal use only

25PFRC014	54	55	M101504	FA50/OE	0.038
25PFRC014	55	56	M101505	FA50/OE	0.038
25PFRC014	56	57	M101506	FA50/OE	0.049
25PFRC014	57	58	M101507	FA50/OE	0.029
25PFRC014	58	59	M101508	FA50/OE	0.035
25PFRC014	59	60	M101509	FA50/OE	0.022
25PFRC014	60	61	M101512	FA50/OE	0.012
25PFRC014	61	62	M101513	FA50/OE	0.013
25PFRC014	62	63	M101514	FA50/OE	0.014
25PFRC014	63	64	M101515	FA50/OE	0.071
25PFRC014	64	65	M101516	FA50/OE	0.053
25PFRC014	65	66	M101517	FA50/OE	0.018
25PFRC014	66	67	M101518	FA50/OE	0.014
25PFRC014	67	68	M101519	FA50/OE	0.016
25PFRC014	68	69	M101520	FA50/OE	0.015
25PFRC014	69	70	M101521	FA50/OE	0.018
25PFRC014	70	71	M101522	FA50/OE	0.015
25PFRC014	71	72	M101523	FA50/OE	0.016
25PFRC014	72	73	M101524	FA50/OE	0.032
25PFRC014	73	74	M101525	FA50/OE	0.057
25PFRC014	74	75	M101526	FA50/OE	0.025
25PFRC014	75	76	M101527	FA50/OE	0.044
25PFRC014	76	77	M101528	FA50/OE	0.039
25PFRC014	77	78	M101529	FA50/OE	0.072
25PFRC014	78	79	M101530	FA50/OE	0.022
25PFRC014	79	80	M101531	FA50/OE	0.016
25PFRC014	80	81	M101535	FA50/OE	0.01
25PFRC014	81	82	M101536	FA50/OE	0.018
25PFRC014	82	83	M101537	FA50/OE	0.021
25PFRC014	83	84	M101538	FA50/OE	0.013
25PFRC014	84	85	M101539	FA50/OE	0.011
25PFRC014	85	86	M101540	FA50/OE	0.015
25PFRC014	86	87	M101541	FA50/OE	-0.005
25PFRC014	87	88	M101542	FA50/OE	0.014
25PFRC014	88	89	M101543	FA50/OE	0.016
25PFRC014	89	90	M101544	FA50/OE	0.033
25PFRC014	90	91	M101545	FA50/OE	0.007
25PFRC014	91	92	M101546	FA50/OE	0.007
25PFRC014	92	93	M101547	FA50/OE	0.009
25PFRC014	93	94	M101548	FA50/OE	0.006
25PFRC014	94	95	M101549	FA50/OE	-0.005
25PFRC014	95	96	M101550	FA50/OE	-0.005
25PFRC014	96	97	M101551	FA50/OE	0.015
25PFRC014	97	98	M101552	FA50/OE	0.032
25PFRC014	98	99	M101553	FA50/OE	0.013
25PFRC014	99	100	M101554	FA50/OE	0.011
25PFRC014	100	101	M101557	FA50/OE	0.021
25PFRC014	101	102	M101558	FA50/OE	0.021
25PFRC014	102	103	M101559	FA50/OE	0.016
25PFRC014	103	104	M101560	FA50/OE	0.016
25PFRC014	104	105	M101561	FA50/OE	0.112
25PFRC014	105	106	M101562	FA50/OE	0.021
25PFRC014	106	107	M101563	FA50/OE	0.022
25PFRC014	107	108	M101564	FA50/OE	0.012
25PFRC014	108	109	M101565	FA50/OE	0.044
25PFRC014	109	110	M101566	FA50/OE	0.047
25PFRC014	110	111	M101567	FA50/OE	0.019
25PFRC014	111	112	M101568	FA50/OE	0.112
25PFRC014	112	113	M101569	FA50/OE	0.119
25PFRC014	113	114	M101570	FA50/OE	0.135
25PFRC014	114	115	M101571	FA50/OE	0.12
25PFRC014	115	116	M101572	FA50/OE	0.204
25PFRC014	116	117	M101573	FA50/OE	0.066

For personal use only

25PFRC014	117	118	M101574	FA50/OE	0.054
25PFRC014	118	119	M101575	FA50/OE	0.044
25PFRC014	119	120	M101576	FA50/OE	0.023
25PFRC014	120	121	M101577	FA50/OE	-0.005
25PFRC014	121	122	M101578	FA50/OE	0.019
25PFRC014	122	123	M101579	FA50/OE	0.378
25PFRC014	123	124	M101580	FA50/OE	0.02
25PFRC014	124	125	M101581	FA50/OE	0.032
25PFRC014	125	126	M101582	FA50/OE	0.011
25PFRC014	126	127	M101583	FA50/OE	0.021
25PFRC014	127	128	M101584	FA50/OE	0.017
25PFRC014	128	129	M101585	FA50/OE	0.052
25PFRC014	129	130	M101586	FA50/OE	0.021
25PFRC014	130	131	M101587	FA50/OE	0.254
25PFRC014	131	132	M101588	FA50/OE	0.065