

ASX Announcement

27 May 2025

KINGSROSE-BHP ALLIANCES UPDATE

Kingsrose Mining Limited (ASX: KRM) (**Kingsrose** or **Company**) is pleased to provide a progress update on the Finnmark (Norway) and Central Finland exploration alliances with BHP (through a wholly-owned subsidiary) (**Alliances**).

HIGHLIGHTS

- In May 2024 Kingsrose commenced one of the largest generative exploration programs globally, under Alliances funded by BHP (see ASX announcement dated 22 May 2024).
- With the support of BHP's generative exploration expertise, Kingsrose is applying mineral systems analysis of the mineral belts to identify the most prospective areas for discovery of polymetallic copper-nickel-PGE massive sulphides.
- To date, BHP has provided total Alliance funding of US\$5.84 million (US\$3.84 million to the Finnmark Alliance and US\$2.00 million to the Central Finland Alliance), exceeding its commitment to fund US\$ 5.00 million during year 1 of the Alliances.
- Pursuant to the terms of the Alliance Agreements, BHP has elected to cease funding of and terminate the Central Finland Alliance in order to focus on the Finnmark Alliance.
- Kingsrose has further consolidated exploration tenure in Finnmark through entry into an option to acquire the Gallujavri project from EMX Royalty Corp.
- The work program and budget approved by the Management Committee of the Finnmark Alliance for FY2026 totals approximately US\$3.50 million.

Fabian Baker, Managing Director, commented *“During the past year we achieved one of the largest generative exploration programs globally. It is a rare opportunity to explore entire mineral belts from first principles; we are grateful to BHP for supporting these efforts financially and with the support and expertise of their multidisciplinary teams. The upcoming work program will produce proprietary datasets over more than 200 kilometres strike of the Karasjok and Kautokeino Greenstone Belts, to define the most prospective areas for potential ‘camps’ of copper-nickel-PGE sulphide mineral deposits.”*

FINNMARK ALLIANCE

Following encouraging geological results and meaningful progress in community engagement, BHP has elected to progress the Finnmark Alliance into its second year with increased exploration funding of US\$3.50 million. Kingsrose and BHP believe the region holds potential for globally significant discoveries.

The second year of the Alliance aims to complete a ‘play scale’ prospectivity assessment across the Finnmark Area of Interest with a view to the development of camps of intrusions deemed prospective for accumulations of Cu-Ni-PGE massive sulphides. To achieve this Kingsrose has designed an ambitious programme of airborne gravity gradiometry surveys covering the remainder of its un-flown tenure, to be followed up with regional-scale airborne helicopter EM surveys. When combined, these datasets will aid in

**ASX:KRM**

Suite 5 CPC, 145 Stirling Highway, Nedlands Western Australia 6009 • ABN 49 112 389 910

E: info@kingsrose.com T: +61 8 9389 3190 W: kingsrose.com

identifying conductive bodies spatially associated with intrusions, which field teams will ground truth through field mapping and prospecting during the coming European summer.

Results of the 2025 work program will be used to prioritise camps or clusters of mafic-ultramafic intrusions based on geophysical response, geochemical signature, and geochronological and structural setting for follow-up detailed ground surveys in order to generate drill targets.

Gallujavri Option Agreement

In order to expand and consolidate exploration tenure in the Karasjok Greenstone Belt, Kingsrose, under the Finnmark Alliance, has executed an option agreement (Option) to acquire the Gallujavri nickel-copper-PGE project in Finnmark County, Norway from EMX Royalty Corp (EMX) (Figure 1).

Gallujavri hosts a 16 km trend of mafic-ultramafic intrusions where historical work has identified occurrences of disseminated pyrrhotite-pentlandite and minor chalcopyrite with anomalous nickel, copper and PGE concentrations (Figure 2, Appendix 1 and Appendix 2). Additionally, age dating work conducted by the Norwegian Geological Survey (NGU) has returned an age of 2.05Ga for the Gallujavri intrusion, which is the same age as the host intrusion to the Kevitsa and Sakatti deposits in Finland (see announcement dated 19 July 2024 and Höytiä et al., 2025).

The material acquisition terms for the Gallujavri project are summarised, as follows. The transaction costs of the Option will be funded by the Alliance.

- **On signing Definitive Option Agreement:**
 - \$38,000 cash payment.
- **Option Period (Up to Four Years):**
 - Annual cash payments to EMX: \$6,660.
 - Annual minimum work commitments totalling \$665,000 over 4 years, as follows: \$65,000 (Year 1), \$100,000 (Year 2), \$250,000 (Year 3), \$250,000 (Year 4).
 - Option exercise payment of \$150,000 and grant of a 1% Net Smelter Return Royalty (details below) to acquire a 100% interest in the project, exercisable at any time during the four-year option period.
- **Deferred Consideration:**
 - \$1,000,000 cash on publication of a Mineral Resource.
 - \$2,000,000 cash on a final investment decision to develop a mine.
- **Net Smelter Return Royalty:**
 - 1% NSR.
 - Kingsrose holds the right to buy back 0.25% for \$3.75 million on or before the fourth anniversary of the option exercise.
 - Annual advance royalty payments payable following exercise of option:
 - \$25,000 per year, increasing by 10% annually, capped at \$75,000 per year.
 - Advance royalty payments will be deducted from future NSR payments (if applicable).

CENTRAL FINLAND ALLIANCE

Pursuant to the terms of the Alliance Agreements, BHP has elected to cease funding of and terminate the Central Finland Alliance in order to focus on the Finnmark Alliance. All exploration tenure will be retained 100% by Kingsrose, including the Jakon Project recently acquired from Rio Tinto Exploration Finland Oy (RTX) where initial drilling by RTX intercepted significant intervals of sulphide Ni-Cu-Co mineralisation (Plates 1 & 2, see ASX announcement dated 28 February 2025). The Company is assessing options to progress these assets including through new joint venture partnerships.

Kingsrose believes its significant landholding in an underexplored mineral belt represents a compelling opportunity for other mining companies currently active in, or seeking to enter, the region, to investigate joint venture opportunities with Kingsrose, particularly amid a notable increase in industry interest across Central Finland.



Plate 1 (Left): Massive and blebby pyrrhotite-pentlandite-chalcopyrite hosted by coarse grained gabbro from a 1.48 m sample that returned 1.8% Ni, 0.2% Cu, 0.08% Co from 273.22 m, KUSK0015 (RTX drilling).
Plate 2 (Right): Massive pyrrhotite-pentlandite-chalcopyrite hosted by medium grained pyroxenite from a 0.54 m sample that returned 3.7% Ni, 0.20% Cu, 0.15% Co from 361.0 m, KUSK0015 (RTX drilling).

- ENDS -

This announcement has been authorised for release to the ASX by the Managing Director.

For further information regarding the Company and its projects please visit www.kingsrose.com

For more information please contact:

Fabian Baker
Managing Director
+61 893 894 494
info@kingsrose.com

Scott North
Corporate Development Manager
+61 477 007 414
Scott.North@Kingsrose.com

ABOUT KINGSROSE MINING LIMITED

Kingsrose Mining Limited is a leading sustainability-conscious and technically proficient mineral exploration company listed on the ASX. The Company has a discovery-focused strategy, targeting the acquisition and exploration of critical mineral deposits. This has resulted in the acquisition of, or joint venture into, the Råna nickel-copper-cobalt and Penikat PGE projects in Norway and Finland. Additionally, Kingsrose was selected for the first cohort of the BHP Xplor exploration accelerator program which operated from January to June 2023.

FORWARD-LOOKING STATEMENTS

This announcement includes forward-looking statements, including forward-looking statements relating to the future operation of the Company. These forward-looking statements are based on the Company's expectations and beliefs concerning future events. Forward-looking statements are necessarily subject to risks, uncertainties and other factors, many of which are outside the control of the Company, which could cause actual results to differ materially from such statements. The Company makes no undertaking to subsequently update or revise the forward-looking statements made in this announcement to reflect the circumstances or events after the date of this announcement.

You are strongly cautioned not to place undue reliance on forward-looking statements.

COMPETENT PERSONS STATEMENT

The information in this report that relates to the Finnmark Alliance and Exploration Results at the Gallujavri Project is based on information compiled under the supervision of Andrew Tunningley, who is a Member and Chartered Professional (Geology) of the Australasian Institute of Mining and Metallurgy and is Head of Exploration for Kingsrose Mining Limited. Mr Tunningley has sufficient experience that is relevant to the style of mineralisation and type of deposit under consideration and to the activity which he is undertaking to qualify as a Competent Person as defined in the 2012 Edition of the "Australasian Code for Reporting Exploration Results, Mineral Resources and Ore Reserves." Mr Tunningley consents to the inclusion in this report of the matters based on this information in the form and context in which it appears.

The information in this report that relates to the Exploration Results concerning the Central Finland Alliance was first reported by the Company in compliance with the 2012 edition of the JORC Code in an ASX announcement dated 28 February 2025. The Company confirms that it is not aware of any new information or data that materially affects the information included in the ASX release referred to above and it further confirms that all material assumptions and technical parameters underpinning the exploration results continue to apply and have not materially changed.

Appendix 1 – JORC Code Table 1 for the Gallujavri Project

Section 1 Sampling Techniques and Data

(Criteria in this section apply to all succeeding sections)

Criteria	JORC Code explanation	Commentary
Sampling techniques	<ul style="list-style-type: none"> Nature and quality of sampling (e.g. cut channels, random chips, or specific industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc). These examples should not be taken as limiting the broad meaning of sampling. Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used. Aspects of the determination of mineralization that are Material to the Public Report. In cases where 'industry standard' work has been done this would be relatively simple (eg 'reverse circulation drilling was used to obtain 1m samples from which 3kg was pulverised to produce a 30g charge for fire assay'). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (eg submarine nodules) may warrant disclosure of detailed information. 	<ul style="list-style-type: none"> The historical exploration drilling results were not completed under the supervision of the Competent Person or Kingsrose. The sampling techniques are not known.
Drilling techniques	<ul style="list-style-type: none"> Drill type (eg core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (eg core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc). 	<ul style="list-style-type: none"> The historical exploration drilling results were not completed under the supervision of the Competent Person or Kingsrose, and the drilling techniques are not known.
Drill sample recovery	<ul style="list-style-type: none"> Method of recording and assessing core and chip sample recoveries and results assessed. Measures taken to maximise sample recovery and ensure representative nature of the samples. Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material. 	<ul style="list-style-type: none"> The historical exploration drilling results were not completed under the supervision of the Competent Person or Kingsrose, and the method of recording and assessing drill core recoveries, measures taken to maximise sample recovery and representative nature of samples, and the relationship between sample recovery and grade and whether sample bias may have occurred are not known.
Logging	<ul style="list-style-type: none"> Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies. 	<ul style="list-style-type: none"> Historical drill core was geologically logged Historical drill core photos are not available Historical logging was qualitative All historical drill core was logged

Criteria	JORC Code explanation	Commentary
	<ul style="list-style-type: none"> Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc) photography. The total length and percentage of the relevant intersections logged. 	
Sub-sampling techniques and sample preparation	<ul style="list-style-type: none"> If core, whether cut or sawn and whether quarter, half or all core taken. If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled wet or dry. For all sample types, the nature, quality and appropriateness of the sample preparation technique. Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples. Measures taken to ensure that the sampling is representative of the in situ material collected, incl. for instance results for field duplicate/second-half sampling. Whether sample sizes are appropriate to the grain size of the material being sampled. 	<ul style="list-style-type: none"> The historical exploration drilling results were not completed under the supervision of the Competent Person or Kingsrose, and the sub-sampling techniques and sample preparation methods are not known.
Quality of assay data and laboratory tests	<ul style="list-style-type: none"> The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total. For geophysical tools, spectrometers, handheld XRF instruments, etc, the parameters used in determining the analysis incl. instrument make and model, reading times, calibrations factors applied and their derivation, etc. Nature of quality control procedures adopted (eg standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (ie lack of bias) and precision have been established. 	<ul style="list-style-type: none"> The historical exploration drilling results were not completed under the supervision of the Competent Person or Kingsrose. The nature, quality and appropriateness of the assaying and laboratory procedures is not known and nature of quality control procedures adopted are not known.
Verification of sampling and assaying	<ul style="list-style-type: none"> The verification of significant intersections by either independent or alternative company personnel. The use of twinned holes. Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols. Discuss any adjustment to assay data. 	<ul style="list-style-type: none"> No verification of significant intercepts has been undertaken. No twinned holes. The historical exploration drilling results were not completed under the supervision of the Competent Person or Kingsrose and documentation procedures of primary data, data verification and data storage are not known. Kingsrose has not adjusted any of the historical exploration data.
Location of data points	<ul style="list-style-type: none"> Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and 	<ul style="list-style-type: none"> The historical exploration drilling results were not completed under the supervision of the Competent Person or Kingsrose and the accuracy and quality of surveys used to locate drill holes is not known.

Criteria	JORC Code explanation	Commentary
	<p>other locations used in Mineral Resource estimation.</p> <ul style="list-style-type: none"> • Specification of the grid system used. • Quality and adequacy of topographic control. 	<ul style="list-style-type: none"> • The grid system used is UTM WGS84 Zone 35 Northern Hemisphere. • Topographic control is by publicly available LIDAR mapping data and is considered adequate for reporting of Exploration Results.
Data spacing and distribution	<ul style="list-style-type: none"> • Data spacing for reporting of Exploration Results. • Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied. • Whether sample compositing has been applied. 	<ul style="list-style-type: none"> • Historical exploration drilling was spaced according to early stage targeting criteria. • No Mineral Resource or Ore Reserve estimations are reported. • No sample compositing has been applied.
Orientation of data in relation to geological structure	<ul style="list-style-type: none"> • Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type. • If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material. 	<ul style="list-style-type: none"> • Historical drill holes may not have resulted in unbiased sampling of structures. Further geological interpretation and future drilling is required to better understand the nature of orientation of historical drill holes relative to geological structure. • There is a risk that some historical drill holes have introduced a sampling bias. Further geological interpretation and future drilling is required to better understand the nature of orientation of historical drill holes relative to geological structure
Sample security	<ul style="list-style-type: none"> • The measures taken to ensure sample security. 	<ul style="list-style-type: none"> • The historical exploration drilling results were not completed under the supervision of the Competent Person or Kingsrose and the measures to ensure sample security are not known.
Audits or reviews	<ul style="list-style-type: none"> • The results of any audits or reviews of sampling techniques and data. 	<ul style="list-style-type: none"> • There have been no audits of sampling techniques and data.



Section 2 Reporting of Exploration Results

(Criteria in this section apply to all succeeding sections)

Criteria	JORC Code explanation	Commentary																																																																						
Mineral tenement and land tenure status	<ul style="list-style-type: none"> Type, reference name/number, location and ownership incl. agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historic sites, wilderness or national park and environmental settings. The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area. 	<ul style="list-style-type: none"> The Gallujavri project comprises thirteen contiguous exploration licences totalling 102.8 km² as described in the below table: <table border="1"> <thead> <tr> <th>Licence Name</th> <th>Licence Number</th> <th>Area (km²)</th> <th>Grant Date</th> <th>Expiry Date</th> </tr> </thead> <tbody> <tr> <td>Gallujavri 1</td> <td>0026/2021</td> <td>10</td> <td>08/02/2021</td> <td>08/02/2028</td> </tr> <tr> <td>Gallujavri 2</td> <td>0027/2021</td> <td>10</td> <td>08/02/2021</td> <td>08/02/2028</td> </tr> <tr> <td>Gallujavri 3</td> <td>0028/2021</td> <td>10</td> <td>08/02/2021</td> <td>08/02/2028</td> </tr> <tr> <td>Gallujavri 4</td> <td>0029/2021</td> <td>10</td> <td>08/02/2021</td> <td>08/02/2028</td> </tr> <tr> <td>Gallujavri 5</td> <td>0030/2021</td> <td>10</td> <td>08/02/2021</td> <td>08/02/2028</td> </tr> <tr> <td>Gallujavri 6</td> <td>0031/2021</td> <td>10</td> <td>08/02/2021</td> <td>08/02/2028</td> </tr> <tr> <td>Gallujavri 7</td> <td>0032/2021</td> <td>10</td> <td>08/02/2021</td> <td>08/02/2028</td> </tr> <tr> <td>Gallujavri 8</td> <td>0033/2021</td> <td>10</td> <td>08/02/2021</td> <td>08/02/2028</td> </tr> <tr> <td>Gallujavri 9</td> <td>0686/2023</td> <td>5</td> <td>27/07/2023</td> <td>27/07/2030</td> </tr> <tr> <td>Gallujavri 10</td> <td>0682/2023</td> <td>2.5</td> <td>27/07/2023</td> <td>27/07/2030</td> </tr> <tr> <td>Gallujavri 11</td> <td>0683/2023</td> <td>2.5</td> <td>27/07/2023</td> <td>27/07/2030</td> </tr> <tr> <td>Gallujavri 12</td> <td>0684/2023</td> <td>5</td> <td>27/07/2023</td> <td>27/07/2030</td> </tr> <tr> <td>Gallujavri 13</td> <td>0685/2023</td> <td>7.8</td> <td>27/07/2023</td> <td>27/07/2030</td> </tr> </tbody> </table> <ul style="list-style-type: none"> Each licence is 100% owned by EMX Norwegian Services AS, a 100 % owned subsidiary of EMX Royalties The acquisition terms of the Gallujavri Project are as follows: <ul style="list-style-type: none"> On Signing Definitive Agreement: USD Currency \$38,000 cash payment. Option Period (Up to Four Years): Annual cash payments to EMX: \$6,660. 	Licence Name	Licence Number	Area (km ²)	Grant Date	Expiry Date	Gallujavri 1	0026/2021	10	08/02/2021	08/02/2028	Gallujavri 2	0027/2021	10	08/02/2021	08/02/2028	Gallujavri 3	0028/2021	10	08/02/2021	08/02/2028	Gallujavri 4	0029/2021	10	08/02/2021	08/02/2028	Gallujavri 5	0030/2021	10	08/02/2021	08/02/2028	Gallujavri 6	0031/2021	10	08/02/2021	08/02/2028	Gallujavri 7	0032/2021	10	08/02/2021	08/02/2028	Gallujavri 8	0033/2021	10	08/02/2021	08/02/2028	Gallujavri 9	0686/2023	5	27/07/2023	27/07/2030	Gallujavri 10	0682/2023	2.5	27/07/2023	27/07/2030	Gallujavri 11	0683/2023	2.5	27/07/2023	27/07/2030	Gallujavri 12	0684/2023	5	27/07/2023	27/07/2030	Gallujavri 13	0685/2023	7.8	27/07/2023	27/07/2030
Licence Name	Licence Number	Area (km ²)	Grant Date	Expiry Date																																																																				
Gallujavri 1	0026/2021	10	08/02/2021	08/02/2028																																																																				
Gallujavri 2	0027/2021	10	08/02/2021	08/02/2028																																																																				
Gallujavri 3	0028/2021	10	08/02/2021	08/02/2028																																																																				
Gallujavri 4	0029/2021	10	08/02/2021	08/02/2028																																																																				
Gallujavri 5	0030/2021	10	08/02/2021	08/02/2028																																																																				
Gallujavri 6	0031/2021	10	08/02/2021	08/02/2028																																																																				
Gallujavri 7	0032/2021	10	08/02/2021	08/02/2028																																																																				
Gallujavri 8	0033/2021	10	08/02/2021	08/02/2028																																																																				
Gallujavri 9	0686/2023	5	27/07/2023	27/07/2030																																																																				
Gallujavri 10	0682/2023	2.5	27/07/2023	27/07/2030																																																																				
Gallujavri 11	0683/2023	2.5	27/07/2023	27/07/2030																																																																				
Gallujavri 12	0684/2023	5	27/07/2023	27/07/2030																																																																				
Gallujavri 13	0685/2023	7.8	27/07/2023	27/07/2030																																																																				

Criteria	JORC Code explanation	Commentary
		<ul style="list-style-type: none"> ○ Annual minimum work commitments: \$65,000 (Year 1), \$100,000 (Year 2), \$250,000 (Year 3), \$250,000 (Year 4). ○ Option exercise payment of \$150,000 (exercisable at any time during the four-year option period). ○ Deferred Consideration: ○ \$1,000,000 cash on publication of a Mineral Resource. ○ \$2,000,000 cash on a final investment decision to develop a mine. ○ Net Smelter Return Royalty: ○ 1% NSR. ○ Kingsrose can buy back 0.25% for \$3.75 million on or before the fourth anniversary of the option exercise. ○ Annual Advance Royalty (Payable Following Exercise of Option): ○ \$25,000 per year, increasing by 10% annually, capped at \$75,000 per year. ○ Advance royalty payments will be deducted from future NSR payments (if applicable). ○ A 0.5% state royalty is payable to the Norwegian state. An additional 0.25% royalty is payable on licences in Finnmark County. • The Project is subject to regional, national, and international legislation due to recognition of Sámi rights holders in the Finnmark Act, the Minerals Act, and the Norwegian Constitution, which is reflected by ratification of ILO Convention 169, which recognises Sámi as Indigenous Peoples. • However, a clear process exists to receive permission to undertake exploration activities and gain a social license to operate, including escalation to relevant statutory bodies. • To improve management of these complexities, Kingrose actively engages with stakeholders (including Sami), undertakes cultural heritage surveys, completes biodiversity assessments, advances understanding of traditional land use, and develops/agrees impact and benefit sharing mechanisms as early as possible in the exploration program.
Exploration done by other parties	<ul style="list-style-type: none"> • Acknowledgment and appraisal of exploration by other parties. 	<ul style="list-style-type: none"> • Between 1978 and 1983 Sydvaranger A/S identified a number of Ni-Cu showings in the Karasjok Belt, including an outcrop of serpentinised ultramafic in the Gallujavri area containing up to 5 wt% disseminated pyrrhotite-chalcocopyrite with minor pentlandite, mackinawite and violarite. A Turam EM survey over the intrusion resulted in a 740 m drill program across 10 holes ranging from 10-180 m deep targeting conductive units was conducted. Only weak sulphide mineralisation was intersected (Tertiary Minerals Report, 2002). • From 2001-2003 Tertiary Minerals conducted exploration across the Karasjok Belt, including at Gallujavri. The company completed MaxMin, IP and Self Potential geophysical orientation surveys over the intrusion, with IP selected as the method of choice for the wider project area. The follow-up IP survey successfully identified zones of high chargeability, and a number of conductors were delineated. A further dipole-dipole-array IP survey was conducted over the priority areas and three drill holes were completed with weak Ni-Cu-PGE mineralisation intersected.

Criteria	JORC Code explanation	Commentary
		<ul style="list-style-type: none"> From 2006-2010 Anglo American completed a combined base of till and ground geophysical program over 6 survey lines at Gallujavri. Ground measurements consisted of walk magnetics and Slingram MaxMin over 13.5 line kilometres. No diamond drilling was conducted and all work ceased in 2010 with the rejection by the Sámi Parliament of the new mining law cited as a key rationale for relinquishing the licences. From 2008-2012 Store Norske Gull AS held exploration licenses over Gallujavri, conducting orientation snow sampling, heavy mineral sampling, and auger/cobra till sampling. SNG's sampling programs indicated that the intrusion continues to the south of the mapped extent, and that the eastern contact of the intrusion is mineralised. No drilling was conducted (Tertiary Minerals Report, 2002). The historical drilling and exploration data is considered by Kingsrose as 'historical exploration results' where the methodology, sampling and assay procedures are unknown to Kingsrose. A Competent Person has not been able to undertake sufficient work to report the historical exploration results in accordance with the JORC Code. The historical exploration results are considered to be an indication of the geology, styles and tenor of mineralisation that may be present and Kingsrose intends to validate the historical exploration results by way of geological mapping, geophysical and geochemical surveys, leading to future generation of drill targets for exploration drilling. It is uncertain that following further exploration work that the historical exploration results will be able to be reported under the JORC Code 2012, or used in Mineral Resources or Ore Reserves in accordance with the JORC Code.
Geology	<ul style="list-style-type: none"> Deposit type, geological setting and style of mineralisation. 	<ul style="list-style-type: none"> The Gallujavri project lies within the Karasjok Greenstone Belt, which represents the northernmost extension of the Central Lapland Greenstone Belt, extending from Northern Norway through Finland into Russia. This Palaeoproterozoic greenstone belt represents a prolonged period of extensional tectonism with volcano-sedimentary deposits overlaying Archean basement, showing a gradual deepening of the rift-basin from subaerial and shallow-water, to deep water conditions. The Gallujavri intrusion is interpreted to have been intruded into the lower most portion of the Corgas formation, a series of shallow marine sediments and subaerial mafic volcanics, in the latest phase of discrete magmatic episodes occurring at 2.44, 2.22 and 2.05 Ga (Orvik, 2022., Hanski & Huhma, 2005)
Drill hole Information	<ul style="list-style-type: none"> A summary of all information material to the understanding of the exploration results incl. a tabulation of the following information for all Material drill holes: <ul style="list-style-type: none"> – easting and northing of the drill hole collar – elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar – dip and azimuth of the hole – down hole length and interception depth – hole length. 	<ul style="list-style-type: none"> Historical drill hole information is tabulated in this report.

Criteria	JORC Code explanation	Commentary
	<ul style="list-style-type: none"> If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case. 	
Data aggregation methods	<ul style="list-style-type: none"> In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (eg cutting of high-grades) and cut-off grades are usually Material and should be stated. Where aggregate intercepts incorporate short lengths of high-grade results and longer lengths of low grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail. The assumptions used for any reporting of metal equivalent values should be clearly stated. 	<ul style="list-style-type: none"> No weighting averaging techniques, maximum and/or minimum grade truncations (eg cutting of high-grades) or cut-off grades are reported No aggregate intercepts are reported. No metal equivalent values are reported.
Relationship between mineralisation widths and intercept lengths	<ul style="list-style-type: none"> These relationships are particularly important in the reporting of Exploration Results. If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported. If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (eg 'down hole length, true width not known'). 	<ul style="list-style-type: none"> Geometry of the mineralisation with respect to the drill hole is not well understood given the early stage of exploration and limited amount of drilling to date. Down hole length is reported, true width not known.
Diagrams	<ul style="list-style-type: none"> Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported. These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views. 	<ul style="list-style-type: none"> Maps, sections and tabulated drilling results are included in this report.
Balanced reporting	<ul style="list-style-type: none"> Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high-grades and/or widths should be practiced to avoid misleading reporting of Exploration Results. 	<ul style="list-style-type: none"> A table of historical drill assay results is provided.
Other substantive exploration data	<ul style="list-style-type: none"> Other exploration data, if meaningful and material, should be reported incl. (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances. 	<ul style="list-style-type: none"> No other substantive data is reported as Kingsrose has not conducted any exploration work to date on the Gallujavri project.
Further work	<ul style="list-style-type: none"> The nature and scale of planned further work (eg tests for lateral extensions or 	<ul style="list-style-type: none"> Kingsrose intends to follow up high priority targets with an initial phase of non-invasive exploration techniques

Criteria	JORC Code explanation	Commentary
	<p>depth extensions or large-scale step-out drilling).</p> <ul style="list-style-type: none">Diagrams clearly highlighting the areas of possible extensions, incl. the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.	<p>including airborne and ground based geophysical surveys (one or more of gravity, magnetic, electromagnetic, magnetotelluric techniques), geological mapping, rockchip sampling and overburden sampling.</p>

For personal use only






Figure 1: Location of the Gallujavri project within Kingsrose's existing exploration tenure under the Finnmark BHP Alliance.




Figure 2: Map of the Gallujavri project showing simplified geology and historical drill collar locations.




Figure 3: Long section of the Gallujavri project, showing historical diamond drill holes with Cu% and Ni% assays.

Appendix 2 – Historical Diamond Drilling Data for the Gallujavri Project

Table 1: Historical drill collar data, Gallujavri Project.

Hole ID	Company	Year Drilled	Easting	Northing	Elevation (m)	Azimuth (°)	Inclination (°)	Length (m)
03GD001	Tertiary Gold	2003	437164	7725539	321.4	270	-45	125.3
03GD002	Tertiary Gold	2003	437249	7725537	320.5	270	-45	124.9
03GD003	Tertiary Gold	2003	437201	7724844	343.9	270	-45	127
DDH1E	Prospektering AS	1979	437163	7725308	323.6	90	-45	20
DDH1W	Prospektering AS	1979	437163	7725308	323.6	270	-45	12
DDH2	Prospektering AS	1979	437173	7725193	327.6	270	-45	10
DDH2B	Prospektering AS	1979	437166	7725193	326.6	270	-40	4
DDH2C	Prospektering AS	1979	437166	7725193	326.6	270	-45	4
DDH3	Prospektering AS	1979	437171	7726373	352.4	279	-45	89
DDH4	Prospektering AS	1979	437305	7725423	325.3	112	-45	107.4
DDH5	Prospektering AS	1979	437260	7725070	338.1	279	-45	108.4
DDH6	Prospektering AS	1983	437212	7725914	324.5	200	-45	160.9
DDH7	Prospektering AS	1983	437302	7725670	320.1	30	-45	160

Table 2: Historical drill assay data, Gallujavri Project.

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD001	11.55	0.22	0.01	0.02	0.00			
03GD001	11.87	0.29	0.01	0.02	0.00			
03GD001	12.16	0.3	0.02	0.03	0.00			
03GD001	12.55	0.29	0.02	0.03	0.01			
03GD001	12.85	0.29	0.02	0.04	0.00			
03GD001	13.14	0.3	0.02	0.03	0.00			
03GD001	13.50	0.29	0.02	0.03	0.01			
03GD001	13.80	0.29	0.02	0.04	0.00			
03GD001	14.09	0.3	0.02	0.04	0.00			
03GD001	14.45	0.05	0.01	0.03	0.00			
03GD001	14.50	0.3	0.02	0.03	0.00			
03GD001	14.80	0.29	0.01	0.03	0.00			
03GD001	15.10	0.29	0.02	0.03	0.00			
03GD001	15.45	0.29	0.02	0.03	0.01			
03GD001	15.75	0.29	0.02	0.03	0.00			
03GD001	16.04	0.3	0.02	0.03	0.00			

For personal use only

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD001	16.50	0.3	0.02	0.03	0.00			
03GD001	16.80	0.29	0.03	0.04	0.00			
03GD001	17.10	0.29	0.02	0.03	0.00			
03GD001	17.40	0.3	0.02	0.03	0.00			
03GD001	17.70	0.29	0.02	0.04	0.01			
03GD001	18.00	0.29	0.02	0.03	0.01			
03GD001	18.45	0.3	0.02	0.03	0.01			
03GD001	18.75	0.29	0.02	0.03	0.00			
03GD001	19.05	0.29	0.02	0.03	0.01			
03GD001	19.35	0.27	0.02	0.03	0.00			
03GD001	19.73	0.29	0.02	0.04	0.00			
03GD001	20.03	0.26	0.02	0.04	0.00			
03GD001	20.44	0.29	0.02	0.03	0.00			
03GD001	20.74	0.29	0.02	0.03	0.00			
03GD001	21.05	0.28	0.02	0.03	0.00			
03GD001	21.34	0.28	0.02	0.03	0.00			
03GD001	21.62	0.29	0.02	0.03	0.00			
03GD001	21.91	0.08	0.02	0.03	0.00			
03GD001	22.02	0.3	0.01	0.03	0.00			
03GD001	22.32	0.29	0.02	0.03	0.00			
03GD001	22.61	0.3	0.02	0.03	0.00			
03GD001	22.89	0.3	0.02	0.03	0.00			
03GD001	23.19	0.29	0.02	0.03	0.00			
03GD001	23.49	0.29	0.02	0.04	0.01			
03GD001	23.86	0.3	0.02	0.03	0.00			
03GD001	24.16	0.29	0.02	0.04	0.01			
03GD001	24.46	0.29	0.02	0.04	0.01			
03GD001	24.73	0.29	0.02	0.03	0.01			
03GD001	25.03	0.29	0.02	0.05	0.00			
03GD001	25.32	0.29	0.02	0.04	0.00			
03GD001	25.61	0.06	0.02	0.03	0.00			
03GD001	25.71	0.28	0.02	0.04	0.00			
03GD001	26.00	0.29	0.02	0.04	0.00			
03GD001	26.29	0.3	0.02	0.03	0.00			
03GD001	26.60	0.3	0.02	0.04	0.01			
03GD001	26.90	0.29	0.02	0.04	0.01			
03GD001	27.19	0.3	0.02	0.04	0.01			
03GD001	27.52	0.27	0.02	0.03	0.00			



Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD001	27.80	0.29	0.02	0.03	0.01			
03GD001	28.09	0.3	0.02	0.03	0.00			
03GD001	28.35	0.29	0.01	0.02	0.00			
03GD001	28.65	0.29	0.02	0.02	0.00			
03GD001	28.95	0.29	0.02	0.03	0.00			
03GD001	29.70	0.29	0.02	0.03	0.00			
03GD001	29.99	0.3	0.02	0.04	0.01			
03GD001	40.05	0.3	0.02	0.02	0.00			
03GD001	40.35	0.29	0.02	0.03	0.00			
03GD001	40.65	0.29	0.02	0.03	0.00			
03GD001	41.30	0.29	0.02	0.03	0.01			
03GD001	41.60	0.29	0.02	0.04	0.01			
03GD001	41.89	0.3	0.02	0.04	0.00			
03GD001	42.45	0.29	0.02	0.03	0.01			
03GD001	42.75	0.25	0.02	0.03	0.00			
03GD001	43.07	0.29	0.01	0.02	0.00			
03GD001	43.70	0.29	0.02	0.04	0.00			
03GD001	44.00	0.29	0.01	0.03	0.00			
03GD001	44.29	0.3	0.02	0.04	0.01			
03GD001	44.45	0.29	0.02	0.03	0.01			
03GD001	44.75	0.24	0.02	0.03	0.00			
03GD001	45.13	0.26	0.02	0.03	0.00			
03GD001	45.15	0.04	0.02	0.03	0.00			
03GD001	45.28	0.21	0.02	0.03	0.00			
03GD001	45.50	0.29	0.02	0.03	0.00			
03GD001	45.79	0.3	0.02	0.03	0.00			
03GD001	46.15	0.3	0.02	0.04	0.00			
03GD001	46.45	0.29	0.02	0.03	0.00			
03GD001	46.75	0.29	0.02	0.03	0.00			
03GD001	47.20	0.29	0.02	0.03	0.00			
03GD001	47.50	0.29	0.02	0.03	0.00			
03GD001	47.79	0.3	0.02	0.03	0.00			
03GD001	48.05	0.13	0.01	0.03	0.00			
03GD001	48.27	0.3	0.02	0.03	0.00			
03GD001	48.57	0.29	0.02	0.03	0.00			
03GD001	48.87	0.12	0.02	0.03	0.00			
03GD001	49.48	0.21	0.04	0.10	0.01			
03GD001	49.50	0.05	0.02	0.03	0.00			

For personal use only



Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD001	49.55	0.29	0.01	0.03	0.00			
03GD001	49.69	0.3	0.02	0.02	0.00			
03GD001	49.85	0.29	0.02	0.03	0.00			
03GD001	50.14	0.29	0.02	0.03	0.00			
03GD001	50.44	0.05	0.02	0.04	0.00			
03GD001	50.50	0.3	0.02	0.04	0.00			
03GD001	50.80	0.29	0.02	0.03	0.01			
03GD001	51.10	0.29	0.02	0.03	0.00			
03GD001	51.35	0.3	0.02	0.03	0.00			
03GD001	51.65	0.29	0.02	0.04	0.00			
03GD001	51.95	0.29	0.02	0.03	0.00			
03GD001	52.70	0.3	0.03	0.06	0.01			
03GD001	53.00	0.29	0.02	0.04	0.01			
03GD001	53.29	0.3	0.02	0.03	0.00			
03GD001	53.65	0.3	0.02	0.04	0.01			
03GD001	53.95	0.29	0.02	0.03	0.00			
03GD001	54.24	0.3	0.02	0.03	0.00			
03GD001	55.09	0.29	0.02	0.04	0.01			
03GD001	55.48	0.21	0.02	0.04	0.00			
03GD001	55.69	0.3	0.02	0.04	0.01			
03GD001	56.05	0.3	0.02	0.05	0.01			
03GD001	56.35	0.29	0.02	0.03	0.01			
03GD001	56.65	0.22	0.02	0.04	0.01			
03GD001	57.10	0.29	0.02	0.04	0.01			
03GD001	57.40	0.29	0.02	0.04	0.00			
03GD001	57.69	0.3	0.02	0.03	0.00			
03GD001	57.85	0.23	0.02	0.03	0.00			
03GD001	58.17	0.3	0.02	0.03	0.00			
03GD001	58.47	0.29	0.02	0.03	0.00			
03GD001	58.80	0.29	0.02	0.04	0.01			
03GD001	59.09	0.3	0.02	0.03	0.00			
03GD001	60.05	0.29	0.02	0.03	0.01			
03GD001	60.35	0.29	0.02	0.03	0.00			
03GD001	60.64	0.29	0.02	0.04	0.00			
03GD001	60.94	0.05	0.02	0.03	0.00			
03GD001	61.00	0.29	0.02	0.03	0.00			
03GD001	61.30	0.29	0.02	0.03	0.00			
03GD001	61.55	0.29	0.01	0.01	0.00			

For personal use only



Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD001	61.59	0.3	0.02	0.04	0.00			
03GD001	62.04	0.29	0.02	0.03	0.00			
03GD001	62.34	0.06	0.01	0.02	0.00			
03GD001	62.35	0.05	0.01	0.01	0.00			
03GD001	62.41	0.29	0.01	0.01	0.00			
03GD001	62.70	0.29	0.02	0.02	0.01			
03GD001	62.99	0.3	0.01	0.01	0.00			
03GD001	63.35	0.29	0.02	0.02	0.01			
03GD001	63.65	0.29	0.02	0.03	0.01			
03GD001	63.95	0.29	0.01	0.02	0.00			
03GD001	65.10	0.29	0.01	0.01	0.00			
03GD001	65.40	0.29	0.01	0.01	0.00			
03GD001	65.69	0.3	0.01	0.01	0.00			
03GD001	65.75	0.3	0.02	0.03	0.00			
03GD001	66.05	0.29	0.02	0.04	0.00			
03GD001	66.34	0.3	0.02	0.03	0.00			
03GD001	66.40	0.3	0.02	0.03	0.00			
03GD001	66.70	0.29	0.02	0.03	0.00			
03GD001	66.99	0.3	0.02	0.03	0.00			
03GD001	67.75	0.3	0.02	0.03	0.00			
03GD001	68.05	0.29	0.02	0.03	0.00			
03GD001	68.34	0.29	0.02	0.04	0.01			
03GD001	68.64	0.05	0.02	0.03	0.00			
03GD001	69.05	0.29	0.02	0.04	0.01			
03GD001	69.10	0.29	0.02	0.03	0.00			
03GD001	69.35	0.26	0.01	0.03	0.00			
03GD001	69.40	0.29	0.02	0.03	0.00			
03GD001	69.62	0.29	0.01	0.03	0.00			
03GD001	69.91	0.08	0.02	0.03	0.01			
03GD001	70.01	0.29	0.02	0.03	0.01			
03GD001	70.30	0.29	0.02	0.03	0.00			
03GD001	70.59	0.3	0.02	0.03	0.00			
03GD001	70.85	0.3	0.02	0.03	0.00			
03GD001	71.15	0.29	0.02	0.03	0.00			
03GD001	71.45	0.24	0.02	0.04	0.01			
03GD001	72.15	0.05	0.02	0.03	0.01			
03GD001	72.31	0.19	0.02	0.04	0.00			
03GD001	72.50	0.29	0.02	0.03	0.00			

For personal use only



Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD001	72.79	0.3	0.02	0.03	0.00			
03GD001	73.15	0.3	0.02	0.03	0.00			
03GD001	73.45	0.29	0.02	0.04	0.00			
03GD001	73.74	0.3	0.02	0.03	0.00			
03GD001	74.55	0.15	0.02	0.03	0.00			
03GD001	74.70	0.29	0.02	0.03	0.00			
03GD001	75.00	0.26	0.02	0.03	0.00			
03GD001	75.33	0	0.00	0.12	0.00			
03GD001	75.33	0.16	0.01	0.02	0.00			
03GD001	75.55	0.29	0.02	0.03	0.00			
03GD001	75.85	0.29	0.02	0.03	0.00			
03GD001	76.14	0.3	0.02	0.03	0.00			
03GD001	77.10	0.29	0.02	0.03	0.00			
03GD001	77.40	0.29	0.02	0.04	0.01			
03GD001	77.70	0.29	0.02	0.04	0.00			
03GD001	77.85	0.3	0.02	0.04	0.00			
03GD001	78.15	0.29	0.02	0.04	0.01			
03GD001	78.45	0.29	0.02	0.04	0.00			
03GD001	79.05	0.3	0.02	0.03	0.00			
03GD001	79.35	0.29	0.02	0.03	0.00			
03GD001	79.52	0.29	0.02	0.03	0.01			
03GD001	79.64	0.3	0.02	0.03	0.00			
03GD001	79.95	0.24	0.02	0.03	0.00			
03GD001	80.01	0.29	0.02	0.03	0.00			
03GD001	80.30	0.29	0.02	0.03	0.00			
03GD001	80.55	0.3	0.01	0.03	0.00			
03GD001	80.59	0.3	0.02	0.03	0.00			
03GD001	80.85	0.29	0.02	0.03	0.00			
03GD001	81.14	0.3	0.03	0.04	0.01			
03GD001	81.75	0.16	0.02	0.04	0.01			
03GD001	81.91	0.29	0.02	0.03	0.01			
03GD001	82.21	0.29	0.02	0.03	0.00			
03GD001	82.61	0.08	0.01	0.03	0.00			
03GD001	83.05	0.3	0.02	0.03	0.00			
03GD001	83.35	0.29	0.02	0.02	0.00			
03GD001	83.60	0.29	0.02	0.02	0.00			
03GD001	83.64	0.16	0.02	0.04	0.01			
03GD001	83.89	0.1	0.02	0.03	0.00			

For personal use only



Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD001	83.90	0.29	0.02	0.03	0.00			
03GD001	84.19	0.3	0.02	0.02	0.00			
03GD001	84.45	0.24	0.02	0.04	0.00			
03GD001	84.80	0.29	0.02	0.03	0.00			
03GD001	85.09	0.29	0.02	0.03	0.00			
03GD001	85.40	0.3	0.02	0.04	0.00			
03GD001	85.70	0.29	0.02	0.04	0.00			
03GD001	85.99	0.3	0.02	0.03	0.00			
03GD001	86.25	0.29	0.02	0.03	0.00			
03GD001	86.55	0.29	0.02	0.03	0.00			
03GD001	86.84	0.29	0.02	0.03	0.00			
03GD001	87.50	0.29	0.01	0.01	0.00			
03GD001	87.79	0.3	0.01	0.02	0.00			
03GD001	88.45	0.23	0.01	0.02	0.01			
03GD001	88.78	0.29	0.02	0.04	0.00			
03GD001	89.08	0.22	0.01	0.01	0.00			
03GD001	89.40	0.29	0.01	0.01	0.00			
03GD001	89.69	0.29	0.01	0.01	0.00			
03GD001	89.98	0.3	0.01	0.01	0.00			
03GD001	90.23	0.29	0.01	0.01	0.00			
03GD001	90.28	0	0.01	0.01	0.00			
03GD001	90.32	0.01	0.00	0.01	0.00			
03GD001	90.65	0.29	0.01	0.01	0.00			
03GD001	90.94	0.23	0.01	0.02	0.00			
03GD001	91.17	0.29	0.01	0.01	0.00			
03GD001	91.47	0.29	0.01	0.02	0.00			
03GD001	91.76	0.3	0.01	0.01	0.00			
03GD001	92.01	0.3	0.01	0.01	0.00			
03GD001	92.31	0.29	0.01	0.01	0.00			
03GD001	92.61	0.16	0.01	0.01	0.00			
03GD001	92.88	0.07	0.01	0.02	0.00			
03GD001	92.95	0.29	0.01	0.01	0.00			
03GD001	93.24	0.3	0.01	0.01	0.00			
03GD001	93.60	0.24	0.01	0.01	0.00			
03GD001	93.79	0.3	0.01	0.01	0.00			
03GD001	94.09	0.29	0.01	0.01	0.00			
03GD001	94.39	0.29	0.01	0.01	0.00			
03GD001	94.74	0.29	0.01	0.02	0.00			

For personal use only



Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD001	95.03	0.29	0.01	0.01	0.00			
03GD001	95.32	0.3	0.01	0.02	0.00			
03GD001	95.57	0.3	0.01	0.01	0.00			
03GD001	95.87	0.29	0.01	0.01	0.00			
03GD001	96.16	0.3	0.01	0.02	0.00			
03GD001	96.81	0.29	0.01	0.02	0.00			
03GD001	97.10	0.3	0.01	0.01	0.00			
03GD001	98.05	0.3	0.01	0.02	0.00			
03GD001	98.35	0.29	0.01	0.01	0.00			
03GD001	98.64	0.14	0.01	0.01	0.00			
03GD001	98.90	0.09	0.01	0.01	0.00			
03GD001	99.00	0.29	0.01	0.01	0.00			
03GD001	99.29	0.29	0.01	0.01	0.00			
03GD001	99.58	0.3	0.01	0.01	0.00			
03GD001	99.83	0.3	0.01	0.01	0.00			
03GD001	100.13	0.29	0.01	0.01	0.00			
03GD001	100.43	0.29	0.01	0.01	0.00			
03GD001	100.77	0.3	0.01	0.01	0.00			
03GD001	101.07	0.29	0.01	0.02	0.00			
03GD001	101.36	0.3	0.01	0.01	0.00			
03GD001	101.61	0.3	0.01	0.01	0.00			
03GD001	101.91	0.29	0.02	0.04	0.00			
03GD001	102.21	0.29	0.02	0.04	0.00			
03GD001	102.55	0.29	0.02	0.04	0.00			
03GD001	102.85	0.29	0.02	0.03	0.00			
03GD001	103.14	0.3	0.02	0.03	0.00			
03GD001	103.39	0.29	0.02	0.03	0.00			
03GD001	103.69	0.29	0.03	0.04	0.01			
03GD001	103.98	0.3	0.02	0.04	0.01			
03GD001	104.33	0.3	0.02	0.03	0.01			
03GD001	104.63	0.29	0.02	0.03	0.00			
03GD001	104.93	0.29	0.02	0.03	0.00			
03GD001	105.17	0.21	0.02	0.03	0.00			
03GD001	105.49	0.3	0.02	0.04	0.00			
03GD001	105.79	0.3	0.02	0.03	0.00			
03GD001	106.41	0.29	0.02	0.04	0.00			
03GD001	106.70	0.3	0.03	0.03	0.00			
03GD001	107.25	0.3	0.02	0.03	0.00			

For personal use only



For personal use only

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD001	107.55	0.29	0.02	0.04	0.01			
03GD001	107.85	0.29	0.02	0.04	0.00			
03GD001	108.25	0.26	0.02	0.03	0.00			
03GD001	108.60	0.29	0.02	0.04	0.00			
03GD001	108.89	0.3	0.02	0.03	0.00			
03GD001	109.25	0.29	0.02	0.03	0.00			
03GD001	109.55	0.29	0.02	0.04	0.00			
03GD001	109.84	0.29	0.02	0.03	0.00			
03GD001	110.13	0.06	0.02	0.03	0.00			
03GD001	110.30	0.29	0.02	0.03	0.00			
03GD001	110.60	0.29	0.02	0.04	0.00			
03GD001	110.90	0.29	0.02	0.03	0.01			
03GD001	111.25	0.3	0.02	0.03	0.00			
03GD001	111.55	0.06	0.02	0.04	0.01			
03GD001	111.69	0.29	0.01	0.03	0.00			
03GD001	111.99	0.14	0.02	0.03	0.00			
03GD001	112.30	0.3	0.02	0.03	0.00			
03GD001	112.60	0.29	0.02	0.04	0.01			
03GD001	112.90	0.29	0.02	0.02	0.00			
03GD001	113.25	0.3	0.02	0.03	0.00			
03GD001	113.55	0.29	0.02	0.03	0.00			
03GD001	113.84	0.3	0.02	0.03	0.00			
03GD001	114.25	0.1	0.02	0.04	0.00			
03GD001	114.36	0.29	0.02	0.03	0.01			
03GD001	114.72	0.17	0.01	0.01	0.00			
03GD001	114.89	0.3	0.01	0.02	0.00			
03GD001	115.25	0.29	0.01	0.02	0.00			
03GD001	115.55	0.29	0.01	0.02	0.00			
03GD001	115.84	0.3	0.01	0.02	0.00			
03GD001	116.60	0.29	0.02	0.03	0.00			
03GD001	116.90	0.29	0.02	0.03	0.00			
03GD001	117.05	0.3	0.02	0.04	0.01			
03GD001	117.35	0.29	0.02	0.03	0.00			
03GD001	117.64	0.3	0.02	0.03	0.00			
03GD001	118.00	0.29	0.02	0.04	0.01			
03GD001	118.30	0.29	0.02	0.04	0.00			
03GD001	118.59	0.3	0.01	0.03	0.00			
03GD001	118.85	0.3	0.02	0.03	0.00			



For personal use only

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD001	119.15	0.29	0.01	0.03	0.00			
03GD001	119.45	0.29	0.02	0.03	0.00			
03GD001	119.80	0.29	0.02	0.03	0.00			
03GD001	120.10	0.29	0.02	0.03	0.00			
03GD001	120.39	0.3	0.02	0.03	0.00			
03GD001	120.65	0.3	0.02	0.03	0.00			
03GD001	120.95	0.3	0.03	0.04	0.00			
03GD001	121.25	0.29	0.02	0.03	0.00			
03GD001	122.10	0.29	0.02	0.03	0.00			
03GD001	122.40	0.29	0.02	0.04	0.00			
03GD001	122.45	0.3	0.02	0.03	0.00			
03GD001	122.70	0.29	0.02	0.03	0.00			
03GD001	122.75	0.29	0.02	0.03	0.00			
03GD001	123.05	0.29	0.02	0.03	0.00			
03GD001	123.40	0.29	0.02	0.03	0.01			
03GD001	123.70	0.29	0.02	0.04	0.01			
03GD001	123.99	0.3	0.02	0.04	0.01			
03GD001	124.25	0.24	0.02	0.03	0.00			
03GD002	2.85	0.29	0.01	0.02	0.00			
03GD002	3.15	0.29	0.01	0.02	0.00			
03GD002	3.44	0.3	0.01	0.02	0.00			
03GD002	3.75	0.09	0.01	0.02	0.00			
03GD002	3.84	0.29	0.01	0.02	0.00			
03GD002	4.14	0.29	0.01	0.01	0.00			
03GD002	4.57	0.12	0.01	0.02	0.00			
03GD002	4.65	0.29	0.01	0.03	0.00			
03GD002	4.95	0.29	0.01	0.02	0.00			
03GD002	5.24	0.3	0.01	0.02	0.00			
03GD002	5.60	0.29	0.01	0.02	0.00			
03GD002	5.90	0.29	0.01	0.02	0.00			
03GD002	6.20	0.29	0.01	0.02	0.00			
03GD002	6.45	0.29	0.01	0.02	0.00			
03GD002	6.75	0.29	0.01	0.01	0.00			
03GD002	7.04	0.29	0.01	0.02	0.00			
03GD002	7.34	0.05	0.01	0.02	0.00			
03GD002	8.71	0.29	0.01	0.01	0.00			
03GD002	9.00	0.29	0.01	0.02	0.00			
03GD002	9.29	0.3	0.01	0.02	0.00			



For personal use only

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD002	9.65	0.29	0.01	0.02	0.00			
03GD002	9.95	0.29	0.01	0.02	0.00			
03GD002	10.25	0.29	0.01	0.02	0.00			
03GD002	10.70	0.29	0.01	0.03	0.00			
03GD002	11.00	0.29	0.01	0.02	0.01			
03GD002	11.29	0.3	0.01	0.02	0.00			
03GD002	11.65	0.3	0.01	0.02	0.00			
03GD002	11.95	0.29	0.01	0.01	0.01			
03GD002	12.24	0.3	0.01	0.01	0.00			
03GD002	13.00	0.29	0.01	0.02	0.00			
03GD002	13.05	0.3	0.01	0.02	0.00			
03GD002	13.29	0.3	0.01	0.01	0.00			
03GD002	13.35	0.29	0.01	0.02	0.00			
03GD002	13.65	0.29	0.01	0.02	0.00			
03GD002	14.01	0.29	0.01	0.02	0.00			
03GD002	14.30	0.29	0.01	0.03	0.00			
03GD002	14.60	0.29	0.02	0.05	0.01			
03GD002	14.85	0.3	0.02	0.02	0.01			
03GD002	15.15	0.29	0.01	0.03	0.01			
03GD002	15.45	0.29	0.02	0.08	0.01			
03GD002	15.75	0.07	0.04	0.09	0.01			
03GD002	15.83	0.29	0.03	0.02	0.01			
03GD002	16.12	0.3	0.01	0.05	0.00			
03GD002	16.42	0.27	0.02	0.04	0.00			
03GD002	16.65	0.27	0.01	0.02	0.00			
03GD002	16.93	0.29	0.01	0.00	0.00			
03GD002	17.22	0.29	0.01	0.01	0.00			
03GD002	17.52	0.07	0.01	0.02	0.00			
03GD002	17.60	0.3	0.01	0.02	0.00			
03GD002	17.90	0.29	0.01	0.02	0.00			
03GD002	18.19	0.3	0.01	0.01	0.00			
03GD002	18.45	0.3	0.01	0.01	0.00			
03GD002	18.75	0.29	0.01	0.01	0.00			
03GD002	19.05	0.29	0.01	0.01	0.00			
03GD002	19.40	0.3	0.01	0.03	0.00			
03GD002	19.70	0.29	0.01	0.02	0.00			
03GD002	19.99	0.3	0.01	0.02	0.00			
03GD002	20.25	0.29	0.00	0.01	0.00			



Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD002	20.55	0.29	0.01	0.02	0.00			
03GD002	20.84	0.3	0.01	0.03	0.00			
03GD002	21.23	0.29	0.01	0.03	0.00			
03GD002	21.52	0.27	0.01	0.03	0.00			
03GD002	21.79	0.3	0.01	0.00	0.00			
03GD002	23.05	0.26	0.00	0.01	0.00			
03GD002	23.31	0.3	0.01	0.00	0.00			
03GD002	23.61	0.29	0.00	0.01	0.00			
03GD002	23.91	0.08	0.01	0.00	0.00			
03GD002	23.95	0.11	0.00	0.03	0.00			
03GD002	24.06	0.26	0.01	0.01	0.00			
03GD002	24.33	0.29	0.00	0.01	0.00			
03GD002	24.62	0.27	0.01	0.01	0.00			
03GD002	24.85	0.3	0.01	0.14	0.00			
03GD002	25.15	0.29	0.01	0.01	0.00			
03GD002	25.44	0.27	0.01	0.04	0.00			
03GD002	25.71	0.08	0.01	0.05	0.00			
03GD002	25.80	0.3	0.06	0.43	0.01			
03GD002	26.10	0.29	0.04	0.51	0.01			
03GD002	26.39	0.3	0.04	0.04	0.01			
03GD002	26.65	0.29	0.02	0.10	0.01			
03GD002	26.95	0.29	0.11	0.12	0.01			
03GD002	27.25	0.29	0.03	0.06	0.01			
03GD002	27.55	0.07	0.02	0.29	0.01			
03GD002	27.63	0.27	0.02	0.10	0.01			
03GD002	27.90	0.29	0.02	0.07	0.01			
03GD002	28.19	0.3	0.02	0.04	0.01			
03GD002	28.45	0.27	0.02	0.07	0.01			
03GD002	28.73	0.29	0.03	0.05	0.01			
03GD002	29.02	0.29	0.03	0.18	0.01			
03GD002	29.40	0.29	0.03	0.05	0.01			
03GD002	29.70	0.29	0.04	0.06	0.01			
03GD002	30.00	0.29	0.06	0.09	0.01			
03GD002	30.25	0.3	0.02	0.22	0.01			
03GD002	30.55	0.29	0.02	0.09	0.01			
03GD002	30.84	0.3	0.04	0.06	0.01			
03GD002	31.45	0.13	0.02	0.11	0.01			
03GD002	31.45	0.13	0.02	0.15	0.01			

For personal use only



Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD002	31.50	0.29	0.02	0.24	0.01			
03GD002	31.68	0.29	0.02	0.07	0.01			
03GD002	31.68	0.29	0.02	0.07	0.01			
03GD002	31.79	0.3	0.02	0.09	0.01			
03GD002	31.97	0.27	0.02	0.08	0.01			
03GD002	31.97	0.27	0.02	0.03	0.01			
03GD002	32.32	0.07	0.02	0.03	0.01			
03GD002	32.32	0.07	0.02	0.05	0.01			
03GD002	32.35	0.06	0.03	0.04	0.01			
03GD002	32.35	0.06	0.03	0.04	0.01			
03GD002	32.49	0.21	0.01	0.06	0.00			
03GD002	32.49	0.25	0.02	0.04	0.01			
03GD002	32.70	0.29	0.02	0.04	0.01			
03GD002	32.75	0.26	0.02	0.06	0.01			
03GD002	32.99	0.3	0.02	0.04	0.00			
03GD002	33.02	0.27	0.02	0.04	0.01			
03GD002	33.25	0.27	0.02	0.06	0.01			
03GD002	33.25	0.3	0.02	0.06	0.01			
03GD002	33.53	0.26	0.02	0.03	0.01			
03GD002	33.55	0.29	0.02	0.05	0.01			
03GD002	33.80	0.29	0.03	0.03	0.01			
03GD002	33.84	0.3	0.02	0.05	0.00			
03GD002	34.09	0.1	0.03	0.04	0.01			
03GD002	34.15	0.29	0.02	0.09	0.01			
03GD002	34.15	0.29	0.02	0.06	0.01			
03GD002	34.55	0.24	0.02	0.06	0.00			
03GD002	34.55	0.24	0.02	0.04	0.00			
03GD002	34.79	0.3	0.02	0.05	0.01			
03GD002	34.79	0.3	0.02	0.04	0.01			
03GD002	35.05	0.29	0.02	0.06	0.01			
03GD002	35.05	0.29	0.02	0.04	0.01			
03GD002	35.45	0.29	0.02	0.07	0.01			
03GD002	35.45	0.29	0.02	0.05	0.01			
03GD002	35.84	0.15	0.01	0.03	0.00			
03GD002	35.84	0.15	0.01	0.03	0.00			
03GD002	35.95	0.13	0.02	0.04	0.01			
03GD002	35.95	0.13	0.02	0.04	0.01			
03GD002	36.16	0.12	0.02	0.04	0.01			

For personal use only



For personal use only

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD002	36.16	0.12	0.02	0.04	0.01			
03GD002	36.43	0.2	0.02	0.09	0.01			
03GD002	36.43	0.2	0.02	0.04	0.01			
03GD002	36.77	0.12	0.02	0.04	0.01			
03GD002	36.77	0.12	0.02	0.03	0.01			
03GD002	36.85	0.13	0.02	0.03	0.01			
03GD002	36.85	0.13	0.02	0.03	0.01			
03GD002	37.07	0.29	0.02	0.03	0.01			
03GD002	37.07	0.29	0.02	0.05	0.01			
03GD002	37.36	0.2	0.02	0.05	0.01			
03GD002	37.36	0.2	0.02	0.04	0.01			
03GD002	37.72	0.07	0.02	0.03	0.01			
03GD002	37.72	0.07	0.02	0.03	0.01			
03GD002	37.80	0.29	0.02	0.04	0.01			
03GD002	37.80	0.3	0.01	0.04	0.00			
03GD002	38.10	0.29	0.02	0.05	0.01			
03GD002	38.10	0.29	0.02	0.05	0.01			
03GD002	38.39	0.3	0.02	0.04	0.00			
03GD002	38.40	0.29	0.02	0.04	0.00			
03GD002	39.25	0.3	0.01	0.01	0.00			
03GD002	39.25	0.3	0.01	0.04	0.00			
03GD002	39.67	0.29	0.02	0.04	0.01			
03GD002	39.67	0.29	0.02	0.04	0.01			
03GD002	39.96	0.23	0.02	0.04	0.01			
03GD002	39.96	0.23	0.02	0.05	0.01			
03GD002	40.21	0.18	0.02	0.05	0.01			
03GD002	40.21	0.18	0.02	0.05	0.01			
03GD002	40.39	0.3	0.02	0.02	0.00			
03GD002	40.40	0.29	0.02	0.03	0.00			
03GD002	40.69	0.3	0.01	0.05	0.00			
03GD002	40.69	0.3	0.01	0.05	0.00			
03GD002	41.05	0.3	0.01	0.03	0.00			
03GD002	41.35	0.3	0.01	0.03	0.00			
03GD002	41.65	0.29	0.02	0.06	0.01			
03GD002	42.05	0.27	0.02	0.02	0.01			
03GD002	42.32	0.29	0.02	0.02	0.01			
03GD002	42.62	0.29	0.02	0.04	0.01			
03GD002	42.89	0.3	0.02	0.04	0.01			



For personal use only

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD002	43.19	0.27	0.02	0.04	0.01			
03GD002	43.46	0.3	0.02	0.04	0.00			
03GD002	43.76	0.07	0.02	0.07	0.01			
03GD002	43.89	0.29	0.02	0.04	0.01			
03GD002	44.18	0.27	0.02	0.04	0.01			
03GD002	44.46	0.29	0.02	0.03	0.01			
03GD002	44.73	0.29	0.01	0.03	0.00			
03GD002	45.03	0.27	0.02	0.03	0.01			
03GD002	45.30	0.29	0.02	0.03	0.01			
03GD002	45.60	0.07	0.02	0.05	0.01			
03GD002	45.70	0.3	0.02	0.04	0.01			
03GD002	46.00	0.29	0.02	0.03	0.01			
03GD002	46.30	0.29	0.02	0.03	0.01			
03GD002	46.57	0.08	0.02	0.05	0.01			
03GD002	46.72	0.3	0.02	0.05	0.01			
03GD002	47.02	0.29	0.02	0.04	0.01			
03GD002	47.31	0.2	0.02	0.03	0.01			
03GD002	47.54	0.29	0.02	0.05	0.01			
03GD002	47.84	0.29	0.02	0.02	0.01			
03GD002	48.13	0.3	0.02	0.05	0.01			
03GD002	48.41	0.29	0.01	0.04	0.00			
03GD002	48.71	0.29	0.02	0.05	0.01			
03GD002	49.00	0.3	0.02	0.04	0.01			
03GD002	50.00	0.29	0.02	0.02	0.01			
03GD002	50.05	0.3	0.02	0.04	0.01			
03GD002	50.30	0.29	0.02	0.04	0.01			
03GD002	50.35	0.29	0.02	0.03	0.00			
03GD002	50.64	0.3	0.02	0.03	0.00			
03GD002	51.09	0.29	0.02	0.04	0.01			
03GD002	51.39	0.29	0.02	0.04	0.00			
03GD002	51.68	0.3	0.02	0.04	0.00			
03GD002	52.65	0.05	0.02	0.04	0.01			
03GD002	52.81	0.29	0.02	0.02	0.01			
03GD002	53.11	0.28	0.02	0.03	0.00			
03GD002	53.40	0.07	0.02	0.04	0.00			
03GD002	53.40	0.3	0.02	0.04	0.01			
03GD002	53.70	0.29	0.02	0.04	0.01			
03GD002	54.00	0.29	0.02	0.02	0.00			



For personal use only

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD002	54.35	0.3	0.02	0.04	0.00			
03GD002	54.65	0.29	0.02	0.05	0.01			
03GD002	54.94	0.3	0.02	0.05	0.01			
03GD002	55.65	0.18	0.02	0.04	0.00			
03GD002	55.91	0.08	0.01	0.02	0.01			
03GD002	56.00	0.29	0.02	0.04	0.01			
03GD002	56.29	0.3	0.01	0.04	0.00			
03GD002	56.45	0.29	0.02	0.04	0.01			
03GD002	56.75	0.29	0.02	0.02	0.01			
03GD002	57.04	0.29	0.02	0.05	0.01			
03GD002	57.34	0.05	0.02	0.04	0.01			
03GD002	57.50	0.29	0.02	0.04	0.01			
03GD002	57.80	0.29	0.02	0.03	0.01			
03GD002	58.09	0.3	0.02	0.04	0.00			
03GD002	58.65	0.23	0.02	0.03	0.01			
03GD002	58.97	0.3	0.02	0.04	0.00			
03GD002	59.27	0.29	0.01	0.04	0.00			
03GD002	59.60	0.29	0.02	0.03	0.00			
03GD002	59.90	0.29	0.02	0.03	0.00			
03GD002	60.65	0.3	0.02	0.04	0.00			
03GD002	60.95	0.29	0.02	0.03	0.00			
03GD002	61.25	0.29	0.02	0.03	0.01			
03GD002	61.70	0.29	0.02	0.03	0.00			
03GD002	62.00	0.29	0.02	0.04	0.00			
03GD002	62.29	0.3	0.02	0.04	0.01			
03GD002	62.65	0.3	0.02	0.03	0.01			
03GD002	62.95	0.29	0.02	0.04	0.00			
03GD002	63.25	0.29	0.02	0.04	0.01			
03GD002	63.70	0.29	0.02	0.04	0.01			
03GD002	64.00	0.29	0.02	0.04	0.01			
03GD002	64.29	0.3	0.02	0.04	0.00			
03GD002	64.65	0.3	0.02	0.04	0.00			
03GD002	64.95	0.29	0.02	0.04	0.01			
03GD002	65.25	0.25	0.02	0.04	0.01			
03GD002	65.70	0.29	0.02	0.04	0.01			
03GD002	66.00	0.29	0.02	0.03	0.01			
03GD002	66.29	0.3	0.02	0.04	0.01			
03GD002	66.65	0.3	0.02	0.04	0.01			



For personal use only

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD002	66.95	0.3	0.02	0.03	0.01			
03GD002	67.25	0.29	0.02	0.03	0.00			
03GD002	67.70	0.29	0.02	0.03	0.01			
03GD002	68.00	0.29	0.02	0.02	0.00			
03GD002	68.29	0.3	0.02	0.03	0.00			
03GD002	68.65	0.29	0.02	0.03	0.00			
03GD002	68.95	0.29	0.02	0.03	0.00			
03GD002	69.24	0.29	0.02	0.03	0.00			
03GD002	70.00	0.29	0.02	0.03	0.01			
03GD002	70.29	0.3	0.02	0.03	0.00			
03GD002	70.65	0.3	0.02	0.03	0.00			
03GD002	70.95	0.08	0.02	0.03	0.00			
03GD002	71.12	0.29	0.01	0.04	0.00			
03GD002	71.41	0.18	0.02	0.03	0.00			
03GD002	71.60	0.05	0.02	0.04	0.00			
03GD002	71.66	0.28	0.01	0.05	0.00			
03GD002	71.94	0.3	0.02	0.04	0.01			
03GD002	72.24	0.3	0.01	0.04	0.00			
03GD002	72.55	0.29	0.02	0.03	0.00			
03GD002	72.85	0.29	0.01	0.05	0.00			
03GD002	73.14	0.3	0.02	0.03	0.00			
03GD002	73.57	0.29	0.03	0.03	0.01			
03GD002	73.87	0.29	0.02	0.04	0.01			
03GD002	74.23	0.21	0.02	0.04	0.01			
03GD002	74.45	0.3	0.01	0.04	0.00			
03GD002	74.75	0.29	0.01	0.04	0.00			
03GD002	75.05	0.29	0.02	0.03	0.00			
03GD002	75.45	0.29	0.02	0.04	0.00			
03GD002	75.74	0.3	0.02	0.03	0.00			
03GD002	76.04	0.3	0.02	0.04	0.00			
03GD002	76.35	0.3	0.02	0.03	0.00			
03GD002	76.65	0.29	0.02	0.03	0.00			
03GD002	76.95	0.29	0.01	0.03	0.00			
03GD002	77.35	0.29	0.02	0.04	0.01			
03GD002	77.64	0.3	0.02	0.03	0.01			
03GD002	77.94	0.3	0.02	0.03	0.00			
03GD002	78.25	0.3	0.02	0.04	0.01			
03GD002	78.55	0.29	0.02	0.03	0.01			



Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD002	78.85	0.29	0.02	0.03	0.00			
03GD002	79.90	0.29	0.02	0.03	0.01			
03GD002	80.20	0.29	0.01	0.03	0.00			
03GD002	80.75	0.29	0.02	0.04	0.00			
03GD002	81.05	0.29	0.02	0.03	0.01			
03GD002	81.34	0.3	0.02	0.03	0.00			
03GD002	81.70	0.3	0.02	0.02	0.00			
03GD002	82.00	0.29	0.02	0.03	0.00			
03GD002	82.30	0.29	0.02	0.04	0.00			
03GD002	82.55	0.3	0.02	0.04	0.00			
03GD002	82.85	0.29	0.02	0.04	0.00			
03GD002	83.15	0.29	0.02	0.03	0.01			
03GD002	83.50	0.3	0.02	0.03	0.00			
03GD002	83.80	0.29	0.01	0.03	0.00			
03GD002	84.09	0.3	0.02	0.03	0.00			
03GD002	84.35	0.29	0.02	0.03	0.00			
03GD002	84.65	0.29	0.02	0.03	0.01			
03GD002	84.95	0.27	0.02	0.03	0.01			
03GD002	85.30	0.29	0.02	0.03	0.00			
03GD002	85.60	0.29	0.02	0.03	0.01			
03GD002	85.89	0.3	0.02	0.04	0.00			
03GD002	86.15	0.29	0.02	0.04	0.00			
03GD002	86.45	0.29	0.02	0.03	0.01			
03GD002	86.75	0.29	0.02	0.04	0.00			
03GD002	87.10	0.29	0.02	0.03	0.01			
03GD002	87.40	0.29	0.02	0.03	0.01			
03GD002	87.69	0.3	0.02	0.03	0.01			
03GD002	87.95	0.08	0.02	0.03	0.01			
03GD002	88.10	0.3	0.02	0.04	0.01			
03GD002	88.40	0.29	0.02	0.03	0.01			
03GD002	88.70	0.14	0.02	0.03	0.00			
03GD002	89.20	0.29	0.02	0.03	0.01			
03GD002	89.49	0.3	0.02	0.03	0.01			
03GD002	89.55	0.3	0.02	0.04	0.00			
03GD002	89.85	0.29	0.02	0.03	0.01			
03GD002	90.14	0.3	0.02	0.03	0.01			
03GD002	90.45	0.01	0.02	0.04	0.00			
03GD002	90.52	0.27	0.02	0.04	0.00			

For personal use only



For personal use only

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD002	90.79	0.3	0.02	0.03	0.01			
03GD002	91.09	0.3	0.02	0.03	0.00			
03GD002	91.35	0.3	0.02	0.03	0.01			
03GD002	91.65	0.29	0.02	0.04	0.00			
03GD002	91.94	0.29	0.02	0.04	0.00			
03GD002	92.23	0.06	0.02	0.04	0.00			
03GD002	92.30	0.29	0.02	0.04	0.01			
03GD002	92.60	0.29	0.02	0.03	0.00			
03GD002	92.89	0.3	0.02	0.03	0.00			
03GD002	93.15	0.29	0.02	0.05	0.01			
03GD002	93.45	0.29	0.02	0.03	0.00			
03GD002	93.74	0.3	0.02	0.04	0.00			
03GD002	94.10	0.29	0.02	0.04	0.01			
03GD002	94.40	0.29	0.02	0.04	0.00			
03GD002	94.69	0.3	0.02	0.04	0.00			
03GD002	94.95	0.3	0.02	0.03	0.00			
03GD002	95.25	0.29	0.02	0.04	0.00			
03GD002	95.55	0.29	0.02	0.04	0.00			
03GD002	95.90	0.29	0.02	0.03	0.01			
03GD002	96.20	0.29	0.01	0.03	0.00			
03GD002	96.49	0.3	0.01	0.04	0.00			
03GD002	96.75	0.3	0.01	0.04	0.01			
03GD002	97.05	0.29	0.02	0.04	0.00			
03GD002	97.34	0.3	0.01	0.03	0.00			
03GD002	97.81	0.29	0.01	0.04	0.00			
03GD002	98.19	0.1	0.01	0.04	0.00			
03GD002	98.29	0.3	0.01	0.04	0.00			
03GD002	99.65	0.29	0.01	0.04	0.00			
03GD002	99.95	0.29	0.01	0.03	0.00			
03GD002	100.24	0.29	0.01	0.04	0.00			
03GD002	100.71	0.29	0.02	0.04	0.00			
03GD002	101.00	0.29	0.02	0.04	0.00			
03GD002	101.29	0.3	0.02	0.04	0.00			
03GD002	101.65	0.3	0.02	0.04	0.01			
03GD002	101.95	0.29	0.02	0.04	0.01			
03GD002	102.25	0.29	0.02	0.04	0.00			
03GD002	102.65	0.06	0.00	0.03	0.00			
03GD002	102.72	0.29	0.02	0.03	0.01			



For personal use only

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD002	103.01	0.3	0.02	0.03	0.01			
03GD002	103.40	0.19	0.02	0.03	0.00			
03GD002	103.65	0.29	0.02	0.03	0.00			
03GD002	103.95	0.29	0.02	0.04	0.00			
03GD002	104.25	0.29	0.02	0.03	0.00			
03GD002	104.65	0.06	0.04	0.03	0.01			
03GD002	104.84	0.16	0.02	0.01	0.01			
03GD002	105.00	0.29	0.02	0.01	0.01			
03GD002	105.30	0.29	0.02	0.03	0.01			
03GD002	105.65	0.29	0.02	0.02	0.00			
03GD002	105.95	0.29	0.02	0.02	0.00			
03GD002	106.24	0.09	0.01	0.02	0.00			
03GD002	106.46	0.13	0.02	0.01	0.00			
03GD002	106.70	0.3	0.02	0.02	0.00			
03GD002	107.00	0.29	0.02	0.01	0.00			
03GD002	107.29	0.3	0.02	0.01	0.00			
03GD002	107.65	0.3	0.02	0.02	0.00			
03GD002	107.95	0.29	0.02	0.03	0.01			
03GD002	108.25	0.29	0.02	0.03	0.00			
03GD002	108.84	0.3	0.02	0.03	0.00			
03GD002	109.21	0.08	0.02	0.03	0.00			
03GD002	109.29	0.3	0.02	0.03	0.01			
03GD002	110.05	0.29	0.02	0.03	0.00			
03GD002	110.35	0.29	0.02	0.02	0.00			
03GD002	110.64	0.3	0.02	0.03	0.00			
03GD002	111.00	0.3	0.02	0.04	0.00			
03GD002	111.30	0.29	0.02	0.03	0.00			
03GD002	111.59	0.3	0.02	0.03	0.00			
03GD002	111.85	0.3	0.02	0.03	0.01			
03GD002	112.15	0.17	0.02	0.04	0.00			
03GD002	112.52	0.27	0.02	0.07	0.00			
03GD002	112.80	0.29	0.02	0.03	0.00			
03GD002	113.09	0.3	0.02	0.04	0.00			
03GD002	113.39	0.3	0.02	0.04	0.00			
03GD002	113.65	0.29	0.02	0.03	0.00			
03GD002	113.95	0.29	0.02	0.03	0.01			
03GD002	114.24	0.29	0.02	0.04	0.01			
03GD002	114.55	0.05	0.02	0.03	0.01			



Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD002	114.61	0.29	0.02	0.03	0.00			
03GD002	114.91	0.29	0.02	0.04	0.00			
03GD002	115.28	0.21	0.02	0.03	0.00			
03GD002	115.45	0.3	0.02	0.03	0.00			
03GD002	115.75	0.29	0.02	0.03	0.00			
03GD002	116.05	0.29	0.02	0.03	0.01			
03GD002	116.40	0.3	0.02	0.04	0.00			
03GD002	116.70	0.29	0.02	0.03	0.00			
03GD002	117.00	0.29	0.02	0.04	0.00			
03GD002	117.25	0.29	0.01	0.03	0.00			
03GD002	117.55	0.29	0.02	0.04	0.00			
03GD002	117.84	0.3	0.02	0.04	0.00			
03GD002	118.50	0.29	0.02	0.04	0.01			
03GD002	118.79	0.3	0.02	0.03	0.01			
03GD002	118.95	0.3	0.02	0.04	0.01			
03GD002	119.25	0.29	0.02	0.03	0.01			
03GD002	119.55	0.29	0.02	0.03	0.01			
03GD002	119.95	0.09	0.02	0.03	0.00			
03GD002	120.13	0.17	0.02	0.03	0.01			
03GD002	120.30	0.29	0.02	0.03	0.01			
03GD002	120.59	0.3	0.02	0.03	0.00			
03GD002	120.95	0.29	0.02	0.04	0.01			
03GD002	121.25	0.29	0.02	0.04	0.01			
03GD002	121.54	0.3	0.02	0.04	0.01			
03GD002	122.00	0.29	0.02	0.03	0.00			
03GD002	122.30	0.29	0.02	0.04	0.00			
03GD002	122.60	0.29	0.02	0.04	0.00			
03GD002	122.95	0.09	0.02	0.03	0.01			
03GD002	123.14	0.29	0.02	0.03	0.00			
03GD002	123.43	0.29	0.02	0.03	0.00			
03GD002	123.73	0.16	0.01	0.03	0.01			
03GD002	123.99	0.12	0.01	0.03	0.00			
03GD002	124.12	0.29	0.01	0.04	0.00			
03GD002	124.42	0.29	0.01	0.04	0.00			
03GD002	124.78	0.11	0.01	0.03	0.00			
03GD002	124.95	0.3	0.01	0.03	0.00			
03GD002	125.25	0.29	0.01	0.03	0.00			
03GD002	25.00	0.95	0.13	0.14	0.01	0.02	0.02	0.02

For personal use only



For personal use only

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD002	25.95	0.10	1.00	0.51	0.20			
03GD002	26.05	0.95	0.06	0.04	0.01			
03GD002	27.00	1	0.15	0.10	0.01	0.01	0.01	0.02
03GD002	28.00	1	0.11	0.18	0.01	0.01	0.01	0.04
03GD002	29.00	1	0.13	0.22	0.01	0.03	0.03	0.08
03GD002	30.00	1	0.09	0.15	0.01	0.04	0.03	0.03
03GD002	31.00	1	0.07	0.08	0.01	0.06	0.03	0.04
03GD002	32.00	1	0.09	0.06	0.01	0.06	0.03	0.02
03GD002	33.00	1	0.07	0.09	0.01	0.03	0.04	0.03
03GD002	34.00	1	0.12	0.07	0.01	0.06	0.05	0.02
03GD002	35.00	1	0.06	0.09	0.01	0.03	0.04	0.02
03GD002	36.00	1	0.03	0.04	0.00	0.01	0.01	0.01
03GD002	37.00	1	0.04	0.01	0.00	0.01	0.01	0.00
03GD002	38.00	1	0.04	0.03	0.01			
03GD002	39.00	1	0.04	0.06	0.01			
03GD002	40.00	1	0.05	0.07	0.01			
03GD002	41.00	1	0.06	0.05	0.01	0.01	0.01	0.02
03GD002	42.00	1	0.09	0.05	0.01	0.04	0.05	0.02
03GD002	43.00	1	0.07	0.02	0.01	0.02	0.01	0.00
03GD002	44.00	1	0.07	0.02	0.01	0.01	0.01	0.00
03GD002	45.00	1	0.08	0.03	0.01	0.03	0.04	0.02
03GD002	46.00	1	0.08	0.02	0.01	0.02	0.02	0.01
03GD002	47.00	1	0.08	0.02	0.01	0.01	0.01	0.01
03GD002	48.00	1	0.08	0.02	0.01	0.02	0.01	0.01
03GD002	49.00	1	0.08	0.02	0.01	0.02	0.01	0.01
03GD003	2.55	0.29	0.01	0.01	0.00			
03GD003	2.85	0.29	0.01	0.02	0.00			
03GD003	3.14	0.3	0.01	0.00	0.00			
03GD003	3.60	0.3	0.01	0.01	0.00			
03GD003	3.90	0.29	0.01	0.02	0.00			
03GD003	4.19	0.3	0.01	0.02	0.00			
03GD003	4.55	0.22	0.01	0.02	0.00			
03GD003	4.80	0.3	0.00	0.00	0.00			
03GD003	5.10	0.3	0.01	0.01	0.00			
03GD003	5.40	0.09	0.01	0.02	0.00			
03GD003	5.55	0.07	0.00	0.01	0.00			
03GD003	5.62	0.3	0.01	0.01	0.00			
03GD003	5.92	0.3	0.01	0.01	0.00			



Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD003	6.22	0.27	0.01	0.01	0.00			
03GD003	6.55	0.27	0.01	0.01	0.00			
03GD003	6.82	0.29	0.01	0.00	0.00			
03GD003	7.12	0.16	0.01	0.01	0.00			
03GD003	7.38	0.11	0.01	0.01	0.00			
03GD003	7.60	0.29	0.01	0.01	0.00			
03GD003	7.90	0.29	0.01	0.01	0.00			
03GD003	8.20	0.29	0.01	0.01	0.00			
03GD003	8.55	0.3	0.01	0.01	0.00			
03GD003	8.85	0.29	0.01	0.01	0.00			
03GD003	9.15	0.29	0.01	0.01	0.00			
03GD003	9.60	0.29	0.01	0.01	0.00			
03GD003	9.90	0.29	0.01	0.02	0.00			
03GD003	10.19	0.3	0.01	0.01	0.00			
03GD003	10.55	0.27	0.00	0.01	0.00			
03GD003	10.82	0.3	0.01	0.00	0.00			
03GD003	11.12	0.29	0.01	0.01	0.00			
03GD003	11.41	0.08	0.01	0.01	0.00			
03GD003	11.66	0.24	0.01	0.02	0.00			
03GD003	11.90	0.29	0.01	0.01	0.00			
03GD003	12.19	0.3	0.01	0.01	0.00			
03GD003	12.75	0.3	0.01	0.01	0.00			
03GD003	13.05	0.27	0.01	0.01	0.00			
03GD003	13.32	0.29	0.01	0.01	0.00			
03GD003	13.62	0.07	0.01	0.00	0.00			
03GD003	13.80	0.29	0.01	0.01	0.00			
03GD003	14.10	0.29	0.01	0.01	0.00			
03GD003	14.39	0.3	0.02	0.03	0.00			
03GD003	14.75	0.23	0.01	0.02	0.00			
03GD003	15.16	0.29	0.01	0.01	0.00			
03GD003	15.45	0.24	0.01	0.02	0.00			
03GD003	15.80	0.29	0.01	0.02	0.00			
03GD003	16.10	0.29	0.01	0.02	0.00			
03GD003	16.40	0.29	0.01	0.01	0.00			
03GD003	16.75	0.03	0.01	0.01	0.00			
03GD003	16.84	0.29	0.01	0.01	0.00			
03GD003	17.14	0.29	0.01	0.02	0.00			
03GD003	17.43	0.24	0.01	0.03	0.00			

For personal use only



For personal use only

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD003	17.83	0.27	0.01	0.01	0.00			
03GD003	18.10	0.29	0.01	0.00	0.00			
03GD003	18.39	0.3	0.01	0.02	0.00			
03GD003	18.75	0.29	0.01	0.02	0.00			
03GD003	19.05	0.29	0.01	0.02	0.00			
03GD003	19.35	0.29	0.01	0.00	0.00			
03GD003	19.80	0.29	0.01	0.02	0.00			
03GD003	20.10	0.29	0.01	0.01	0.00			
03GD003	20.39	0.3	0.01	0.01	0.00			
03GD003	20.75	0.3	0.01	0.02	0.00			
03GD003	21.05	0.29	0.01	0.02	0.00			
03GD003	21.34	0.3	0.01	0.01	0.00			
03GD003	21.92	0.3	0.01	0.02	0.00			
03GD003	22.22	0.29	0.02	0.03	0.00			
03GD003	22.59	0.1	0.01	0.03	0.00			
03GD003	22.75	0.3	0.01	0.03	0.00			
03GD003	23.05	0.29	0.01	0.01	0.00			
03GD003	23.35	0.29	0.02	0.03	0.00			
03GD003	23.80	0.3	0.01	0.01	0.00			
03GD003	24.10	0.29	0.01	0.01	0.00			
03GD003	24.39	0.3	0.01	0.02	0.00			
03GD003	24.75	0.29	0.01	0.00	0.00			
03GD003	25.05	0.29	0.01	0.01	0.00			
03GD003	25.34	0.3	0.01	0.02	0.00			
03GD003	25.80	0.3	0.01	0.01	0.00			
03GD003	26.10	0.29	0.00	0.00	0.00			
03GD003	26.40	0.29	0.01	0.01	0.00			
03GD003	26.75	0.3	0.01	0.02	0.00			
03GD003	27.05	0.29	0.01	0.03	0.00			
03GD003	27.35	0.28	0.01	0.01	0.00			
03GD003	27.80	0.29	0.01	0.01	0.00			
03GD003	28.10	0.29	0.01	0.01	0.00			
03GD003	28.39	0.3	0.00	0.02	0.00			
03GD003	28.75	0.3	0.01	0.01	0.00			
03GD003	29.05	0.11	0.02	0.04	0.00			
03GD003	29.25	0.3	0.01	0.02	0.00			
03GD003	29.55	0.14	0.01	0.00	0.00			
03GD003	29.80	0.29	0.01	0.01	0.00			



Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD003	30.10	0.29	0.00	0.01	0.00			
03GD003	30.39	0.3	0.01	0.02	0.00			
03GD003	30.75	0.29	0.01	0.03	0.00			
03GD003	31.05	0.29	0.01	0.01	0.00			
03GD003	31.35	0.29	0.01	0.02	0.00			
03GD003	31.85	0.29	0.01	0.01	0.00			
03GD003	32.10	0.29	0.01	0.02	0.00			
03GD003	32.15	0.29	0.01	0.02	0.00			
03GD003	32.40	0.29	0.01	0.01	0.00			
03GD003	32.45	0.29	0.01	0.01	0.00			
03GD003	32.85	0.16	0.01	0.01	0.00			
03GD003	33.09	0.11	0.00	0.00	0.00			
03GD003	33.20	0.29	0.01	0.01	0.00			
03GD003	33.50	0.29	0.01	0.01	0.00			
03GD003	33.85	0.3	0.01	0.01	0.00			
03GD003	34.15	0.3	0.00	0.01	0.00			
03GD003	34.45	0.29	0.01	0.00	0.00			
03GD003	34.90	0.29	0.01	0.01	0.00			
03GD003	35.20	0.29	0.01	0.01	0.00			
03GD003	35.49	0.3	0.01	0.01	0.00			
03GD003	35.65	0.29	0.01	0.01	0.00			
03GD003	35.95	0.18	0.01	0.02	0.00			
03GD003	36.20	0.29	0.01	0.01	0.00			
03GD003	36.50	0.09	0.01	0.02	0.00			
03GD003	36.90	0.29	0.01	0.01	0.00			
03GD003	37.20	0.29	0.00	0.00	0.00			
03GD003	37.50	0.29	0.01	0.01	0.00			
03GD003	37.85	0.29	0.01	0.01	0.00			
03GD003	38.15	0.26	0.00	0.01	0.00			
03GD003	38.41	0.27	0.00	0.01	0.00			
03GD003	38.68	0.11	0.01	0.01	0.00			
03GD003	38.67	0.29	0.00	0.00	0.00			
03GD003	38.96	0.29	0.01	0.01	0.00			
03GD003	39.32	0.27	0.01	0.02	0.00			
03GD003	39.85	0.29	0.02	0.07	0.01			
03GD003	40.15	0.29	0.01	0.02	0.00			
03GD003	40.44	0.3	0.01	0.03	0.00			
03GD003	41.40	0.29	0.04	0.12	0.01			

For personal use only



ASX:KRM

Suite 5 CPC, 145 Stirling Highway, Nedlands Western Australia 6009 • ABN 49 112 389 910

E: info@kingsrose.com T: +61 8 9389 3190 W: kingsrose.com

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD003	41.65	0.29	0.05	0.13	0.01			
03GD003	41.70	0.29	0.01	0.09	0.00			
03GD003	41.95	0.29	0.05	0.10	0.01			
03GD003	42.24	0.3	0.02	0.04	0.01			
03GD003	42.58	0.15	0.03	0.06	0.01			
03GD003	42.74	0.29	0.05	0.08	0.01			
03GD003	43.45	0.3	0.03	0.06	0.01			
03GD003	43.75	0.29	0.03	0.06	0.01			
03GD003	44.40	0.29	0.02	0.05	0.01			
03GD003	44.70	0.29	0.02	0.06	0.01			
03GD003	44.99	0.3	0.04	0.08	0.01			
03GD003	45.25	0.04	0.03	0.07	0.01			
03GD003	45.34	0.3	0.03	0.07	0.01			
03GD003	45.64	0.29	0.03	0.07	0.01			
03GD003	46.01	0.18	0.02	0.06	0.01			
03GD003	46.20	0.3	0.02	0.06	0.01			
03GD003	46.50	0.29	0.02	0.05	0.01			
03GD003	46.79	0.3	0.02	0.04	0.00			
03GD003	47.45	0.3	0.03	0.07	0.01			
03GD003	47.75	0.23	0.03	0.08	0.01			
03GD003	48.07	0.29	0.03	0.07	0.01			
03GD003	48.50	0.29	0.03	0.07	0.01			
03GD003	48.80	0.29	0.03	0.07	0.00			
03GD003	49.09	0.3	0.02	0.05	0.01			
03GD003	49.45	0.27	0.02	0.06	0.01			
03GD003	49.72	0.3	0.02	0.06	0.01			
03GD003	50.02	0.3	0.03	0.07	0.01			
03GD003	50.32	0.07	0.03	0.08	0.01			
03GD003	50.61	0.29	0.02	0.05	0.01			
03GD003	50.95	0.1	0.05	0.13	0.01			
03GD003	50.90	0.3	0.02	0.05	0.01			
03GD003	51.12	0.27	0.02	0.04	0.01			
03GD003	51.27	0.12	0.02	0.07	0.00			
03GD003	51.40	0.29	0.01	0.02	0.01			
03GD003	51.69	0.2	0.02	0.03	0.00			
03GD003	52.00	0.29	0.01	0.02	0.00			
03GD003	52.30	0.29	0.02	0.03	0.00			
03GD003	52.59	0.3	0.02	0.02	0.01			

For personal use only



For personal use only

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD003	52.75	0.29	0.01	0.02	0.00			
03GD003	53.05	0.29	0.02	0.03	0.01			
03GD003	53.34	0.3	0.02	0.02	0.00			
03GD003	53.85	0.01	0.03	0.06	0.01			
03GD003	53.95	0.25	0.04	0.09	0.01			
03GD003	54.20	0.29	0.03	0.07	0.01			
03GD003	54.49	0.3	0.04	0.09	0.01			
03GD003	55.05	0.3	0.04	0.09	0.01			
03GD003	55.35	0.27	0.03	0.08	0.01			
03GD003	55.62	0.3	0.03	0.08	0.01			
03GD003	55.92	0.07	0.04	0.09	0.01			
03GD003	56.00	0.3	0.03	0.09	0.01			
03GD003	56.30	0.29	0.03	0.07	0.01			
03GD003	56.35	0.3	0.02	0.06	0.01			
03GD003	56.59	0.3	0.03	0.06	0.01			
03GD003	56.77	0.29	0.02	0.04	0.00			
03GD003	57.06	0.23	0.02	0.03	0.00			
03GD003	58.15	0.29	0.04	0.11	0.01			
03GD003	58.45	0.27	0.05	0.15	0.01			
03GD003	58.51	0.29	0.02	0.04	0.00			
03GD003	58.72	0.27	0.02	0.06	0.01			
03GD003	58.80	0.29	0.02	0.05	0.01			
03GD003	58.99	0.1	0.01	0.06	0.00			
03GD003	59.10	0.29	0.03	0.09	0.01			
03GD003	59.15	0.27	0.03	0.09	0.01			
03GD003	59.42	0.27	0.02	0.05	0.01			
03GD003	59.69	0.3	0.02	0.05	0.01			
03GD003	60.55	0.27	0.02	0.04	0.01			
03GD003	60.82	0.27	0.02	0.06	0.01			
03GD003	61.09	0.3	0.02	0.06	0.01			
03GD003	61.39	0.1	0.02	0.04	0.00			
03GD003	61.50	0.3	0.02	0.04	0.01			
03GD003	61.80	0.29	0.02	0.04	0.01			
03GD003	62.10	0.29	0.02	0.04	0.01			
03GD003	62.35	0.3	0.03	0.07	0.01			
03GD003	62.65	0.29	0.02	0.04	0.01			
03GD003	62.95	0.29	0.02	0.03	0.01			
03GD003	63.25	0.07	0.01	0.02	0.00			



Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD003	63.32	0.27	0.02	0.04	0.01			
03GD003	63.60	0.29	0.02	0.03	0.00			
03GD003	63.89	0.3	0.02	0.04	0.01			
03GD003	64.15	0.3	0.02	0.04	0.00			
03GD003	64.45	0.29	0.02	0.03	0.00			
03GD003	64.74	0.3	0.02	0.03	0.00			
03GD003	67.40	0.29	0.02	0.03	0.00			
03GD003	67.70	0.29	0.02	0.04	0.00			
03GD003	67.99	0.3	0.02	0.04	0.00			
03GD003	68.35	0.29	0.02	0.03	0.00			
03GD003	68.65	0.29	0.02	0.03	0.00			
03GD003	69.04	0.25	0.02	0.04	0.00			
03GD003	69.40	0.3	0.02	0.03	0.00			
03GD003	69.70	0.29	0.02	0.03	0.00			
03GD003	70.00	0.29	0.02	0.05	0.01			
03GD003	70.35	0.3	0.02	0.04	0.00			
03GD003	70.65	0.29	0.02	0.05	0.01			
03GD003	70.95	0.29	0.02	0.04	0.01			
03GD003	71.05	0.29	0.02	0.04	0.00			
03GD003	71.25	0.1	0.02	0.03	0.00			
03GD003	71.35	0.29	0.02	0.03	0.00			
03GD003	71.43	0.16	0.02	0.03	0.01			
03GD003	71.60	0.29	0.02	0.03	0.00			
03GD003	71.65	0.29	0.02	0.03	0.00			
03GD003	71.70	0.29	0.02	0.06	0.01			
03GD003	71.89	0.3	0.02	0.04	0.00			
03GD003	72.00	0.29	0.02	0.04	0.01			
03GD003	72.25	0.21	0.05	0.12	0.01			
03GD003	72.54	0.29	0.03	0.10	0.01			
03GD003	72.83	0.29	0.02	0.03	0.00			
03GD003	73.13	0.06	0.02	0.03	0.00			
03GD003	73.35	0.25	0.02	0.03	0.00			
03GD003	73.70	0.29	0.02	0.02	0.00			
03GD003	73.99	0.3	0.02	0.02	0.00			
03GD003	74.85	0.3	0.02	0.03	0.00			
03GD003	75.15	0.29	0.01	0.02	0.00			
03GD003	75.44	0.12	0.01	0.02	0.00			
03GD003	75.64	0.15	0.01	0.02	0.00			

For personal use only



For personal use only

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD003	75.60	0.3	0.02	0.03	0.00			
03GD003	75.90	0.29	0.02	0.03	0.00			
03GD003	76.20	0.29	0.01	0.02	0.00			
03GD003	76.45	0.3	0.01	0.03	0.00			
03GD003	76.75	0.29	0.02	0.03	0.00			
03GD003	77.04	0.3	0.02	0.03	0.00			
03GD003	77.65	0.23	0.02	0.04	0.01			
03GD003	77.89	0.29	0.02	0.03	0.01			
03GD003	78.35	0.17	0.02	0.02	0.00			
03GD003	78.29	0.3	0.02	0.02	0.00			
03GD003	78.58	0.29	0.01	0.02	0.00			
03GD003	78.88	0.29	0.02	0.03	0.00			
03GD003	79.17	0.12	0.02	0.03	0.00			
03GD003	79.69	0.3	0.02	0.03	0.00			
03GD003	79.85	0.3	0.02	0.03	0.00			
03GD003	79.99	0.3	0.02	0.03	0.00			
03GD003	80.15	0.29	0.02	0.03	0.00			
03GD003	80.44	0.29	0.01	0.02	0.00			
03GD003	80.85	0.29	0.02	0.03	0.00			
03GD003	81.21	0.28	0.02	0.03	0.00			
03GD003	81.49	0.3	0.02	0.03	0.00			
03GD003	81.85	0.29	0.02	0.02	0.00			
03GD003	82.15	0.29	0.02	0.03	0.00			
03GD003	82.44	0.3	0.02	0.04	0.00			
03GD003	82.90	0.3	0.02	0.03	0.00			
03GD003	83.20	0.29	0.02	0.03	0.00			
03GD003	83.50	0.29	0.02	0.03	0.00			
03GD003	83.85	0.29	0.02	0.02	0.00			
03GD003	84.15	0.29	0.02	0.03	0.01			
03GD003	84.44	0.29	0.02	0.04	0.00			
03GD003	84.74	0.05	0.02	0.03	0.00			
03GD003	84.90	0.29	0.02	0.03	0.00			
03GD003	85.20	0.29	0.02	0.03	0.00			
03GD003	85.49	0.3	0.02	0.03	0.00			
03GD003	85.85	0.3	0.02	0.03	0.00			
03GD003	86.15	0.29	0.02	0.03	0.00			
03GD003	86.44	0.3	0.02	0.03	0.00			
03GD003	86.89	0.29	0.02	0.02	0.00			



For personal use only

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD003	87.26	0.29	0.01	0.03	0.00			
03GD003	87.63	0.16	0.01	0.02	0.00			
03GD003	87.85	0.29	0.02	0.03	0.00			
03GD003	88.15	0.29	0.01	0.02	0.00			
03GD003	88.44	0.29	0.01	0.02	0.00			
03GD003	88.73	0.06	0.01	0.02	0.00			
03GD003	89.20	0.29	0.02	0.02	0.00			
03GD003	89.49	0.3	0.01	0.03	0.00			
03GD003	90.55	0.3	0.02	0.05	0.00			
03GD003	90.85	0.29	0.02	0.03	0.01			
03GD003	91.15	0.29	0.02	0.04	0.00			
03GD003	91.55	0.05	0.02	0.03	0.00			
03GD003	91.61	0.29	0.02	0.03	0.00			
03GD003	91.90	0.29	0.02	0.04	0.00			
03GD003	92.20	0.29	0.02	0.04	0.00			
03GD003	92.55	0.3	0.02	0.03	0.01			
03GD003	92.85	0.29	0.01	0.02	0.00			
03GD003	93.55	0.1	0.01	0.03	0.00			
03GD003	93.90	0.29	0.02	0.02	0.00			
03GD003	94.19	0.3	0.00	0.02	0.00			
03GD003	94.35	0.08	0.01	0.03	0.00			
03GD003	94.47	0.29	0.01	0.02	0.00			
03GD003	94.77	0.27	0.02	0.04	0.00			
03GD003	95.04	0.25	0.02	0.04	0.00			
03GD003	95.25	0.25	0.02	0.05	0.01			
03GD003	95.50	0.29	0.03	0.06	0.01			
03GD003	95.80	0.29	0.02	0.07	0.00			
03GD003	96.45	0.3	0.02	0.03	0.00			
03GD003	96.75	0.29	0.02	0.04	0.01			
03GD003	97.05	0.29	0.01	0.02	0.00			
03GD003	97.80	0.3	0.02	0.03	0.00			
03GD003	98.10	0.29	0.02	0.04	0.00			
03GD003	98.39	0.3	0.02	0.04	0.00			
03GD003	99.05	0.3	0.02	0.02	0.00			
03GD003	99.35	0.29	0.02	0.04	0.01			
03GD003	99.65	0.29	0.02	0.03	0.00			
03GD003	100.40	0.29	0.02	0.03	0.00			
03GD003	100.69	0.3	0.01	0.03	0.00			



Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD003	100.75	0.3	0.02	0.03	0.00			
03GD003	101.05	0.29	0.02	0.03	0.00			
03GD003	101.35	0.18	0.02	0.03	0.00			
03GD003	101.60	0.09	0.01	0.03	0.00			
03GD003	101.80	0.3	0.02	0.03	0.00			
03GD003	102.10	0.29	0.02	0.03	0.00			
03GD003	102.40	0.29	0.02	0.03	0.00			
03GD003	102.75	0.3	0.02	0.03	0.01			
03GD003	103.05	0.29	0.02	0.04	0.01			
03GD003	103.35	0.29	0.02	0.04	0.01			
03GD003	103.81	0.29	0.02	0.03	0.01			
03GD003	104.10	0.29	0.02	0.04	0.00			
03GD003	104.40	0.29	0.01	0.02	0.00			
03GD003	104.75	0.29	0.02	0.03	0.00			
03GD003	105.05	0.29	0.02	0.03	0.00			
03GD003	105.35	0.29	0.02	0.03	0.00			
03GD003	105.80	0.29	0.01	0.02	0.00			
03GD003	106.10	0.29	0.01	0.01	0.00			
03GD003	106.39	0.3	0.01	0.02	0.00			
03GD003	106.75	0.3	0.02	0.03	0.00			
03GD003	107.05	0.29	0.02	0.03	0.00			
03GD003	107.35	0.25	0.02	0.03	0.01			
03GD003	107.80	0.29	0.02	0.03	0.01			
03GD003	108.10	0.29	0.02	0.03	0.00			
03GD003	108.39	0.3	0.02	0.03	0.00			
03GD003	108.75	0.29	0.02	0.03	0.00			
03GD003	109.05	0.29	0.02	0.03	0.00			
03GD003	109.34	0.29	0.02	0.03	0.00			
03GD003	109.90	0.29	0.02	0.03	0.01			
03GD003	110.20	0.29	0.02	0.04	0.00			
03GD003	110.35	0.29	0.02	0.03	0.00			
03GD003	110.56	0.13	0.01	0.03	0.00			
03GD003	110.65	0.29	0.02	0.03	0.00			
03GD003	110.94	0.3	0.03	0.04	0.01			
03GD003	111.40	0.29	0.02	0.03	0.00			
03GD003	111.70	0.29	0.02	0.03	0.00			
03GD003	111.99	0.3	0.02	0.04	0.00			
03GD003	112.35	0.3	0.02	0.03	0.00			

For personal use only



Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD003	112.65	0.29	0.02	0.03	0.00			
03GD003	112.94	0.28	0.02	0.03	0.00			
03GD003	113.40	0.29	0.02	0.03	0.00			
03GD003	113.70	0.29	0.02	0.02	0.00			
03GD003	113.99	0.3	0.02	0.02	0.00			
03GD003	114.35	0.3	0.02	0.03	0.00			
03GD003	114.65	0.29	0.02	0.03	0.00			
03GD003	114.95	0.29	0.02	0.03	0.00			
03GD003	115.40	0.29	0.02	0.02	0.00			
03GD003	115.70	0.29	0.02	0.03	0.00			
03GD003	115.99	0.3	0.02	0.03	0.00			
03GD003	116.35	0.29	0.02	0.03	0.00			
03GD003	116.65	0.29	0.02	0.03	0.00			
03GD003	116.95	0.29	0.02	0.03	0.00			
03GD003	117.40	0.29	0.02	0.03	0.00			
03GD003	117.70	0.29	0.02	0.04	0.00			
03GD003	117.99	0.3	0.02	0.03	0.00			
03GD003	118.35	0.29	0.02	0.04	0.00			
03GD003	118.65	0.15	0.01	0.03	0.00			
03GD003	118.88	0.29	0.01	0.03	0.00			
03GD003	119.70	0.29	0.02	0.03	0.00			
03GD003	119.99	0.3	0.02	0.03	0.00			
03GD003	120.05	0.3	0.02	0.03	0.00			
03GD003	120.35	0.29	0.02	0.03	0.00			
03GD003	120.65	0.29	0.02	0.03	0.00			
03GD003	121.05	0.07	0.02	0.04	0.00			
03GD003	121.12	0.29	0.02	0.04	0.00			
03GD003	121.42	0.29	0.02	0.04	0.00			
03GD003	121.80	0.19	0.01	0.02	0.00			
03GD003	122.05	0.3	0.02	0.03	0.00			
03GD003	122.35	0.29	0.02	0.02	0.00			
03GD003	122.65	0.29	0.02	0.04	0.00			
03GD003	123.10	0.3	0.02	0.03	0.00			
03GD003	123.40	0.29	0.02	0.03	0.00			
03GD003	123.65	0.17	0.02	0.03	0.00			
03GD003	123.69	0.3	0.02	0.03	0.00			
03GD003	123.89	0.29	0.02	0.03	0.00			
03GD003	124.19	0.29	0.02	0.03	0.00			

For personal use only



For personal use only

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD003	124.48	0.11	0.02	0.04	0.01			
03GD003	124.70	0.29	0.02	0.03	0.00			
03GD003	125.00	0.29	0.02	0.02	0.00			
03GD003	125.30	0.29	0.02	0.03	0.00			
03GD003	127.05	0.06	0.02	0.03	0.01			
03GD003	127.21	0.29	0.02	0.04	0.00			
03GD003	127.51	0.29	0.02	0.03	0.00			
03GD003	39.90	1.1	0.11	0.31	0.01	0.04	0.09	0.05
03GD003	41.00	1.0	0.14	0.12	0.01			
03GD003	42.00	1	0.12	0.06	0.01			
03GD003	43.00	1	0.07	0.03	0.01			
03GD003	44.00	1	0.08	0.02	0.01	0.02	0.02	0.00
03GD003	45.00	1	0.08	0.03	0.01	0.04	0.04	0.01
03GD003	46.00	1	0.07	0.03	0.01	0.02	0.01	0.00
03GD003	47.00	1	0.06	0.03	0.01	0.03	0.03	0.03
03GD003	48.00	1	0.06	0.02	0.01	0.01	0.01	0.01
03GD003	49.00	1	0.09	0.09	0.01	0.08	0.07	0.02
03GD003	50.00	1	0.06	0.03	0.01	0.01	0.01	0.01
03GD003	51.00	1	0.03	0.01	0.01			
03GD003	52.00	1	0.01	0.03	0.00			
03GD003	53.00	1	0.03	0.03	0.01			
03GD003	54.00	1	0.06	0.07	0.01	0.02	0.02	0.02
03GD003	55.00	1	0.06	0.03	0.00	0.06	0.05	0.01
03GD003	56.00	1	0.08	0.03	0.01	0.03	0.03	0.01
03GD003	57.00	1	0.07	0.02	0.01	0.01	0.01	0.00
03GD003	58.00	1	0.11	0.08	0.01	0.06	0.06	0.02
03GD003	59.00	1	0.12	0.09	0.01	0.06	0.07	0.03
03GD003	60.00	1	0.08	0.06	0.01	0.04	0.05	0.02
03GD003	61.00	1	0.09	0.06	0.01	0.05	0.05	0.01
03GD003	62.00	1	0.10	0.05	0.01	0.04	0.04	0.01
03GD003	63.00	1	0.07	0.02	0.01	0.01	0.01	0.01
03GD003	64.00	1	0.07	0.02	0.01	0.01	0.01	0.00
03GD003	65.00	1	0.07	0.02	0.01	0.01	0.01	0.00
03GD003	66.00	1	0.07	0.02	0.01	0.01	0.01	0.00
03GD003	67.00	1	0.07	0.02	0.01	0.01	0.01	0.00
03GD003	68.00	1	0.07	0.01	0.01	0.01	0.01	0.00
03GD003	69.00	1	0.07	0.02	0.01	0.01	0.01	0.00
03GD003	70.00	1	0.08	0.02	0.01	0.02	0.01	0.00



For personal use only

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
03GD003	71.00	1	0.07	0.01	0.01	0.01	0.01	0.00
03GD003	72.00	1	0.12	0.03	0.01	0.02	0.02	0.00
03GD003	73.00	1	0.07	0.01	0.01	0.02	0.01	0.00
03GD003	74.00	1	0.05	0.02	0.01	0.01	0.01	0.00
03GD003	75.00	1	0.07	0.01	0.01	0.01	0.01	0.00
03GD003	76.00	1	0.08	0.01	0.01	0.02	0.01	0.01
03GD003	77.00	1	0.08	0.01	0.01	0.01	0.01	0.00
03GD003	78.00	1	0.07	0.01	0.01	0.01	0.01	0.00
03GD003	79.00	1	0.07	0.01	0.01	0.01	0.01	0.00
DDH1E	0.00	1	0.18	0.11				
DDH1E	1.00	1	0.15	0.04				
DDH1E	2.00	1	0.09	0.06				
DDH1E	3.00	1	0.12	0.09				
DDH1E	4.00	1	0.14	0.09				
DDH1E	5.00	1	0.25	0.17				
DDH1E	6.00	1	0.30	0.20				
DDH1E	7.00	1	0.34	0.22				
DDH1E	8.00	1	0.23	0.14				
DDH1E	9.00	1	0.21	0.14				
DDH1E	10.00	1	0.08	0.05				
DDH1E	11.00	1	0.12	0.07				
DDH1E	12.00	1	0.10	0.07				
DDH1E	13.00	1	0.12	0.07				
DDH1E	14.00	1	0.17	0.09				
DDH1E	15.00	1	0.19	0.11				
DDH1E	16.00	1	0.14	0.09				
DDH1E	17.00	1	0.39	0.24				
DDH1E	18.00	1	0.63	0.37				
DDH1E	19.00	1	0.47	0.26				
DDH1W	0.00	1	0.53	0.33				
DDH1W	1.00	1	0.45	0.27				
DDH1W	2.00	1	0.25	0.14				
DDH1W	3.00	1	0.10	0.07				
DDH1W	4.00	1	0.10	0.07				
DDH1W	5.00	1	0.08	0.05				
DDH1W	6.00	1	0.08	0.05				
DDH1W	7.00	2	0.05	0.03				
DDH1W	9.00	1	0.07	0.04				



ASX:KRM

Suite 5 CPC, 145 Stirling Highway, Nedlands Western Australia 6009 • ABN 49 112 389 910

E: info@kingsrose.com T: +61 8 9389 3190 W: kingsrose.com

For personal use only

Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
DDH1W	10.00	1	0.07	0.04				
DDH1W	11.00	1	0.06	0.03				
DDH2	0.00	2	0.08	0.05				
DDH2	2.00	2	0.08	0.05				
DDH2	4.00	1	0.13	0.08				
DDH2	5.00	1	0.36	0.21				
DDH2	6.00	1	0.47	0.25				
DDH2	7.00	1	0.45	0.23				
DDH2	8.00	1	0.31	0.19				
DDH2	9.00	1	0.20	0.11				
DDH2B	0.00	2	0.16	0.10				
DDH2B	2.00	1	0.37	0.21				
DDH2B	3.00	1	0.27	0.16				
DDH2C	3.00	1	0.27	0.16				
DDH2C	4.00	Unknown	0.37	0.21				
DDH2C	4.00	Unknown	0.16	0.10				
DDH5	60.10	1.1	0.30	0.14				
DDH5	61.20	0.6	0.10	0.06				
DDH5	63.70	0.7	0.41	0.24				
DDH5	64.40	0.8	0.35	0.20				
DDH5	65.20	0.9	0.21	0.09				
DDH5	66.10	1.1	0.09	0.05				
DDH5	67.20	0.8	0.07	0.04				
DDH5	68.00	0.7	0.10	0.07				
DDH5	68.70	0.6	0.09	0.07				
DDH5	69.30	0.7	0.12	0.06				
DDH5	70.00	1.2	0.17	0.09				
DDH5	71.20	0.9	0.24	0.14				
DDH5	72.10	1.2	0.23	0.14				
DDH5	73.30	1	0.30	0.17				
DDH5	74.30	0.5	0.18	0.11				
DDH5	74.80	0.4	0.11	0.05				
DDH5	75.20	0.6	0.07	0.03				
DDH5	60.00	1	0.11	0.11	0.01	0.07	0.06	0.04
DDH5	61.00	1	0.07	0.04	0.01	0.08	0.08	0.04
DDH5	62.00	1	0.07	0.05	0.01	0.06	0.04	0.03
DDH5	63.00	1	0.17	0.13	0.01	0.11	0.10	0.06
DDH5	64.00	1	0.16	0.15	0.01	0.13	0.11	0.08



Hole ID	From (m)	Interval (m)	Ni (%)	Cu (%)	Co (%)	Pt (ppm)	Pd (ppm)	Au g/t
DDH5	65.00	1	0.17	0.08	0.01	0.16	0.16	0.03
DDH5	66.00	1	0.08	0.03	0.01	0.05	0.05	0.01
DDH5	67.00	1	0.06	0.03	0.01	0.03	0.02	0.02
DDH5	68.00	1	0.07	0.05	0.01	0.04	0.03	0.01
DDH5	69.00	1	0.10	0.07	0.01	0.09	0.09	0.03
DDH5	70.00	1	0.11	0.07	0.01	0.11	0.11	0.03
DDH5	71.00	1	0.08	0.05	0.01	0.07	0.06	0.02
DDH5	72.00	1	0.10	0.08	0.01	0.10	0.11	0.04
DDH5	73.00	1	0.16	0.13	0.01	0.23	0.29	0.07
DDH5	74.00	1	0.11	0.08	0.01	0.12	0.10	0.03
DDH5	75.00	1	0.08	0.04	0.01	0.03	0.03	0.01
DDH5	76.00	1	0.07	0.03	0.01	0.03	0.01	0.01
DDH5	77.00	1	0.06	0.03	0.01	0.02	0.01	0.01
DDH5	78.00	1	0.07	0.03	0.01	0.01	0.01	0.01
DDH5	79.00	1	0.07	0.02	0.01	0.01	0.01	0.01
DDH6	34.60	0.4	0.14	0.01	0.03			
DDH6	34.90	0.07	0.13	0.01	0.01			
DDH6	35.00	0.1	0.23	0.02	0.01			
DDH6	35.00	0.4	0.14	0.01	0.03			
DDH6	54.00	1	0.14	0.01	0.03			
DDH6	54.40	0.2	0.15	0.01	0.01			
DDH6	55.50	0.1	0.23	0.01	0.01			
DDH6	69.90	0.1	0.14	0.01	0.01			
DDH7	57.85	0.15	0.01	0.01	0.00			
DDH7	58.00	0.1	0.01	0.00	0.00			
DDH7	141.30	0.7	0.23	0.11	0.03			
DDH7	141.80	Unknown	0.25	0.10	0.01			
DDH7	142.00	1	0.13	0.15	0.03			
DDH7	142.55	Unknown	0.20	0.14	0.03			
DDH7	144.50	Unknown	0.45	1.31	0.03			
DDH7	148.00	1	0.15	0.02	0.01			

For personal use only

