



BLACK CANYON

ASX: BCA

8 October 2025

Wandanya Reports Highest Manganese Grades From The Northern Drill Lines

- Assay results from the first 56 of 148 holes drilled in the Phase 3 RC drill program, **confirm consistent shallow, thick and high-grade mineralisation**
- Intervals reported from the northern drill sections represent some of the highest grades and thickest intervals encountered with **multiple holes averaging above 35% Mn**
- Significant Phase 3 manganese assay results include:
 - **7m @ 37.7% Mn** from surface inc. **3m @ 42.6% Mn** from 4m (WDRC164)
 - **8m @ 37.4% Mn** from surface inc. **3m @ 41.9% Mn** from 4m (WDRC165)
 - **8m @ 35.5% Mn** from surface inc. **3m @ 48.3% Mn** from 5m (WDRC166)
 - **6m @ 39.3% Mn** from 6m inc. **3m @ 47.3%** from 9m (WDRC188)
 - **7m @ 31.3% Mn** from 8m inc. **3m @ 48.4% Mn** from 11m (WDRC190)
 - **9m @ 35.1% Mn** from 7m inc. **3m @ 39.1% Mn** from 13m (WDRC212)
 - **5m @ 38.1% Mn** from 13m inc. **3m @ 44.1% Mn** from 15m (WDRC219)
 - **4m @ 37.2% Mn** from 10m inc. **2m @ 43.9%** from 11m (WDRC221)
 - **4m @ 38.4% Mn** from 9m inc. **2m @ 48.1% Mn** from 11m (WDRC222)
- These results **confirm manganese mineralisation along 3km of strike** with cross strike widths ranging between 160m and 500m, **remaining open to the north, south and east.**
- Significant Phase 3 iron assay results include:
 - **8m @ 58.6% Fe** from surface (WDRC157)
 - **10m @ 61.3% Fe** from surface (WDRC158)
 - **8m @ 59.6% Fe** from 2m (WDRC159)
- RC drilling has defined outcropping to shallow iron mineralisation along the western ridge over **1 kilometre of strike**, confirming iron mineralisation widths between 170m to 320m, **remaining open to the north.**
- Assays from the remaining 92 drillholes targeting high-grade iron and manganese are expected to be received through October to early November 2025.
- A diamond drill program for metallurgical testwork sample is expected to commence this quarter.

Contact

35 Richardson Street West Perth, WA, 6005
E info@blackcanyon.com.au
W www.blackcanyon.com.au

Capital Structure (ASX: BCA)

Shares on Issue	158.8M
14c Options (exp 14/10/2026)	6.3M
Top 20 Shareholders	45%
Board & Management	8%
Funds & Institutions	28%

Board of Directors

Graham Ascough
Non-Executive Chairman

Brendan Cummins
Managing Director

Simon Taylor
Non-Executive Director

Adrian Hill
Non-Executive Director

Wandanya Project

High-grade Mn & Fe discovery

Balfour Manganese Field

Global MRE 314Mt @10.5% Mn*
Largest Resource in Western Australia

*BCA Announcement 12/12/23



Australian manganese explorer and developer, Black Canyon Limited (**Black Canyon** or **the Company**) is pleased to announce first assay results from the Phase 3 RC drilling^{1,2} program at Wandanya. The results confirm the scale potential of the Wandanya Project (BCA 100%) with consistent thickness, high-grades and geology of the shallow stratabound manganese mineralisation encountered over at least a 3km strike.

Black Canyon’s Managing Director Brendan Cummins said:

“The Phase 3 drill results from Wandanya continue to impress with consistent intervals of high-grade manganese along 3km of strike and further high-grade iron has also been confirmed with these assay results. Both the manganese and iron remain open to the north with widespread cross width mineralisation logged and assayed on the northern most drill lines ranging between 400 and 500m.

“Significantly, the drilling success rate remains very high with 55 of the 56 holes reported in this release all intersecting high-grade manganese or iron. The intervals reported from the northern sections represent some of the highest grades and thickest intervals encountered with multiple holes averaging above 35% Mn and several footwall intervals above 45% Mn.

“There remains substantial upside along strike to the north where the iron mineralisation continues to form a prominent ridge for at least another 3km with the potential for manganese mineralisation down dip. To the south, the W2 Prospect outcrops of manganese have been mapped intermittently over 1km and provide strong targets to further expand the mineralisation footprint.

“The consistency, grade and scale potential of Wandanya continue to be key features of this discovery since completion of the first drill program in September 2024. We look forward to receiving the remaining Phase 3 results and building on this exploration success, as we continue to define and expand the footprint of this important discovery.”



Figure 1. Drill lines looking to the east extending for approximately 2km along the Wandanya Discovery




Figure 2. Cross section 7,526,300mN looking to the north showing the location of RC drill holes with shallow high-grade iron and manganese mineralisation (4x Vertical Exaggeration).

Manganese Assay Results

Phase 3 RC drilling completed at Wandanya totalled 148 holes for 3,838m of drilling with drill line spacing ranging between 100m, 200m and up to 300m, and hole centres at 40m. Total drill meterage for the Wandanya project since commencement is 6,777m for 284 drill holes with an average drill depth of only 24m.

Assay results and associated quality control/assurance (QAQC) data has been received and approved for holes WDRRC137 to WDRRC169, WDRRC187 to WDRRC190 and WDRRC209 to WDRRC222, which are primarily manganese targeted drill holes. Results for the remaining 92 drillholes are expected through October until early November.

Drilling has defined manganese mineralisation along 3km of strike from the southern boundary of the tenement. The Phase 3 drill program extended the mineralisation to the north a further 1km from the drilling completed in Phase 2. The latest assay results confirm the lateral continuity of the stratabound manganese mineralisation with drilled cross-strike widths between 400m and 500m and the mineralisation remains open to the east on multiple lines.

The shallow, higher grade mineralisation is associated with thick intervals of manganese oxide, while further to the east the shallow dipping stratabound mineralisation transitions to manganese carbonate.

Iron Assay Results

At the conclusion of the Phase 3 drill program iron mineralisation was logged along 1km of strike with drill holes along 6 cross lines indicating mineralisation widths of 160 to 200m and intersects between 2m to 12m thickness. Mapping to the north has identified iron mineralisation extending over 3km from the most northern drill line completed by the Company.

Cross-sections and drill plans are presented in Figures 2-5. Significant manganese and iron assay results are presented in Table 1 and all assay results are presented in Appendix 2.

Table 1. Significant assay results from the August 2025 Phase 3 drill program.

HOLE ID	E_GDA94	N_GDA94	RL	EOH	DIP	AZIMUTH	DRILL INTERSECTION
WDRC137	322742	7524402	400	30	-90	360	3m @ 42% Mn & 2.3% Fe from 18m
WDRC139	322819	7524406	400	30	-90	360	6m @ 27.9% Mn & 2.3% Fe from 21m including 3m @ 37.3% Mn & 1.5% Fe from 23m
WDRC140	322859	7524402	400	34	-90	360	5m @ 24.9% Mn & 2.7% Fe from 25m including 2m @ 36% Mn & 1.5% Fe from 27m
WDRC141	322897	7524400	400	36	-90	360	4m @ 25.5% Mn & 2.1% Fe from 27m
WDRC142	322936	7524398	400	36	-90	360	6m @ 23.4% Mn & 2.7% Fe from 28m
WDRC144	323017	7524400	400	45	-90	360	6m @ 19.6% Mn & 2.6% Fe from 32m
WDRC151	322978	7524102	402	40	-90	360	5m @ 28% Mn & 1.9% Fe from 30m
WDRC152	323017	7524102	402	40	-90	360	4m @ 32% Mn & 1.4% Fe from 33m
WDRC153	323057	7524100	402	45	-90	360	5m @ 26% Mn & 1.9% Fe from 35m
WDRC157	322238	7526304	434	20	-90	360	8m @ 0.1% Mn & 58.6% Fe from 0m
WDRC158	322277	7526300	431	20	-90	360	10m @ 0.4% Mn & 61.3% Fe from 0m
WDRC159	322315	7526301	428	20	-90	360	8m @ 1.7% Mn & 59.6% Fe from 2m
WDRC163	322476	7526298	418	20	-90	360	6m @ 32% Mn & 9.6% Fe from 2m
WDRC164	322519	7526297	416	20	-90	360	7m @ 37.7% Mn & 8.9% Fe from 0m including 3m @ 42.6% Mn & 8.5% Fe from 4m
WDRC165	322557	7526295	414	18	-90	360	8m @ 37.4% Mn & 4.9% Fe from 0m including 3m @ 41.9% Mn & 3.7% Fe from 4m
WDRC166	322597	7526298	413	18	-90	360	8m @ 35.5% Mn & 3.7% Fe from 0m including 3m @ 48.3% Mn & 3.2% Fe from 5m
WDRC167	322639	7526300	412	18	-90	360	7m @ 31.4% Mn & 3.6% Fe from 0m including 3m @ 39.3% Mn & 3.1% Fe from 4m
WDRC168	322680	7526299	411	18	-90	360	8m @ 32.5% Mn & 3.7% Fe from 0m including 3m @ 38.3% Mn & 4.1% Fe from 4m
WDRC169	322718	7526297	409	18	-90	360	4m @ 30.2% Mn & 3.6% Fe from 6m

WDRC187	322681	7526502	411.5	18	-90	360	10m @ 26% Mn & 2.2% Fe from 1m including 4m @ 41.5% Mn & 2.7% Fe from 7m
WDRC188	322720	7526499	411.5	18	-90	360	6m @ 39.3% Mn & 4% Fe from 6m including 3m @ 47.3% Mn & 3.2% Fe from 9m
WDRC189	322758	7526494	410	18	-90	360	3m @ 36.5% Mn & 3.1% Fe from 9m
WDRC190	322799	7526492	409	18	-90	360	7m @ 31.3% Mn & 2.4% Fe from 8m including 3m @ 48.4% Mn & 1.4% Fe from 11m
WDRC212	322799	7525920	410.7	20	-90	360	9m @ 35.1% Mn & 4.4% Fe from 7m including 3m @ 39.1% Mn & 5.5% Fe from 13m
WDRC213	322800	7525957	410	20	-90	360	9m @ 28.1% Mn & 5% Fe from 8m
WDRC215	322799	7526764	414.1	24	-90	360	4m @ 28.1% Mn & 3.3% Fe from 18m
WDRC216	322798	7526721	413.3	24	-90	360	4m @ 31% Mn & 2% Fe from 17m
WDRC217	322801	7526685	412.6	24	-90	360	5m @ 30.2% Mn & 2.6% Fe from 15m
WDRC218	322802	7526641	411.9	24	-90	360	6m @ 29.6% Mn & 3.7% Fe from 13m
WDRC219	322802	7526606	411.3	20	-90	360	5m @ 38.1% Mn & 2.9% Fe from 13m including 3m @ 44.1% Mn & 2.7% Fe from 15m
WDRC220	322801	7526567	410	18	-90	360	4m @ 35.3% Mn & 5.4% Fe from 12m including 2m @ 43.0% Mn & 6.9% Fe from 14m
WDRC221	322799	7526443	408.2	18	-90	360	4m @ 37.2% Mn & 3.7% Fe from 10m including 2m @ 43.9% Mn & 4.1% Fe from 11m
WDRC222	322799	7526401	408	18	-90	360	4m @ 38.4% Mn & 2.6% Fe from 9m including 2m @ 48.1% Mn & 1.9% Fe from 11m




Figure 3. Wandanya significant results from previous drilling and Phase 3 (Solid Red and Blue text boxes). Refer to ASX release 27/08/2025 for further detail².




Figure 4. Cross section 7,524,100mN looking to the north showing the location of RC drill holes with shallow high-grade iron and manganese mineralisation (4x Vertical Exaggeration).




Figure 5. LONG SECTION 322,800mE looking to the east showing the location of RC drill holes with shallow high-grade manganese mineralisation and most northern holed drilled to date (WDRC214) (4x Vertical Exaggeration).

Metallurgical Testwork^{3,4}

Metallurgical testwork completed on W2 stratabound manganese mineralisation has shown composite samples **averaging 30% Mn** can be beneficiated using density-based separation which **achieved a 45% Mn product grade** exceeding the premium 44% Mn benchmark grade (Table 2).

Table 2. Heavy Liquid Separation (HLS) testwork results from the W2 moderate and high-grade composites^{3,4}.

Composite	Sample type	Head grade feed Mn (%)	Size fraction	HLS Results						
				Density Parameter	Mn (%) Conc	Mn Stage Rec (%)	Mn (%) avge Conc	Mn overall Conc rec (%)	Combined Mn (%) Conc	Combined overall Conc rec (%)
WD01LG	RC chip composite	21.2	+1.0mm - 10mm	SG 2.85	39.6	88.6	39.5	77.9	44.8	79.5
			-1.0mm +0.045mm		39.3	93.6				
WD02HG	RC chip composite	41.5	+1.0mm - 10mm	SG 2.85	49.4	99.0	50.1	81		
			-1.0mm +0.045mm		50.8	99.0				

Next Steps

- Remaining assay results for both manganese and iron are expected through October and into early November 2025.
- The logistics to commence a PQ3 diamond drill program for metallurgical testwork is advancing well with drilling expected to be completed this quarter and core to be available for testwork over the wet season.
- A heritage survey was recently completed with another heritage survey planned at the end of November. The heritage surveys are being completed to allow infill and extension drilling to commence as early as possible after the wet season in 2026.

-END-

This announcement has been approved by the Board of Black Canyon Limited.

For further details:

Brendan Cummins
Managing Director

Telephone: +61 400 799 756

Email: brendan.cummins@blackcanyon.com.au

For media and broker enquiries:

Jason Mack
White Noise Communications


Telephone: +61 400 643 799

Email: jason@whitenoisecomms.com

ASX Reference List:

1. ASX Announcement 1 September 2025 – Wandanya Drilling Confirms Manganese along 3km Strike
2. ASX Announcement 27 August 2025 -Thick, high-grade manganese intersects from Wandanya
3. ASX Announcement 11 February 2025 – Metallurgical testwork Delivers 48% to 50% Manganese Concentrates
4. ASX Announcement 16 April 2025 – Higher Manganese Recovery Achieved

About Black Canyon



Black Canyon has consolidated a significant land holding totalling 2,000km² in the underexplored Balfour Manganese Field (BMF) and across the Oakover Basin, in Western Australia.

The Company holds several exploration licenses 100% or under joint venture within the BMF. A Global Mineral Resource (Measured, Indicated & Inferred) of 314 Mt @ 10.4% Mn has been defined across the BMF projects. This MRE comprises 100Mt @ 10.4% Mn (Measured), 150Mt @ 10.1% Mn (Indicated) and 64Mt @ 11.9% Mn (Inferred) – refer to ASX release 12 Dec 2023.

Wandanya Discovery represents a new exploration model on the eastern margin of the Oakover Basin comprising hydrothermal, stratabound high-grade manganese and high-grade iron with significant scale and grade potential.

Manganese continues to have attractive long-term fundamentals where it is essential and non-substitutable in the manufacturing of alloys for the steel industry and a critical mineral in the cathodes of Li-ion batteries.

Compliance Statements

Reporting of Exploration Results and Previously Reported Information

The information in this report that relates to Exploration Results is based on, and fairly represents, information and supporting documentation reviewed by Mr Brendan Cummins, Managing Director of Black Canyon Limited. Mr Cummins is a member of the Australian Institute of Geoscientists, and he has sufficient experience which is relevant to the style of mineralisation and type of deposits under consideration and to the activity which has been undertaken to qualify as a Competent Person as defined in the 2012 Edition of the “Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves”. Mr Cummins consents to the inclusion in this release of the matters based on the information in the form and context in which they appear. Mr Cummins is a shareholder of Black Canyon Limited.

For further information, please refer to ASX announcements dated 14 February 2023, 27 March 2023, June 1 2023, June 14 2023, June 17 2023, July 14 2023, 23 August 2023, 5 September 2023, 26 September 2023, 12 October 2023, 27 November 2023, 12 December 2023, 26 March 2024, and 1 May 2024, 2 July 2024, 21 August 2024, 25 September 2024, 27 September 2024, 8 October 2024, 18 October 2024, 14 November 2024, 27 November 2024, 4 December 2024, 23 December 2024 and 11 February 2025, 1 April 2025, 16 April 2025, 1 May 2025, 30 June 2025 7 July 2025, 7 August 2025, 27 August 2025 and 1 September 2025 which are available from the ASX Announcement web page on the Company’s website.

The Company confirms that it is not aware of any new information or data that materially affects the information included in this release that relate to Exploration Results and, in the case of mineral resource estimates, that all material assumptions and technical parameters underpinning the estimates in the relevant release continue to apply and have not materially changed.

APPENDIX 1: JORC 2012: TABLE 1

Section 1 Sampling Techniques and Data		
Criteria	Explanation	Comment
Sampling techniques	<p>Nature and quality of sampling (eg cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc). These examples should not be taken as limiting the broad meaning of sampling.</p> <p>Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used.</p> <p>Aspects of the determination of mineralisation that are Material to the Public Report. In cases where 'industry standard' work has been done this would be relatively simple (eg 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (eg submarine nodules) may warrant disclosure of detailed information.</p>	<p>Reverse circulation ('RC') was used as the primary drilling technique for the projects.</p> <p>RC cuttings were continuously sampled at 1 m intervals. All drill holes were sampled and logged from surface to end of hole or depth of mineralisation.</p> <p>Drilling completed by Black Canyon has been used for the projects.</p> <p>All drill samples were logged for weathering, colour, lithology and mineralogy.).</p> <p>RC samples were collected and placed in marked green plastic bags in order at each collar position.</p> <p>The 1m interval samples are considered industry standard and representative of the material being tested.</p> <p>There was limited water encountered during the drill program.</p> <p>The drilling and sample techniques are considered representative for the style of mineralisation utilising 1m sample intervals</p> <p>The target sample weight was between 2-3kg which is appropriate for the style of mineralisation</p>
Drilling techniques	<p>Drill type (eg core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (eg core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc).</p>	<p>Black Canyon drilling was completed using RC technique at 90-degree angle to collect 1 m samples as RC chips. Drill diameter is 5.25 inches as per standard RC sizing. A face sampling hammer was used to drill and sample the holes.</p> <p>The Company contracted for the August 2025 drill program was Impact Drilling.</p>

<p><i>Drill sample recovery</i></p>	<p><i>Method of recording and assessing core and chip sample recoveries and results assessed.</i></p> <p><i>Measures taken to maximise sample recovery and ensure representative nature of the samples.</i></p> <p><i>Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.</i></p>	<p><i>The 2025 drill campaign recorded satisfactory drill sample recovery. The sample weights were not recorded on site, but the samples were weighed once received at the laboratory. The samples weights show good overall recoveries with smaller samples weights recorded in the top 1-2m.</i></p> <p><i>During the 2025 drill program the 1m samples were collected from a levelled cone splitter affixed to the side of the drill rig.</i></p> <p><i>It is unlikely the lower weights encountered in the top 1 - 2m of the holes has biased the samples particularly with the style of mineralisation.</i></p> <p><i>The samples were drilled mostly dry minimising sample bias</i></p>
<p><i>Logging</i></p>	<p><i>Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies.</i></p> <p><i>Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc) photography.</i></p> <p><i>The total length and percentage of the relevant intersections logged.</i></p>	<p><i>Geological logs exist for the August 2025 drill program.</i></p> <p><i>Logging of individual 1 metre intervals was completed using logging code dictionary which recorded weathering, colour, lithology and observed commentary to assist with determining manganese mineralisation.</i></p> <p><i>Logging and sampling has been carried out to industry standards.</i></p> <p><i>Drill holes were geologically logged in their entirety, and a reference set of drill chips were collected in 20m interval chip trays for the drill program. The chip trays were all photographed on site at the end of drilling each hole.</i></p> <p><i>All metres drilled were logged</i></p>

<p><i>Sub-sampling techniques and sample preparation</i></p>	<p><i>If core, whether cut or sawn and whether quarter, half or all core taken.</i></p> <p><i>If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled wet or dry.</i></p> <p><i>For all sample types, the nature, quality and appropriateness of the sample preparation technique.</i></p> <p><i>Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples.</i></p> <p><i>Measures taken to ensure that the sampling is representative of the in-situ material collected, including for instance results for field duplicate/second-half sampling.</i></p> <p><i>Whether sample sizes are appropriate to the grain size of the material being sampled.</i></p>	<p><i>The 1m RC samples were gathered by using a levelled cone splitter of the side of the rig.</i></p> <p><i>The samples the subject of this release were submitted to Bureau Veritas who dried the sample for 12 hrs and pulverised the entire sample until 95% passing 105µm. This method is considered appropriate to ensure sample representivity</i></p> <p><i>The samples were dominantly dry.</i></p> <p><i>Black Canyon inserted Certified Reference Material (CRM) at a rate of 1/50, blanks at a rate of 1/50 and field duplicates from the cone splitter at a rate of 1/50 for a total insertion rate of QA/QC materials at 6%</i></p> <p><i>The sub sampling technique and quality control procedures is considered appropriate to ensure sample representivity</i></p> <p><i>The sample size is considered appropriate for the grainsize and style of mineralisation</i></p>
<p><i>Quality of assay data and laboratory tests</i></p>	<p><i>The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total.</i></p> <p><i>For geophysical tools, spectrometers, handheld XRF instruments, etc, the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc.</i></p> <p><i>Nature of quality control procedures adopted (eg standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (ie lack of bias) and precision have been established.</i></p>	<p><i>The samples were submitted to the primary laboratory - Bureau Veritas in Canningvale, WA.</i></p> <p><i>The 2 – 3kg samples were weighed and dried prior to pulverising 100% of the sample 95% passing 105µm.</i></p> <p><i>The sample was then analysed using method XF203 for manganese ores using fusion disc XRF for Fe, SiO₂, Mn, Al₂O₃, TiO₂, P₂O₅, S, MgO, K₂O, CaO and BaO.</i></p> <p><i>Loss on Ignition (LOI) was also measured by Thermo Gravimetric Analysis (TGA)</i></p> <p><i>Review of the quality control results received to date that include CRM, blanks, duplicates show an acceptable level of accuracy (lack of bias) and precision has been achieved.</i></p> <p><i>In addition, Bureau Veritas has undertaken its own internal QAQC checks using CRM, Blanks and pulp duplicates and no issues have been reported or identified.</i></p> <p><i>A selected number of samples will also be submitted to a secondary laboratory for verification</i></p> <p><i>The CP is satisfied that the analysis was completed to an acceptable standard in the context in which the results have been reported.</i></p>

<p><i>Verification of sampling and assaying</i></p>	<p><i>The verification of significant intersections by either independent or alternative company personnel.</i></p> <p><i>The use of twinned holes.</i></p> <p><i>Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.</i></p> <p><i>Discuss any adjustment to assay data.</i></p>	<p><i>Validation of the drilling files (collar, assay and lithology) was undertaken with field and data entry cross checks</i></p> <p><i>Adjustment of elemental oxides to primary element was completed using well known conversion factors.</i></p> <p><i>There were no twin holes at this stage</i></p> <p><i>There has been no adjustment to the assay data</i></p>
<p><i>Location of data points</i></p>	<p><i>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</i></p> <p><i>Specification of the grid system used.</i></p> <p><i>Quality and adequacy of topographic control.</i></p>	<p><i>All drill holes in the project area were surveyed by handheld GPS with an accuracy of +/-5 m. The accuracy of the location of the drill collars is sufficient at this stage of exploration and resource development.</i></p> <p><i>The grid system used: GDA94 / UTM zone 51S.</i></p>
<p><i>Data spacing and distribution</i></p>	<p><i>Data spacing for reporting of Exploration Results.</i></p> <p><i>Whether the data spacing, and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.</i></p> <p><i>Whether sample compositing has been applied.</i></p>	<p><i>The 2025 drilling completed at Wandanya was conducted via a conventional drill grid. The nominal drill spacing was 40 m along east-west traverses and each traverse was spaced between 100 and 350m apart north-south.</i></p> <p><i>The drill spacing is sufficient to establish grade and geological continuity.</i></p> <p><i>No sample compositing has been applied.</i></p>
<p><i>Orientation of data in relation to geological structure</i></p>	<p><i>Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.</i></p> <p><i>If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.</i></p>	<p><i>At Wandanya the drill lines were oriented east-west across the strike of the primary mineralisation trend. The drill holes were completed at 90 degrees (vertical).</i></p> <p><i>At Wandanya the mineralisation is relatively flat lying exhibiting a gentle dip to the east.</i></p> <p><i>The drill grid is assumed to be located both perpendicular to the planar orientation of the key mineralised horizon with no or limited bias introduced with respect to the strike or dip of the mineralised horizon.</i></p>

Sample security	The measures taken to ensure sample security.	<p>The samples were collected into bulka bags, sealed with cable ties and stored on site until the drill program was completed.</p> <p>The samples were then trucked to Perth in one consignment and delivered directly to Bureau Veritas in Canningvale.</p> <p>The bulka bags were inspected and audited by Bureau Veritas who did not report any suspicious or tampered samples.</p>
Audits or reviews	The results of any audits or reviews of sampling techniques and data.	<p>No audits or reviews have taken place on the sampling techniques or data</p> <p>The CP was on site for half of RC drill program and considers the sampling and sub sampling techniques to be equal to industry standard and appropriate for the style of mineralisation and the results being reported</p>

Section 2 – Reporting of Exploration Results

Criteria	Explanation	Comment
Mineral tenement and land tenure status	<p>Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings.</p> <p>The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area.</p>	<p>The Wandanya mineralisation is located within E46/1407 held 100% by Black Canyon Ltd. Tenement E47/1407 was granted on the 11/04/2022 and expires on 10/04/2027</p> <p>The tenement upon which Wandanya is located are subject to a native title agreement with the Karlka Niyaparli Aboriginal Corporation. Archaeologic and Ethnographic heritage surveys have been completed on the Wandanya deposits which has enabled the drilling to be completed. Further Heritage surveys will be required to continue ground disturbing activities beyond the current drill areas.</p> <p>There are no other known impediments to obtaining a licence to operate in the area.</p>
Exploration done by other parties	Acknowledgment and appraisal of exploration by other parties.	<p>No other material historic exploration has been completed on the tenement for manganese on E46/1407.</p> <p>For Wandanya Black Canyon completed a ground reconnaissance exercise in 2023 to map the manganese enrichments and determine down dip upside. The exercise proved significant manganese enrichment throughout the project areas both as outcropping, sub-cropping and as substantial float material. The early reconnaissance groundwork by Black Canyon was used as a basis for the 2023 DDIP survey and the September 2024 and June 2025 RC drilling programmes.</p>
Geology	Deposit type, geological setting and style of mineralisation.	<p>The mineralisation model at Wandanya is preliminary but it appears to be a fault related hydrothermal stratabound deposit. There is likely supergene overprint to the original hydrothermal mineralisation.</p> <p>The mineralisation is located within a sedimentary sequence. From the base to the top of the sequence the geology comprises footwall dolomite, spotted manganese dolomite, massive manganese and manganese dolomite</p>

Criteria	Explanation	Comment
		<p><i>breccia overlain by hangingwall dolomite. The consistency of the mineralisation down dip and along strike has been interpreted to represent fault related, hydrothermal stratabound style of manganese mineralisation. Geothite alteration is common above the manganese zone and hematite was logged within the mineralised zones as jaspilitic bands. Manganese intensity increases towards the base of the sequence.</i></p> <p><i>The overall geological sequence is dipping very shallowly to the east but is also openly folded with a northerly axial plane forming undulating outcrops. Several large north-easterly faults can be identified along strike associated with surface mineralisation.</i></p> <p><i>The hematite iron mineralisation appears to be a thicker up dip lateral equivalent of the manganese, but further drilling and evaluation is required to understand its genesis.</i></p> <p><i>The lithological sequence of the Wandanya project principally consists of the overlying Enachedong Formation carbonates overlying the Stag Arrow Formation sediments from the Proterozoic Manganese Group of the southern Oakover Basin. The mineralisation style at Wandanya is stratabound and maybe associated with hydrothermal fluids replacing a suitable reactive host work at the base of the Enachedong Formation. Faults and structure are considered important features of this style of mineralisation with multiple northeast trending faults visible from surface imagery.</i></p>
<p><i>Drill hole Information</i></p>	<p><i>A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes:</i></p> <ul style="list-style-type: none"> <i>• easting and northing of the drill hole collar</i> <i>• elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar</i> <i>• dip and azimuth of the hole</i> <i>• down hole length and interception depth</i> <i>• hole length.</i> <p><i>If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should</i></p>	<p><i>See drill hole location tables, plans and figures in main body of the release and Appendix 2.</i></p> <p><i>A listing of drill holes and their corresponding coordinates, elevation and depth are listed in Appendix 2.</i></p> <p><i>All drill holes reported that have been finalised and QA/QC checked and approved have been reported in Appendix 2.</i></p>

Criteria	Explanation	Comment
	<p><i>clearly explain why this is the case.</i></p>	
<p><i>Data aggregation methods</i></p>	<p><i>In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (eg cutting of high grades) and cut-off grades are usually Material and should be stated.</i></p> <p><i>Where aggregate intercepts incorporate short lengths of high-grade results and longer lengths of low-grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail.</i></p> <p><i>The assumptions used for any reporting of metal equivalent values should be clearly stated.</i></p>	<p><i>No grade cutting to assays has been undertaken.</i></p> <p><i>Aggregation of samples has been undertaken using simple average calculations for each 1m sample.</i></p> <p><i>Manganese intervals have been reported at 10% Mn cut off allowing 1m internal dilution that enables the total reported grade to be greater than 25% Mn.</i></p> <p><i>Iron intervals have been reported at 50% Mn cut off allowing 1m internal dilution that enables the total reported grade to be greater than 55% Mn.</i></p> <p><i>Assays have been reported as elements</i></p>
<p><i>Relationship between mineralisation widths and intercept lengths</i></p>	<p><i>These relationships are particularly important in the reporting of Exploration Results.</i></p> <p><i>If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported.</i></p> <p><i>If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (eg 'down hole length, true width not known').</i></p>	<p><i>The Wandanya Prospect is mostly flat lying exhibiting a gentle dip of mineralisation to the east and 90-degree (vertical) drill holes considered appropriate.</i></p> <p><i>The drill results reported are interpreted to represent close to true widths of the mineralisation and are reported as down hole length.</i></p>

Criteria	Explanation	Comment
<i>Diagrams</i>	<i>Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported. These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views.</i>	<i>Refer images within the body of this release for further details.</i>
<i>Balanced reporting</i>	<i>Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.</i>	<i>Information considered material to the reader's understanding of the Exploration Results has been reported in the body of the text and significant results have selectively been reported to provide the reader with the potential tenor and widths of the mineralisation.</i> <i>APPENDIX 2- contains the location, drill holes details and assay results as received and QA/QC approved for the August 2025 drill program.</i> <i>Holes denoted with NSR indicated that no significant mineralisation over 10% Mn was detected in that hole.</i>
<i>Other substantive exploration data</i>	<i>Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.</i>	<i>No other substantive exploration has been completed at Wandanya.</i>
<i>Further work</i>	<i>The nature and scale of planned further work (eg tests for lateral extensions or depth extensions or large-scale step-out drilling).</i> <i>Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.</i>	<i>Further RC and Diamond core drilling is required.</i> <i>Gravity surveys might also detect deeper buried mineralisation associated with the underlying sedimentary sequences.</i>

APPENDIX 2: SUMMARY DRILL HOLE COLLAR AND ASSAYS SUMMARIES

HOLE ID	Commodity target	E_GDA94	N_GDA94	RL	EOH	DIP	AZIMUTH	FROM (m)	TO (m)	THICKNESS (m)	Mn (%)	Fe (%)	Drill intersection
WDRC137	Mn	322742	7524402	400	30	-90	360	18	21	3	42.0	2.3	3m @ 42% Mn & 2.3% Fe from 18m
WDRC138	Mn	322778	7524406	400	29	-90	360	21	24	3	27.0	3.7	3m @ 27% Mn & 3.7% Fe from 21m
WDRC139	Mn	322819	7524406	400	30	-90	360	21	27	6	27.9	2.3	6m @ 27.9% Mn & 2.3% Fe from 21m including 3m @ 37.3% Mn & 1.5% Fe from 23m
WDRC140	Mn	322859	7524402	400	34	-90	360	25	30	5	24.9	2.7	5m @ 24.9% Mn & 2.7% Fe from 25m including 2m @ 36% Mn & 1.5% Fe from 27m
WDRC141	Mn	322897	7524400	400	36	-90	360	27	31	4	25.5	2.1	4m @ 25.5% Mn & 2.1% Fe from 27m
WDRC142	Mn	322936	7524398	400	36	-90	360	28	34	6	23.4	2.7	6m @ 23.4% Mn & 2.7% Fe from 28m
WDRC143	Mn	322978	7524396	400	42	-90	360	36	38	2	36.1	1.9	2m @ 36.1% Mn & 1.9% Fe from 36m
WDRC144	Mn	323017	7524400	400	45	-90	360	32	38	6	19.6	2.6	6m @ 19.6% Mn & 2.6% Fe from 32m
WDRC145	Mn	323058	7524399	399	45	-90	360	37	40	3	22.1	2.8	3m @ 22.1% Mn & 2.8% Fe from 37m
WDRC146	Mn	323107	7524401	398	42	-90	360	35	38	3	22.0	3.1	3m @ 22% Mn & 3.1% Fe from 35m
WDRC147	Mn	323144	7524404	399	48	-90	360	36	37	1	29.4	2.7	1m @ 29.4% Mn & 2.7% Fe from 36m
								40	42	2	20.4	2.5	2m @ 20.4% Mn & 2.5% Fe from 40m
WDRC148	Mn	323179	7524400	402	50	-90	360	40	41	1	16.8	3.2	1m @ 16.8% Mn & 3.21% Fe from 40m
								43	44	1	19.7	4.2	1m @ 19.7% Mn & 4.23% Fe from 43m
WDRC149	Mn	322899	7524102	402	30	-90	360	23	27	4	20.6	2.7	4m @ 20.6% Mn & 2.7% Fe from 23m
WDRC150	Mn	322938	7524104	402	36	-90	360	28	31	3	19.5	4.7	3m @ 19.5% Mn & 4.7% Fe from 28m
WDRC151	Mn	322978	7524102	402	40	-90	360	30	35	5	28.0	1.9	5m @ 28% Mn & 1.9% Fe from 30m
WDRC152	Mn	323017	7524102	402	40	-90	360	33	37	4	32.0	1.4	4m @ 32% Mn & 1.4% Fe from 33m
WDRC153	Mn	323057	7524100	402	45	-90	360	35	40	5	26.0	1.9	5m @ 26% Mn & 1.9% Fe from 35m
WDRC154	Mn	323096	7524102	403	48	-90	360	39	43	4	24.4	2.4	4m @ 24.4% Mn & 2.4% Fe from 39m
WDRC155	Mn	323137	7524099	404	48	-90	360	42	46	4	25.1	2.7	4m @ 25.1% Mn & 2.7% Fe from 42m
WDRC156	Mn	323173	7524105	404	54	-90	360	45	48	3	28.4	2.6	3m @ 28.4% Mn & 2.6% Fe from 45m
WDRC157	Fe	322238	7526304	434	20	-90	360	0	8	8	0.1	58.6	8m @ 0.1% Mn & 58.6% Fe from 0m
WDRC158	Fe	322277	7526300	431	20	-90	360	0	10	10	0.4	61.3	10m @ 0.4% Mn & 61.3% Fe from 0m
WDRC159	Fe	322315	7526301	428	20	-90	360	2	10	8	1.7	59.6	8m @ 1.7% Mn & 59.6% Fe from 2m
WDRC160	Fe Mn	322362	7526295	425	20	-90	360	4	10	6	1.2	55.2	6m @ 1.2% Mn & 55.2% Fe from 4m
WDRC161	Fe Mn	322397	7526300	423	30	-90	360	1	3	2	23.1	19.5	2m @ 23.1% Mn & 19.5% Fe from 1m
								4	9	5	0.8	53.4	5m @ 0.8% Mn & 53.4% Fe from 4m
WDRC162		322437	7526296	420	20	-90	360			0			NSR
WDRC163	Fe Mn	322476	7526298	418	20	-90	360	2	8	6	32.0	9.6	6m @ 32% Mn & 9.6% Fe from 2m
								9	12	3	0.9	58.5	3m @ 0.93% Mn & 58.5% Fe from 9m
WDRC164	Fe Mn	322519	7526297	416	20	-90	360	0	7	7	37.7	8.9	7m @ 37.7% Mn & 8.9% Fe from 0m including 3m @ 42.6% Mn & 8.5% Fe from 4m
								7	11	4	1.1	58.0	4m @ 1.1% Mn & 58% Fe from 7m
WDRC165	Mn	322557	7526295	414	18	-90	360	0	8	8	37.4	4.9	8m @ 37.4% Mn & 4.9% Fe from 0m including 3m @ 41.9% Mn & 3.7% Fe from 4m
WDRC166	Mn	322597	7526298	413	18	-90	360	0	8	8	35.5	3.7	8m @ 35.5% Mn & 3.7% Fe from 0m including 3m @ 48.3% Mn & 3.2% Fe from 5m
WDRC167	Mn	322639	7526300	412	18	-90	360	0	7	7	31.4	3.6	7m @ 31.4% Mn & 3.6% Fe from 0m including 3m @ 39.3% Mn & 3.1% Fe from 4m

WDRC168	Mn	322680	7526299	411	18	-90	360	0	8	8	32.5	3.7	8m @ 32.5% Mn & 3.7% Fe from 0m including 3m @ 38.3% Mn & 4.1% Fe from 4m
WDRC169	Mn	322718	7526297	409	18	-90	360	6	10	4	30.2	3.6	4m @ 30.2% Mn & 3.6% Fe from 6m
WDRC170	Mn	322754	7526299	408	18	-90	360			0			Awaiting assays
WDRC171	Mn	322798	7526298	407	18	-90	360			0			Awaiting assays
WDRC172	Mn	322839	7526297	407	18	-90	360			0			Awaiting assays
WDRC173	Mn	322885	7526301	406	24	-90	360			0			Awaiting assays
WDRC174	Mn	322919	7526295	406	24	-90	360			0			Awaiting assays
WDRC175	Mn	322962	7526301	406	28	-90	360			0			Awaiting assays
WDRC176	Fe	322241	7526500	430	18	-90	360			0			Awaiting assays
WDRC177	Fe	322281	7526501	428	18	-90	360			0			Awaiting assays
WDRC178	Fe	322318	7526499	425.5	24	-90	360			0			Awaiting assays
WDRC179	Fe	322358	7526500	422.5	18	-90	360			0			Awaiting assays
WDRC180	Fe	322403	7526492	419	18	-90	360			0			Awaiting assays
WDRC181	Fe Mn	322438	7526503	417	18	-90	360			0			Awaiting assays
WDRC182	Fe Mn	322482	7526498	415	18	-90	360			0			Awaiting assays
WDRC183	Fe Mn	322521	7526500	413.3	18	-90	360			0			Awaiting assays
WDRC184	Fe Mn	322560	7526494	412	18	-90	360			0			Awaiting assays
WDRC185	Mn	322599	7526506	412	18	-90	360			0			Awaiting assays
WDRC186	Mn	322639	7526500	412	18	-90	360			0			Awaiting assays
WDRC187	Mn	322681	7526502	411.5	18	-90	360	1	11	10	26.0	2.2	10m @ 26% Mn & 2.2% Fe from 1m including 4m @ 41.5% Mn & 2.7% Fe from 7m
WDRC188	Mn	322720	7526499	411.5	18	-90	360	6	12	6	39.3	4.0	6m @ 39.3% Mn & 4% Fe from 6m including 3m @ 47.3% Mn & 3.2% Fe from 9m
WDRC189	Mn	322758	7526494	410	18	-90	360	9	12	3	36.5	3.1	3m @ 36.5% Mn & 3.1% Fe from 9m
WDRC190	Mn	322799	7526492	409	18	-90	360	8	15	7	31.3	2.4	7m @ 31.3% Mn & 2.4% Fe from 8m including 3m @ 48.4% Mn & 1.4% Fe from 11m
WDRC191	Mn	322838	7526495	409	20	-90	360			0			Awaiting assays
WDRC192	Mn	322873	7526500	409	24	-90	360			0			Awaiting assays
WDRC193	Fe	322279	7526102	436	18	-90	360			0			Awaiting assays
WDRC194	Fe	322318	7526099	434	18	-90	360			0			Awaiting assays
WDRC195	Fe	322358	7526099	432	18	-90	360			0			Awaiting assays
WDRC196	Fe Mn	322397	7526098	427	24	-90	360			0			Awaiting assays
WDRC197	Fe Mn	322435	7526098	424.8	24	-90	360			0			Awaiting assays
WDRC198	Fe Mn	322475	7526103	422	18	-90	360			0			Awaiting assays
WDRC199	Fe Mn	322522	7526092	419	18	-90	360			0			Awaiting assays
WDRC200	Mn	322560	7526092	416.5	17	-90	360			0			Awaiting assays
WDRC201	Mn	322597	7526086	415	18	-90	360			0			Awaiting assays
WDRC202	Mn	322640	7526100	413	18	-90	360			0			Awaiting assays
WDRC203	Mn	322678	7526100	411.5	18	-90	360			0			Awaiting assays
WDRC204	Mn	322721	7526096	410	18	-90	360			0			Awaiting assays
WDRC205	Mn	322759	7526100	407	18	-90	360			0			Awaiting assays
WDRC206	Mn	322797	7526098	408	20	-90	360			0			Awaiting assays
WDRC207	Mn	322835	7526097	407.9	24	-90	360			0			Awaiting assays

WDRC208	Mn	322880	7526094	407	24	-90	360			0			Awaiting assays
WDRC209	Mn	322919	7526097	406.1	28	-90	360	20	23	3	30.6	3.1	3m @ 30.6% Mn & 3.1% Fe from 20m
WDRC210	Mn	322958	7526098	406	30	-90	360	20	24	4	21.3	2.6	4m @ 21.3% Mn & 2.6% Fe from 20m
WDRC211	Mn	323000	7526097	404.7	30	-90	360	20	23	3	28.3	2.3	3m @ 28.3% Mn & 2.3% Fe from 20m
WDRC212	Mn	322799	7525920	410.7	20	-90	360	7	16	9	35.1	4.4	9m @ 35.1% Mn & 4.4% Fe from 7m including 3m @ 39.1% Mn & 5.5% Fe from 13m
WDRC213	Mn	322800	7525957	410	20	-90	360	8	17	9	28.1	5.0	9m @ 28.1% Mn & 5% Fe from 8m
WDRC214	Mn	322796	7526803	414.7	24	-90	360	18	22	4	21.9	4.7	4m @ 21.9% Mn & 4.7% Fe from 18m
WDRC215	Mn	322799	7526764	414.1	24	-90	360	18	22	4	28.1	3.3	4m @ 28.1% Mn & 3.3% Fe from 18m
WDRC216	Mn	322798	7526721	413.3	24	-90	360	17	21	4	31.0	2.0	4m @ 31% Mn & 2% Fe from 17m
WDRC217	Mn	322801	7526685	412.6	24	-90	360	15	20	5	30.2	2.6	5m @ 30.2% Mn & 2.6% Fe from 15m
WDRC218	Mn	322802	7526641	411.9	24	-90	360	13	19	6	29.6	3.7	6m @ 29.6% Mn & 3.7% Fe from 13m
WDRC219	Mn	322802	7526606	411.3	20	-90	360	13	18	5	38.1	2.9	5m @ 38.1% Mn & 2.9% Fe from 13m including 3m @ 44.1% Mn & 2.7% Fe from 15m
WDRC220	Mn	322801	7526567	410	18	-90	360	12	16	4	35.3	5.4	4m @ 35.3% Mn & 5.4% Fe from 12m including 2m @ 43.0% Mn & 6.9% Fe from 14m
WDRC221	Mn	322799	7526443	408.2	18	-90	360	10	14	4	37.2	3.7	4m @ 37.2% Mn & 3.7% Fe from 10m including 2m @ 43.9% Mn & 4.1% Fe from 11m
WDRC222	Mn	322799	7526401	408	18	-90	360	9	13	4	38.4	2.6	4m @ 38.4% Mn & 2.6% Fe from 9m including 2m @ 48.1% Mn & 1.9% Fe from 11m
WDRC223	Mn	322804	7526365	408	20	-90	360			0			Awaiting assays
WDRC224	Mn	322803	7526242	406	18	-90	360			0			Awaiting assays
WDRC225	Mn	322800	7526205	406.8	18	-90	360			0			Awaiting assays
WDRC226	Mn	322802	7526168	407.4	18	-90	360			0			Awaiting assays
WDRC227	Mn	322801	7526044	408	24	-90	360			0			Awaiting assays
WDRC228	Mn	322799	7525998	409.5	20	-90	360			0			Awaiting assays
WDRC229	Fe	322249	7526605	428	18	-90	360			0			Awaiting assays
WDRC230	Fe	322250	7526562	429	18	-90	360			0			Awaiting assays
WDRC231	Fe	322250	7526526	430	18	-90	360			0			Awaiting assays
WDRC232	Fe	322251	7526483	430	18	-90	360			0			Awaiting assays
WDRC233	Fe	322250	7526444	430	18	-90	360			0			Awaiting assays
WDRC234	Fe	322250	7526398	430	18	-90	360			0			Awaiting assays
WDRC235	Fe	322248	7526364	430	18	-90	360			0			Awaiting assays
WDRC236	Fe	322252	7526318	432	18	-90	360			0			Awaiting assays
WDRC237	Fe	322248	7526286	434	18	-90	360			0			Awaiting assays
WDRC238	Fe	322251	7526244	434	18	-90	360			0			Awaiting assays
WDRC239	Fe	322480	7525702	436	18	-90	360			0			Awaiting assays
WDRC240	Fe	322516	7525701	435	18	-90	360			0			Awaiting assays
WDRC241	Fe	322554	7525700	432	18	-90	360			0			Awaiting assays
WDRC242	Fe	322612	7525695	428	18	-90	360			0			Awaiting assays
WDRC243	Fe	322636	7525695	424	18	-90	360			0			Awaiting assays
WDRC244	Fe	322677	7525696	422	18	-90	360			0			Awaiting assays
WDRC245	Fe Mn	322716	7525698	419	18	-90	360			0			Awaiting assays
WDRC246	Fe Mn	322757	7525700	416	18	-90	360			0			Awaiting assays

WDRC247	Fe Mn	322798	7525698	414	18	-90	360			0			Awaiting assays
WDRC248	Mn	322836	7525698	412	18	-90	360			0			Awaiting assays
WDRC249	Mn	322878	7525697	408	20	-90	360			0			Awaiting assays
WDRC250	Mn	322914	7525703	406	20	-90	360			0			Awaiting assays
WDRC251	Mn	322942	7525691	405	18	-90	360			0			Awaiting assays
WDRC252	Mn	322993	7525701	404	18	-90	360			0			Awaiting assays
WDRC253	Mn	323036	7525701	404	20	-90	360			0			Awaiting assays
WDRC254	Mn	323111	7525697	404	24	-90	360			0			Awaiting assays
WDRC255	Mn	323080	7525697	404	20	-90	360			0			Awaiting assays
WDRC256	Mn	322997	7525597	405	18	-90	360			0			Awaiting assays
WDRC257	Mn	322998	7525639	405	20	-90	360			0			Awaiting assays
WDRC258	Mn	323001	7525673	404	20	-90	360			0			Awaiting assays
WDRC259	Mn	323009	7525760	405	20	-90	360			0			Awaiting assays
WDRC260	Mn	323003	7525798	406	20	-90	360			0			Awaiting assays
WDRC261	Mn	323007	7525837	406	20	-90	360			0			Awaiting assays
WDRC262	Mn	323019	7524005	400	40	-90	360			0			Awaiting assays
WDRC263	Mn	323058	7524001	400	42	-90	360			0			Awaiting assays
WDRC264	Mn	323101	7524005	400	48	-90	360			0			Awaiting assays
WDRC265	Mn	323142	7523996	400	48	-90	360			0			Awaiting assays
WDRC266	Mn	323172	7524005	400	48	-90	360			0			Awaiting assays
WDRC267	Mn	323017	7523901	398	36	-90	360			0			Awaiting assays
WDRC268	Mn	323057	7523896	398	36	-90	360			0			Awaiting assays
WDRC269	Mn	323093	7523899	398	36	-90	360			0			Awaiting assays
WDRC270	Mn	323142	7523901	398	40	-90	360			0			Awaiting assays
WDRC271	Mn	323168	7523905	398	45	-90	360			0			Awaiting assays
WDRC272	Mn	323017	7523806	402	30	-90	360			0			Awaiting assays
WDRC273	Mn	323051	7523807	402	42	-90	360			0			Awaiting assays
WDRC274	Mn	323182	7523813	401	48	-90	360			0			Awaiting assays
WDRC275	Mn	323144	7523808	401	46	-90	360			0			Awaiting assays
WDRC276	Mn	323105	7523810	402	45	-90	360			0			Awaiting assays
WDRC277	Mn	323001	7523760	402	39	-90	360			0			Awaiting assays
WDRC278	Mn	323007	7523876	399	36	-90	360			0			Awaiting assays
WDRC279	Mn	323004	7523960	398	36	-90	360			0			Awaiting assays
WDRC280	Mn	323002	7524075	402	42	-90	360			0			Awaiting assays
WDRC281	Mn	323002	7524198	402	40	-90	360			0			Awaiting assays
WDRC282	Mn	323005	7524276	402	42	-90	360			0			Awaiting assays
WDRC283	Mn	323000	7524361	402	42	-90	360			0			Awaiting assays
WDRC284	Mn	322986	7524436	400	42	-90	360			0			Awaiting assays

Notes.

1. NSR – no significant manganese or iron assay received
2. Awaiting assay – currently being processed by the primary analysis laboratory.